or night, and that the fish were present in small shoals of twelve to twenty fish. A local population density of about 2,000,000 fish per square mile was estimated from the known lens angle and limits of visibility.

	R. E. CRAIG
	R. PRIESTLEY
Scottish Home Department,	
Marine Laboratory,	
Victoria Road,	
/D	

Marine Laboratory, Victoria Road, Torry. Aberdeen.

## Influence of the Organic Matrix on Crystal Type in Molluscs

THE calcium carbonate of molluse shells occurs as calcite in some species, as aragonite in others, and certain species deposit calcite in one portion of the shell and aragonite in another portion. Various explanations have been suggested for the formation of aragonite, which is significantly less stable. Participation of the enzyme carbonic anhydrase and the influence of the protein matrix on which the crystals are deposited have both been suggested<sup>1</sup>. We have investigated the capacity of pieces of decalcified matrix to induce aragonite formation when inserted into a molluse which normally forms only calcite, and also under in vitro conditions in which calcium carbonate is normally precipitated as calcite.

Protein matrix was prepared from shells of the fresh-water clam *Elliptio* complanatus, from the marine fan shell Atrina rigidu, and from the nacreous layer of the Japanese pearl oyster Pinctada martensii by decalcifying with 1 per cent sodium ethylenedia-mine tetraacetate at  $p \neq 5.0$ . In each case the shell from which the matrix was taken was aragonite. Microscopic examination of each piece of matrix showed that all crystalline material had been removed. To make certain that submicroscopic crystals did not remain, some pieces of matrix were treated further with 0.01 N hydrochloric acid. For *in vivo* studies a single piece of decalcified matrix was wrapped around a fragment of glass cover-slip and inserted between the mantle and shell of the oyster Crassostrea virginica, which deposits a calcite shell. The temperature of the water was 19-25° C. The inserted pieces of matrix were removed after various intervals, usually 24 hr., washed thoroughly in deionized water, and the crystals identified under the polarizing microscope. In vitro calcification of matrix was carried out at  $25 \pm 2^{\circ}$  C. in 100 ml. of a calcium bicarbonate solution prepared from reagent grade calcium carbonate in deionized water<sup>2</sup>. Pieces of decalcified matrix were placed in this solution for 25-44 hr., during which time the pH rose from 6.4 to 8.3.

Both in vivo and in vitro, aragonite crystals formed on protein matrix from aragonite shells (Table 1). Calcite crystals were also deposited on the matrix in both cases. The forms of calcite and aragonite crystals were distinct, the former being rhombic or rosetteshaped, and the latter irregular, spherulitic or hexagonal elongate. Aragonite was never found on substrates other than aragonite matrix. Tested substrates and conditions included: (1) glass cover-slip fragments inserted in Crassostrea (25 cases); (2) 'Formplastic inserted in Crassostrea (4 cases); (3) decalvar cified calcito matrix from prismatic layor of Pinclada inserted in Crassostrea (3 cases); and (4) decalcified calcite matrix from prismatic layer of Pinctada tested

October 22, 1960 Vol. 188

Table 1

Test system		Total No. of matrix pieces analysed	No. of matrix pieces with aragonite crystals
	Pinctada martensii	4	2
In vivo	Elliptio complanatus	8	1
	Atrina rigida	5	1* (?)
In vitro	Pinctada martensii	5	2†
	Elliptio complanatus		īt
	Tota	3 1 25	6 or 7

The crystals were clustered and could not be analysed. Their form was irregular and different from calcite crystals.
† Final pH 8-3.
‡ Final pH 7-3.

in vitro (10 cases). Calcite crystals only were deposited in each of these instances.

Even though freshly secreted matrix might normally induce aragonite formation in aragoniteforming molluscs, aragonite induction might well have been prevented in the present experiments by at least three conditions: (1) alteration of the original state of the aragonite matrix; (2) conversion of small aragonite crystals to calcite after deposition; (3) presence of freshly secreted matrix by the calcito-forming host mollusc. The finding of aragonite in approximately one-quarter of the cases (Table 1) is accordingly of a higher frequency than might have been anticipated.

The results point to the protein matrix as a factor determining the crystal type in molluses. At present we have no information on molecular spacing of protein matrix of calcite and aragonite shells which might permit profitable speculation as to possible mechanisms.

This work was aided by a grant from the Office of Naval Research, United States Navy.

> NORIMITSU WATABE KARL M. WILBUR

Department of Zoology, Duke University,

Durham, North Carolina,

Wilbur, K. M., in "Calcification in Biological Systems", Amer. Assoc. Adv. Sci., 15-40, Washington, D.C., 1960.
Reitemeier, R. F., and Buehrer, T. F., J. Phys. Chem., 44, 535 (1940).

## The Skipper (Scomberesox saurus) in the Southern North Sea and the Thames Estuary

THE skipper or saury pike is a pelagic fish of the open Atlantic and Mediterranean, ranging from Tristan da Cunha<sup>1</sup> northwards to the Gulf of Maine and the Bay of Fundy<sup>2</sup> in the western Atlantic, and to Christiana Fjord and Gjesvaer, near the North Cape, in the European Atlantic<sup>3</sup>. On the southern and south-western British coast it is of frequent, if not annual, occurrence, and catches of up to 100,000 have been reported at Mevagissey, Cornwall<sup>4</sup>. Farther north it has often been recorded from the Hebrides, the western Scottish coast and the Shetland and Orkney Islands<sup>5</sup>, but the number of records decreases noticeably on the eastern coast of Scotland. Rae (personal communication) has found a specimen off Buchan Noss, Aberdeenshire (November 21, 1957); one in the Moray Firth (December 18, 1958); a shoal at Saltburn, Cromarty Firth (December 21, 1958); one at May Island, Firth of Forth (December 1, 1958); and one from a cod stomach 12' N. St. Abbs, Berwick (February 18, 1959).