It is not easy to distinguish these two mechanisms, as in one case of an oxidized electrode which exhibited short time-lags, a micro-photograph taken at a magnification of 500 showed that parts of the electrodes could also behave as simple roughened electrodes without any oxide. Hence, it is probable that both mechanisms play a part in producing electron emission, together with auto-electronic emission from any sharp irregularities on the cathode. Department of Physics

Department of Physics, University College, Swansea. Nov. 17.

Paetov, Z. Phys., 140, 770 (1939).
 Druyvesteyn and Penning, Rev. Mod. Phys., 12, 117 (1940).
 Cobine and Easton, J. Appl. Phys., 14, 321 (1943).
 Howell, Elec. Eng., 58, 193 (1939).

Negative Resistance-Temperature Coefficient of Thin Evaporated Films of Bismuth

Evaporated Films of Bismuth In the course of work on vacuum bolometers, it has been noticed that films of bismuth evaporated on to a backing film of celluloid (both with thickness of the order of 1 micron) possessed a negative resistance-temperature coefficient. In order further to study the property, films of bismuth were evaporated on to microscope slides, washed and wiped but not otherwise cleaned. In every case these showed a negative resistance-temperature coefficient, which diminished with increasing thickness of film. The pressure in the evaporation chamber was about 10^{-s} mm. mercury. It should be noted that mercury vapour was present during the evaporation, as a mercury diffusion pump was used without a trap.

trap.

trap. In these circumstances some deposition occurred on the backs of the slides (about 2.5 per cent of that on the front). The values of the coefficient a obtained for the first slide (back and front coats), and for each of four successive coats on the second slide are tabulated below. The values for the second, third and fourth coats separately were calculated from the measurements made of the resistance at each steer, the layers being tracted as indemonstrates in stage, the layers being treated as independent conductors in each parallel.

The values of the coefficient obtained from thin films of other metals, evaporated under similar conditions, are added for comparison. The estimated thicknesses for these indicate only their order of magnitude.

Layer	Estimated mean thickness (microns)	$\alpha (^{\circ}C^{-1} \times 10^{-4})$
Bismuth :		
1st slide : front	~1	-27.7
back	~0.03	-20.8
2nd slide : front		
Laver 1	1.5	-31.2
1+2	3.1	-29.1
1 + 2 + 3	4.7	-23.0
1 + 2 + 3 + 4	6.5	-16.8
2	1.6	-27.0
3	1.6	-13.4
4	1.8	- 8.7
Iron : on glass	~1-5	+19
Nickel : on glass	~1	+16
Lead : on glass	~2	+29
Gold : on celluloid	~2	+11.7

It is clear that such modified values of the coefficient must be re-garded in applying theoretical considerations^{1,8} to the selection of bolometer materials.

T. J. TULLEY.

Physics Department, The Royal Cancer Hospital (Free), London, S.W.3. Nov. 1.

²Baker, E. B., and Robb, C. D., Rev. Sci. Inst., 14, 356 (1943). ²Amdur, I., and Glick, C. F., Rev. Sci. Inst., 16, 117 (1945).

Nomenclature of Triterpene Alcohols

It is true that taraxasterol is a triterpene and not a sterol, but there are many cases of substances the names of which end in '-sterol' which are not steroids—lanosterol, to take but one example—and this suffix has long since ceased to carry with it the implication that the molecule of the compound concerned necessarily contains the cholane skeleton. It is therefore to be hoped that the name 'taraxasterol' will receive general acceptance, on grounds of convention and logic alike, for the designation of this alcohol, which may well be a characteristic triter-pene of the Composite and may thus become of major importance; and that the use of unsuitable synonyms (a-lactucel), a-lactucol, anthesterol) will be discontinued.

J. C. E. SIMPSON.

Department of Chemotherapy, Liverpool School of Tropical Medicine. Nov. 14.

¹ Zimmermann, Helv. Chim. Acta, 28, 127 (1945).
 ² Power and Browning, J. Chem. Soc., 105, 1829 (1914).
 ³ Burrows and Simpson, J. Chem. Soc., 2042 (1938).
 ⁴ Simpson, J. Chem. Soc., 283 (1944).
 ⁵ Power and Browning, J. Chem. Soc., 101, 2411 (1912).

Constitution of the Dianhydrides of Sorbitol and Iditol THE hexahydric alcohols mannitol, sorbitol and iditol all form dianhydro compounds on being heated with acid reagents. These compounds and the problem of their constitution have interested us for some time, and the structure of dianhydro mannitol (known as isomannide in the older literature) has already been proved to be that of 1:4-3:6-dianhydro mannitol¹ (I).



E. Hills Laboratories, University, Edgbaston, Birmingham, 15. Oct. 24.

- ¹ Wiggins, L. F., J. Chem. Soc., 4 (1945).
 ⁸ Fischer, E., and Zach, K., Ber., 45, 456 (1912); Ohle, H., and Erlbach, H., Ber., 62, 2758 (1929).
 ⁹ Haworth, W. N., Owen, L. N., and Smith, F., J. Chem. Soc., 88 (1941).
 ⁴ Fletcher, H. G., and Goepp, R. M., J. Amer. Chem. Soc., 67, 1042 (1945).
- (1945). ⁵ Brigl, P., and Gruner, H., Ber., 67, 1969 (1934).