LETTERS TO THE EDITORS

The Editors do not hold themselves responsible for opinions expressed by their correspondents. No notice is taken of anonymous communications

Measurements on Superconductivity in Thin Tin Films

CONTINUING our previous measurements¹ on superconductivity of thin tin films, we have now measured the change in superconductivity, under the influence

Fig. 1

Fig. 2

of a magnetic field and also under the combined action of the current and a magnetic field.

Our deposits are obtained on small glass strips (length of the film, 5 mm.; width, 3 mm.) by sputtering in argon at room temperature using a cathode of spectrographically pure tin prepared by Johnson Matthey and Co., Ltd. In order to

eliminate oxidation, the films are transported to the cryostat in an evacuated tube belonging to our special transport system. In the cryostat the film is dipped into the liquid helium. Hence it is possible to study the change in superconductivity even when using large current densities without the film being warm.

Just as in our previous measurements, we found that, for our films, the transition temperature is a few tenths of a degree higher than for normal tin. The behaviour of one of our films is described in this communication. The resistance of this film at room

temperature is 116 ohms, at the boiling point of liquid oxygen it is 104 ohms, and at the boiling point of liquid helium 87.8 ohms. The transition temperature is 3.82° K., and after the transition there remains no residual resistance. This film, and also the others, showed a peculiar effect when we measured the disturbance under the influence of the combined action of an external magnetic field and the current. Figs. 1 and 2 illustrate the influence of a field, normal to the surface of the film and parallel to the film (in both cases perpendicular to the current) respectively, for different currents. The following points may be noted:

(1) By increasing the current, the transition curves become more and more sharp. Experiments of the same kind have been carried out by de Haas, Voogd and Jonker² on a monocrystalline tin wire, but they obtained flatter curves when the current was increased.

(2) The critical field for the direction parallel to the film is much larger than for the perpendicular direction. This fact has also been observed recently by Zavaritskii³. Moreover, we observed that even for large values of the current, the magnetic threshold value for the film is considerably greater than for the bulk metal.

(3) In Fig. 1 (inset) R per cent is plotted as a function of $H_{i1} - H_{i2}$, which is the compensating field for the current difference. It is noteworthy that straight lines are obtained.

The same general behaviour was found for this film at other temperatures below the transition temperature, and also for our other films.

We wish to thank the Belgian Department of Education for financial aid for these experiments.

A. VAN ITTERBEEK
L. DE GREVE
L. VAN GERVEN
J. SCHEPERS

Instituut voor Lage Temperaturen
en Technische Physica,
Louvain. Feb. 11.

¹ Van Itterbeek, A., De Greve, L., and Van Gerven, L., *Med. Koninkl. Vl. Academie, Brussels* (in English), 14, No. 5 (1952).

² de Haas, W. J., Voogd, J., and Jonker, J., *Physica*, 1, 281 (1933).

³ Zavaritskii, N. V., *Dokl. Akad. Nauk. S.S.S.R.*, 82, 229 (1952).