Figure 1 Catalytic combustion technology for gas-turbine applications⁶. a, Fuel and compressed air pass through two catalytic stages, in which catalyst materials limit the temperature rise through each stage. The gas exiting the second stage contains unburned fuel and is sufficiently hot to spontaneously combust in the post-catalyst zone, just before entering the gas turbine. b, An end view of the catalyst honeycomb structure. Thin strips of metal foil are coated with a layer of catalyst and configured to create an array of narrow (1-mm) channels. Fuel in the gas mixture diffuses through the layers where the catalytic oxidation occurs, thereby releasing heat. The heat of combustion is then returned to the flowing gas by convection. Finding catalysts that work at the high temperatures required for methane combustion is not easy. Zarur and Ying¹ have developed a promising catalyst that is more stable at temperatures up to 1,300 °C and could be used in a variety of combustion applications.

prevents active particles meeting and fusing together, thereby preserving the high surface area of the catalyst. The activity of such catalysts can be viewed as the product of their intrinsic ability to oxidize methane (rate per unit surface area of the active phase) and their dispersion (active surface area per unit volume). It is therefore desirable to find materials that combine high activity with greater resistance to thermal coarsening and so maintain high combustion rates.

Oxide catalysts based on non-noble metals, such as perovskites and hexaaluminates, are exceptionally resistant to thermal coarsening, but are difficult to prepare as fine powders. Zarur and Ying¹ have found a way round this problem by combining several state-of-the-art synthesis methods to produce porous powders with high surface area — that is, nanometre particle sizes — and resistance to thermal coarsening at high temperatures. These hexaaluminate powders show an interesting level of activity for methane combustion, but the most important use of these materials may be as a matrix to disperse and isolate small particles of other catalysts that are more prone to coarsening. Indeed, Zarur and Ying¹ disperse grains of a moderately active catalyst, ceria (CeO₂), within a microemulsion of their hexaaluminate oxide powders with interesting results. In this system, the highly dis-

persed and surprisingly efficient ceria catalyst helped sustain methane combustion at temperatures as low as 400 °C.

The dispersed ceria catalyst appears to remain stable and active within the limited conditions and lifetime of laboratory experiments, and is perhaps superior to the transition-metal hexaaluminates studied by Arai and colleagues some ten years ago⁵. The new catalyst is perhaps unique in that ceria, a low-volatility oxide previously thought to have low combustion activity, remains active and highly dispersed within the porous hexaaluminate support after extended exposure to combustion conditions at temperatures as high as 1,300 °C. It remains to be seen if this catalyst possesses the combination of thermal stability and combustion activity necessary to succeed as a commercial catalytic combustion technology. But clearly the ceria-hexaaluminate catalyst, or another of many possible variations prepared using this approach, is worth a closer look.

Jon G. McCarty is at Catalytica Combustion Systems, Inc., 430 Ferguson Drive Building 3, Mountain View, California 94043-5272, USA. e-mail: jmccarty@mv.catalytica-inc.com

1. Zarur, A. J. & Ying, J. Y. *Nature* **403**, 65–67 (2000).
2. Berzelius, J. J. *Ann. Chim.* **61**, 146 (1836).
3. Davy, H. *Phil. Trans. R. Soc.* **107**, 45 (1817).
4. Pfeifferle, W. *J. Energy* **2**, 142–146 (1978).
5. Arai, H. & Machida, M. *Catal. Today* **10**, 81–95 (1991).
6. Dalla Betta, R. A. *Catal. Today* **35**, 129–135 (1997).

Daedalus

Depth of insight

Computed axial X-ray tomography is an expensive and cumbersome way to obtain three-dimensional X-ray data. Daedalus wants to do it by stereo photography. In its optical form, this uses two lenses separated by the distance between the eyes; each takes a photograph. These are then presented to the viewer so that each eye can only see its 'own' photograph. The result is a persuasive and most informative image in depth. The method should work perfectly well with two X-ray sources, or just one stepped quickly sideways between successive exposures.

The snag is that an X-ray image is essentially a shadowgraph. A point source of X-rays throws a shadow of the subject, in all its variations of transparency or opacity, onto a sensitive screen. With two sources, the screen would just sum the two exposures, giving a confused muddle. An X-ray stereography screen will have to hold a separate image for each of the sources.

Daedalus recalls those fine filters made by exposing a sheet of base material to a beam of ionizing particles. Each particle leaves a track through the sheet, dense with dislocations, photoelectrons and so on. A selective solvent etches away these disturbed regions, leaving a tiny tunnel where each particle passed.

So DREADCO chemists are now seeking a polymer or light alloy which can be activated and etched by the passage of X-ray photons. It will be placed behind the subject; in front of him will be two X-ray sources, separated by the width between a human interpreter's eyes. Each X-ray source will riddle the plate with tracks aligned with it, and diverging from it. The interpreter will etch the plate, place it against a bright background, and look at it from such a position that his two eyes are where the X-ray sources were. Each eye will see only the light which converges on it through the tunnels in the plate made by the corresponding X-ray source, and aligned with it. He will see a true stereo X-ray image of the subject.

Cheap and simple, stereo X-radiography will transform routine medical imaging. Each exposure will give far more useful data; many tricky interpretational problems will vanish. It could even provide airports with still more intimate insights into their customers' luggage.

David Jones

The further Inventions of Daedalus (Oxford University Press), 148 past Daedalus columns expanded and illustrated, is now on sale. Special *Nature* offer: m.curtis@nature.com