ARTICLE

Received 25 Aug 2015 | Accepted 12 Jun 2016 | Published 18 Jul 2016

DOI: 10.1038/ncomms12214

OPEN

Reversible switching between pressure-induced amorphization and thermal-driven recrystallization in VO₂(B) nanosheets

Yonggang Wang^{1,2}, Jinlong Zhu¹, Wenge Yang^{2,3}, Ting Wen⁴, Michael Pravica¹, Zhenxian Liu⁵, Mingqiang Hou⁵, Yingwei Fei⁵, Lei Kang⁶, Zheshuai Lin⁶, Changqing Jin⁷ & Yusheng Zhao^{1,8}

Pressure-induced amorphization (PIA) and thermal-driven recrystallization have been observed in many crystalline materials. However, controllable switching between PIA and a metastable phase has not been described yet, due to the challenge to establish feasible switching methods to control the pressure and temperature precisely. Here, we demonstrate a reversible switching between PIA and thermally-driven recrystallization of VO₂(B) nanosheets. Comprehensive *in situ* experiments are performed to establish the precise conditions of the reversible phase transformations, which are normally hindered but occur with stimuli beyond the energy barrier. Spectral evidence and theoretical calculations reveal the pressure–structure relationship and the role of flexible VO_x polyhedra in the structural switching process. Anomalous resistivity evolution and the participation of spin in the reversible phase transition are observed for the first time. Our findings have significant implications for the design of phase switching devices and the exploration of hidden amorphous materials.

¹High Pressure Science and Engineering Center, University of Nevada, Las Vegas, Nevada 89154, USA. ²HPSynC, Geophysical Laboratory, Carnegie Institution of Washington, Argonne, Illinois 60439, USA. ³Center for High Pressure Science and Technology Advanced Research (HPSTAR), Pudong, Shanghai 201203, China. ⁴Institute of Nanostructured Functional Materials, Huanghe Science and Technology College, Zhengzhou, Henan 450006, China. ⁵Geophysical Laboratory, Carnegie Institution of Washington, Washington, District of Columbia 20015, USA. ⁶Beijing Centre for Crystal Research and Development, Technical Institute of Physics and Chemistry, Chinese Academy of Sciences, Beijing 100190, China. ⁷National Laboratory for Condensed Matter Physics, Institute of Physics, CAS, Beijing 100190, China. ⁸Southern University of Science and Technology, Shenzhen 518055, China. Correspondence and requests for materials should be addressed to Y.W. (email: yggwang@gmail.com) or to W.Y. (email: yangwg@hpstar.ac.cn) or to Y.Z. (email: zhaoy@sustc.edu.cn).

Materials that contain no long-range structural order (for example, glass or amorphous phase) are fundamentally interesting to both the basic sciences and for practical industrial applications^{1,2}. Glass, which has been considered a metastable and kinetically frozen disordered state, can be synthesized by rapidly quenching a melt from high temperature to prevent crystallization. Another frequently reported but distinct approach to amorphous phases or glasses is via pressure-induced amorphization (PIA)^{3,4}. The disordering process in PIA differs significantly from the thermally-induced disorder in substance melting, where a much higher density is expected. PIA has been observed in many materials such as ice^{5–7}, α -quartz SiO_2 (refs 8–10), AlPO_4 (ref. 11), $\text{R-Al}_5\text{Li}_3\text{Cu}$ (ref. 12), and so on, and is widely accepted as an important condensed matter phenomenon. In some cases, mechanical instability caused by ‘thermodynamic melting’ and increased atomic coordination are considered to contribute most to PIA^{8,13}. While in other cases, such as ZrW_2O_8 , negative thermal expansion (NTE) may have some possible connection with the PIA^{14–17}. However, determining the underlying mechanism still remains one of the most fascinating challenges and some recent evidence even shows that previously reported PIAs were due to the fragmentation of bulky particles into nanocrystals and strongly correlated pressurization environments³. Furthermore, new high-density PIA generated materials are expected to drive new theoretical approaches for modelling this phenomenon, which is essential for discovering their practical applications. Recently, pressure-induced crystallization revealed the topological ordering in metallic glasses at room temperature¹⁸. But upon heating, the recovered amorphous phase tends to return to its stable crystalline phase to minimize the system’s energy, depending on the kinetic barrier it needs to overcome. Such examples include the main group compounds SnI_4 , LiKSO_4 , Ca(OH)_2 , clathrasils and berlinite AlPO_4 (refs 19–23). Molecular dynamics calculations on PIA- AlPO_4 (ref. 23) showed that the presence of non-deformable, fourfold coordinated PO_4 interlinking units in the crystal structure have a crucial role in the reversible amorphization and crystallization phase transition, where they acted as templates around which the original structure and even the original orientation were restored^{23,24}. So far, reversible PIA has only been observed in the above-mentioned main group compounds, where only the lattice participates in the intriguing structure transformation. The study of more variables (that is, charge, spin and orbital) involved in PIA and the subsequent recrystallization processes could potentially allow a more comprehensive understanding of the order–disorder transformation mechanism and the electronic behaviour in highly disordered materials.

Discovering new external-stimuli responsive compounds with switchable ground states is a major objective in material science because these materials often lead to unusual phenomena or useful functionalities^{25,26}. When considering PIA materials as metastable and dense phases distinct from their crystalline forms, it is important to achieve a controllable phase switching between either the PIA glass and their crystalline polymorphisms or even between two PIA phases.

In this work, we report a reversible structural switch between the metastable crystalline phase $\text{VO}_2(\text{B})$ and its PIA glass, in the form of nanosheets. The phase switch between these two metastable phases is realized with low-pressure compression (~ 20 GPa) and relative low-temperature annealing ($\sim 200^\circ\text{C}$). The phase transformation and underlying mechanism is thoroughly studied using *in situ* synchrotron X-ray diffraction (XRD), infrared, Raman spectroscopy and theoretical calculations. High-pressure electronic transport properties and magnetic properties are also studied to provide direct evidence

of the participation of charge and spin during the phase transformation, for the first time. Our findings may provide a new research platform for the exploration of novel amorphous materials and phenomena under controllable external stimuli.

Results

Material and crystal structure. There are several crystalline phases of VO_2 at ambient conditions: $\text{VO}_2(\text{A})$, $\text{VO}_2(\text{B})$, $\text{VO}_2(\text{M})$, $\text{VO}_2(\text{R})$ and other metastable phases^{27–31}. Among them, $\text{VO}_2(\text{M})$ is the thermodynamically stable phase but it undergoes an insulator-to-metal transition (ITM) under high pressure to a metallic phase $\text{VO}_2(\text{R})$ around room temperature. The structures and physical properties of the phases differ significantly due to the distinct coordination environments of V atoms in the VO_x polyhedra, the V^{4+} – V^{4+} interactions and the various cross linking manners (Supplementary Fig. 1). $\text{VO}_2(\text{B})$ is a thermodynamically metastable phase adopting an anisotropic layered structure, and is frequently used as a battery material³². Its unique structural features, such as well-embedded layers and hierarchical V–O bonding, also make $\text{VO}_2(\text{B})$ an interesting candidate for structural stability studies under high pressure. In this work, $\text{VO}_2(\text{B})$ nanosheets were synthesized from high pure V_2O_5 raw material via a hydrothermal route with citric acid as the reducing agent³³. The product consisted of well-shaped nanosheets that were several micrometres in length/width and tens of nanometres in thickness, and its single crystal nature is proven by the well-arranged spots in the selected-area electron diffraction pattern (Fig. 1a,b). The structure of $\text{VO}_2(\text{B})$ is characterized by the layered feature in the *bc* plane with a twofold connected O1 atom between the layers (Fig. 1c). Less electron charge distribution between the layers makes the [100] direction more compressible, and there is also a distinct gap along the [001] direction. Overall, the $\text{VO}_2(\text{B})$ structure has a hierarchical structure consisting of condensed face-sharing VO_x polyhedra. More structural features of $\text{VO}_2(\text{B})$ along different axes are shown in Supplementary Fig. 2.

PIA at room temperature. The *in situ* synchrotron XRD patterns of $\text{VO}_2(\text{B})$ nanosheets, as a function of pressure without pressure transition medium, are shown in Fig. 2a. There was no structural transition until the onset of amorphization around 20 GPa. The XRD pattern at ambient conditions is well-indexed with the monoclinic space group *C2/m* and lattice constants $a = 12.054(3)$ Å, $b = 3.693(1)$ Å, $c = 6.424(2)$ Å and $\beta = 106.96(1)^\circ$, in good agreement with other reported values^{12,13}. As discussed above, from a structural chemistry viewpoint, the $\text{VO}_2(\text{B})$ nanosheet was expected to show an anisotropic compressibility under pressure. The lattice parameters at various pressures before PIA were obtained by Reitveld refinements of these XRD patterns, as shown in Supplementary Fig. 3. During compression, the diffraction peaks became broader and weaker from about 17 GPa, and completely vanished around 20 GPa, indicating the loss of long-range ordering in the pressure-amorphized state. To check the shear and non-hydrostaticity effect on the PIA, we repeated the experiments using neon and helium as pressure-transmitting medium (PTM) for comparison. In all cases, the PIA process occurred and the amorphous PIA- $\text{VO}_2(\text{B})$ was preserved to ambient conditions after releasing pressure. In contrast, no PIA was observed in the thermal-stable $\text{VO}_2(\text{M})$ phase up to 55 GPa³⁴.

Spectroscopic techniques can probe the short-range structural features of local atomic coordinates. We employed infrared and Raman spectroscopy to examine the local structural evolution of $\text{VO}_2(\text{B})$ nanosheets during compression and decompression.

Figure 1 | TEM characterizations and crystal structure of VO₂(B) at ambient pressure. (a) Bright field TEM images of VO₂(B) nanosheets. Scale bar, 2 μm . (b) Selected-area electron diffraction of VO₂(B) nanosheets along the [010] zone axis showing its single crystal nature. Scale bar, 5 nm^{-1} . (c) Crystal structure of VO₂(B) showing a dense packed vanadium-oxygen layer in the bc plane and ac plane with hierarchical V-O bonding. The O1 atoms with shortest V=O bonds are highlighted in green.

Figure 2b displays the infrared spectrum of VO₂(B) as a function of pressure up to 23.6 GPa. Characteristic peaks located around $1,000\text{ cm}^{-1}$ (at ambient conditions) are assigned to the shortest $\text{V}^{4+}=\text{O1}$ bonds pointing perpendicularly into the bc interlayer. The mode frequency barely shifted ($<50\text{ cm}^{-1}$) towards high wave numbers upon compression. However, the broadening of the vibrational mode increases with pressure, and finally merging with other broad bands down to 600 cm^{-1} is a more profound change. These were associated with angle deformations of the VO_x polyhedral upon compression and eventually a disordered state resulted in amorphization. This evidence clearly indicates the nature of the degenerated chemical environments of oxygen around the V^{4+} centres. As pressure increases, the enhanced oxygen coordination around vanadium atoms in VO₂(B) is expected to lead to the dynamical lattice instability, which triggers the PIA. It is interesting that the preserved PIA-VO₂(B) has similar local vibrational modes to the pristine VO₂(B) nanosheets, indicating that the short-range structure features of VO₂(B) are preserved, as indicated in Fig. 2d. Moreover, Raman spectroscopy was employed to evaluate the contribution of the electron-phonon interactions to the PIA phase transition of VO₂(B) (Fig. 2c). At low pressure, only five bands near 198, 260, 570, 780 and $1,020\text{ cm}^{-1}$ were observed with moderate intensity in the VO₂(B) nanosheets. Typically, the peak located at $1,020\text{ cm}^{-1}$ can be assigned to the $\text{V}^{4+}=\text{O1}$ stretching modes of terminal oxygen atoms. Upon compression above 10 GPa, all the bands weakened and finally vanished. Meanwhile, broad bands between 600 and $1,000\text{ cm}^{-1}$ were observed corresponding with the PIA process. As anticipated, similarly to the infrared results, all of the atomic location information was preserved with a more disordered state as indicated by the broadening of the vibrational bands in Fig. 2e, which closely resembles the Raman changes during the ITM process from VO₂(M) to metallic VO₂(R).

Thermal-driven recrystallization and the phase diagram. The PIA-VO₂(B) phase returns to the pristine VO₂(B) structure upon annealing at relatively low temperature ($\sim 200^\circ\text{C}$ by *in situ* annealing experiment) for a short time (~ 5 min). Figure 3 shows the XRD pattern of the starting VO₂(B) nanosheets and PIA-VO₂(B) before and after annealing at 250°C (50°C above the critical temperature to guarantee a complete recrystallization). To ensure that the PIA process was achieved, a higher pressure of 31.5 GPa (far beyond the PIA starting point) was applied. As discussed, the loss of the X-ray diffraction peaks in the recovered PIA-VO₂(B) sample suggests the absence of long-range ordering. After annealing at 250°C in a vacuum environment for 5 min, surprisingly, we noticed that the diffraction pattern from this heat-treated sample showed the same powder characteristic peaks as the VO₂(B) phase with a monoclinic space group $C2/m$, lattice constants $a = 12.065(3)\text{ \AA}$, $b = 3.650(9)\text{ \AA}$, $c = 6.482(11)\text{ \AA}$ and $\beta = 107.53(7)^\circ$ (Supplementary Fig. 4) and a little expanded cell volume ($273.5\text{ \AA}^3$ versus $272.2\text{ \AA}^3$ of the pristine sample). This structure switching phenomenon is distinct from the previously reported reversible PIA phenomena with the following characteristics:^{23,24} (1) In the cases of some so-called ‘memory glasses’, such as AlPO_4 , the PIA phases can be restored to their initial crystalline structures spontaneously at room temperature once pressure is released. In contrast, PIA-VO₂(B) can exist as a metastable, high density, intermediate phase, and the small active energy barrier between PIA-VO₂(B) and crystalline VO₂(B) enables feasible control of the phase switch; (2) The reversible PIA and recrystallization processes are guaranteed to occur between VO₂(B) and PIA-VO₂(B) (except some thermodynamically stable phases such as VO₂(M)), due to the relatively low operating temperature (compression at room temperature and annealing at $\sim 200^\circ\text{C}$). The illustration that dynamically low temperature can hinder both the pressure- and temperature-induced traditional phase transitions indicates that

Figure 2 | Diffraction and spectral evidences for VO₂(B) nanosheets under compression. (a) *In situ* synchrotron XRD patterns of VO₂(B) as a function of pressure show the pressure-induced amorphization happened around 21 GPa. (b) Infrared spectra taken between ambient pressure and 23.6 GPa. (c) Raman spectra taken between 1.4 and 22.7 GPa. (d,e) Detailed infrared and Raman spectra at the starting, highest pressure and recovered states.

Figure 3 | XRD patterns of VO₂(B) nanosheets upon compression and heating. (a) XRD pattern of the pristine VO₂(B) nanosheets; (b) XRD pattern of PIA-VO₂(B) recovered from 31.5 GPa; (c) XRD pattern of PIA-VO₂(B) after annealing at 250 °C in a vacuum for 5 min. Bottom: theoretical Bragg lines of VO₂(B) and VO₂(M). The peaks of (c) are indexed with the monoclinic space group C2/m and lattice constants: $a = 12.065(3)$ Å, $b = 3.650(9)$ Å, $c = 6.482(11)$ Å and $\beta = 107.53(7)^\circ$.

more hidden phase relationships may be discovered at low temperature. (3) Moreover, the crystal structure of VO₂(B) is built up of a 3d metal V⁴⁺ ($S = 1/2$) based framework. Both the atomic coordination preference of the distorted VO_x polyhedra and possible electron/magnetic interactions within the crystal lattice may contribute to the reversible structure transformation.

The latter will be discussed in detail in the electron transport property section.

Recent investigations by more powerful and precise techniques show that PIA is highly related to the pressurization environments and crystallinity of the starting materials. Some of the phenomena previously reported as PIA were likely due to either the formation of multiple polymorphic phases, or even that the PIA process did not occur if single crystal samples were adopted or more hydrostatic compression was applied^{8–10,35}. To check this issue in the VO₂(B) system and obtain the exact conditions where the phase transformations occurred, *in situ* powder XRD experiments were conducted. Firstly, the PIA process of VO₂(B) with different PTMs were evaluated. Figure 4a displays the integrated (110) peak intensity of VO₂(B) as a function of pressure without a PTM or with Ne, He as the PTMs. VO₂(B) nanosheets under all of these three conditions showed the onset of PIA around 10 GPa. Without PTM, the PIA process accomplished concluded around 20 GPa or a little higher when a better hydrostatic pressure condition was given (30 and 35 GPa for neon and helium as PTMs, respectively). This indicates that the PIA of VO₂(B) is somewhat related to the deviatoric stress³⁶, which is reasonable considering the hierarchical structural features of VO₂(B). Fortunately, the value of 20 GPa was low enough to obtain bulk samples using a large volume press apparatus for routine magnetism measurements. Figure 4b shows the (110) peak intensity of PIA-VO₂(B) as a function of the annealing temperature. The recrystallization starts from as low as 100 °C and completes around 200 °C. The relatively low annealing temperature makes the switch between PIA-VO₂(B) and crystalline VO₂(B) feasible. The pressure- and

Figure 4 | Diffraction intensity and phase scheme of $\text{VO}_2(\text{B})$. (a) The integrated (110) peak intensity of $\text{VO}_2(\text{B})$ as a function of pressure under three different compression conditions. (b) The integrated (110) peak intensity of $\text{PIA-VO}_2(\text{B})$ as a function of the annealing temperature. The error bars in (b) indicate the s.d. values of the integrated peak intensity at a given pressure. (c) Density-energy scheme of the VO_2 system and the reversible structure switching. Blue and red arrows show the thermally allowed phase transitions between $\text{VO}_2(\text{B})$ and $\text{PIA-VO}_2(\text{B})$; The black arrow shows the dynamically hindered transition from $\text{VO}_2(\text{B})$ to $\text{VO}_2(\text{M})$ under compression.

temperature-induced phase transformations of $\text{VO}_2(\text{B})$ nanosheets observed in our work are summarized schematically in Fig. 4c with other known VO_2 crystalline phases. Under compression at room temperature, the expected phase transformation from metastable $\text{VO}_2(\text{B})$ to thermodynamically stable $\text{VO}_2(\text{M})$ does not occur. This indicates a higher kinetic barrier ($E_{\text{barrier}2}$) of atomic diffusion, and the large surface energy from the nanosheets at room temperature. The formed high-density $\text{PIA-VO}_2(\text{B})$ returned to the pristine metastable $\text{VO}_2(\text{B})$ structure after short-time annealing at relatively low temperature (250–300 °C, 10 min), instead of transforming to the thermodynamically stable $\text{VO}_2(\text{M})$ phase. This indicates a relatively low kinetic barrier transforming to metastable $\text{VO}_2(\text{B})$ compared with the high crystallization energy associated with the $\text{VO}_2(\text{M})$ phase and demonstrate that hidden structural switching can be realized using a compression and heating route, as shown in Fig. 4c. Such an intriguing phase transition is the first ever example observed in a 3d metal involved material. Similar structure switching behaviour was observed in PbTe nanoparticles³⁷, but in our case the switching between two thermally metastable phases was highly dependent on the temperature parameter. We believe that the key factor enabling this reversible phase transformation is the temperature, which is kinetically low enough for sufficient atomic mobility, which thus causes the elastic deformation of the structure. However, when the annealing temperature was high enough to surpass the $\text{VO}_2(\text{B})$ to $\text{VO}_2(\text{M})$ phase transition temperature (~ 550 °C)³³, the $\text{PIA-VO}_2(\text{B})$ can also transfer to $\text{VO}_2(\text{M})$ via the intermediate $\text{VO}_2(\text{B})$ phase.

First-principles calculation of the pressure-phase relationship.

The experimental results evidently show the pressure- and thermal-controlled structure switching of $\text{VO}_2(\text{B})$ nanosheets. To provide further thermodynamic and kinetic insight into the pressure-phase relationship during the phase transformation, we performed density functional theory (DFT) simulations using CASTEP code³⁸. Detailed calculation information is provided in the Supplementary Materials. Total energy calculations demonstrate that $\text{VO}_2(\text{M})$ is the most stable phase of VO_2

Figure 5 | Pressure-volume equations of state of VO_2 phases. Squares present the simulated results based on DFT calculations of $\text{VO}_2(\text{A})$, $\text{VO}_2(\text{B})$, $\text{VO}_2(\text{M})$ and $\text{VO}_2(\text{R})$ upon compression up to 60 GPa; asterisks are the experimental data of the $\text{VO}_2(\text{B})$ nanosheets. The equation of state of $\text{VO}_2(\text{B})$ nanosheets has the parameters: zero-pressure volume $V_0 = 34.325 \text{ \AA}^3$ per VO_2 , bulk modulus $B_0 = 129.1 \text{ GPa}$ and bulk modulus pressure derivative $B'_0 = 4$.

under ambient pressure at room temperature, and that $\text{VO}_2(\text{M})$ and $\text{VO}_2(\text{R})$ have a higher density than $\text{VO}_2(\text{A})$ and $\text{VO}_2(\text{B})$ (Supplementary Fig. 5). Upon compression up to 100 GPa, $\text{VO}_2(\text{B})$ was thermodynamically metastable compared with $\text{VO}_2(\text{M})$ and $\text{VO}_2(\text{R})$. However, no crystal-to-crystal phase

transition from $\text{VO}_2(\text{B})$ to $\text{VO}_2(\text{M})$ or $\text{VO}_2(\text{R})$ was observed, due to the high-kinetic energy barrier between them at room temperature. Figure 5 shows both the calculated pressure–volume equations of states of the four crystalline VO_2 phases and the experimental data of $\text{VO}_2(\text{B})$ nanosheets upon compression. The experimental data of the $\text{VO}_2(\text{B})$ nanosheets exhibit a larger unit cell volume than those theoretically predicted, which is reasonable considering the nanosheet surface defects. This large cell volume falls into the traditional VO_2 glass region. Upon compressing to around 20 GPa, the $\text{VO}_2(\text{B})$ nanosheets passed through the ideal pressure–volume boundary of $\text{VO}_2(\text{B})$ and became amorphous with a higher density. The stable region of PIA- $\text{VO}_2(\text{B})$ is indicated in Fig. 5, which passed between $\text{VO}_2(\text{B})$ and $\text{VO}_2(\text{M})$ under high pressure. Several possibilities have been proposed for the underlying mechanism of a PIA process, such as the mechanical instability beyond the Born stability conditions and ‘thermodynamic melting’^{1,9}. In the case of $\text{VO}_2(\text{B})$, we propose that the combination of kinetic hindrance of the phase transformation to thermodynamically stable $\text{VO}_2(\text{M})$ and the increased atomic coordination are the driving forces of PIA. Upon moderate temperature annealing, the preference of VO_x polyhedra in thermodynamically metastable PIA- $\text{VO}_2(\text{B})$ drives the structure to return to the pristine $\text{VO}_2(\text{B})$.

In the P–V phase diagram, one can clearly see the difference between PIA- $\text{VO}_2(\text{B})$ and VO_2 glass. It is important to note that other hidden phases of VO_2 may exist, either in the low-density glass range or the high-density pressure-induced amorphous range. In this study, we observed profound structure switching behaviour of PIA- $\text{VO}_2(\text{B})$ at kinetically moderate temperatures, which demonstrates an interesting phenomenon of how temperature has a critical role in governing phase transformations under high pressure. The exploration of yet more interesting physical properties related to high density VO_2 glass with a short-range order may greatly boost the development of condensed matter science.

Discussion

VO_2 phases as the famous strongly correlated family always shows interesting magnetic and electric properties. To gain more insight into the participation of charge and spin interactions

during the PIA, *in situ* electrical resistance within a diamond anvil cell (DAC) and *ex situ* magnetic susceptibility measurements (using an amorphized sample synthesized by a large volume press apparatus) were performed. Figure 6 shows the resistance change during compression and decompression, and those at 7.5 and 26 GPa (before and after amorphization) as a function of temperature. At the first stage ($P < 10$ GPa), the resistance drop can be associated with the broadening and partial overlapping of the valence and conduction bands, caused by the normal pressure-induced shortening of V–V distances and bending of the V–O bonds. A steep increase in the resistance, which is caused by the onset and completion of the PIA, dominates the profile between 10 and 18 GPa. During the PIA process, point defects accompany the breaking of the long-range order, and thus the electron transport is suppressed by these increased defects, which serve as scattering centres. After the PIA process, band overlapping proceeds, as revealed by the continuous decrease of the electrical resistance, and finally drops to 30 GPa; nearly the same level as the crystalline $\text{VO}_2(\text{B})$ before PIA. However, after decompression, the resistance increases by two orders of magnitude than the pristine $\text{VO}_2(\text{B})$ sample (Fig. 6b), which indicates a reinforced electronic localization in PIA- $\text{VO}_2(\text{B})$. The temperature dependence of the electric resistance before and after the PIA process (7.5 and 26.0 GPa) proves that PIA- $\text{VO}_2(\text{B})$ remains a semiconductor but has poorer electrical conductivity (Fig. 6c). We also fabricated PIA- $\text{VO}_2(\text{B})$ samples using a large volume press apparatus at room temperature and 20 GPa. The decrease of the effective Bohr magnetic moment in PIA- $\text{VO}_2(\text{B})$ from $1.35\mu_{\text{B}}$ to $1.15\mu_{\text{B}}$ per V^{4+} , as derived from the *ex situ* magnetic susceptibility measurement, suggests that the electron localization may be due to the formation of more V–V pairs/dimers (Supplementary Fig. 6). More investigations are required to further probe the role of charge and spin in the PIA phenomenon and structure memory of $\text{VO}_2(\text{B})$ nanosheets.

In conclusion, we report a precise control of the structure switching between crystalline and pressure-induced amorphous phases in $\text{VO}_2(\text{B})$ nanosheets for the first time. The PIA- $\text{VO}_2(\text{B})$ has no long-range periodicity, but preserves the inherited VO_x polyhedral from $\text{VO}_2(\text{B})$ with highly distorted local ordering. Upon moderate temperature annealing, these VO_x polyhedra release excess energy and restore the pristine long-range

Figure 6 | Electrical resistances of $\text{VO}_2(\text{B})$ nanosheets as a function of pressure. (a) Compression. Scale bar, 100 μm . (b) Decompression. (c) Temperature dependence of the sample before and after the pressure-induced amorphization. The inset in (a) shows the microphotograph of the $\text{VO}_2(\text{B})$ sample inside a DAC with four Au probes.

periodicity. Spectral evidence and DFT calculations provide additional insight into the phase relationship between crystalline VO₂ phases and PIA-VO₂(B) glass. The dynamically moderate annealing temperature provides a key mechanism of energetic control on the hidden reversible amorphization of metastable VO₂(B). Preliminary evidence for the participation of charge and spin interactions during PIA were also observed for the first time. The robust control of the phase transition between the metastable crystalline VO₂(B) phase and the PIA-VO₂(B) amorphous phase, via compression and low-temperature annealing, reveals the structure switching behaviour within a tetravalent vanadium-based material for the first time. This highlights exploration of thermodynamically hindered phase transformations with pressure and temperature tuning. Further investigations on the physical mechanism behind the phenomenon are expected, including orbital, electron and magnetic interactions.

Methods

Sample preparation. VO₂(B) nanosheets were synthesized from high pure V₂O₅ raw material via a hydrothermal route, with citric acid as the reducing agent. Briefly, 0.182 g V₂O₅ powder (1 mmol) and 0.288 g citric acid (1.5 mmol) were added into 20 ml distilled water and continuously stirred to obtain the precursor. The precursor was then transferred into a Teflon-lined autoclave (25 ml capacity, 80% filling). The autoclave was heated to 200 °C at a rate of 3 °C min⁻¹ and maintained at 200 °C for 5 h, followed by air cooling to room temperature by switching the power off. The resulting precipitates were washed with deionized water and dried at 80 °C overnight. Transmission electron microscopy (TEM) techniques were applied to check the morphology of the as-synthesized nanosheets at ambient pressure.

In situ high-pressure characterizations. A symmetric DAC was employed to generate high pressure. A stainless steel gasket was pre-indented to a 40 µm thickness, followed by laser-drilling the central part to form a 120 µm diameter hole to serve as the sample chamber. Pre-compressed VO₂(B) powder pellets and a small ruby ball were loaded in the chamber. Helium or neon was used as the pressure-transmitting medium and the pressures were determined by the ruby fluorescence method³⁹. The *in situ* high-pressure angular-dispersive XRD experiments were carried out at the 16BM-D station of the High-Pressure Collaborative Access Team (HPCAT) at the Advanced Photon Source (APS), Argonne National Laboratory (ANL). A focused monochromatic X-ray beam about 5 µm in diameter (FWHM) and with wavelengths of 0.4246 Å was used for the diffraction experiments. The diffraction data were recorded by a MAR345 image plate and processed with the Fit2D programme. High-pressure infrared spectroscopic experiments were performed at the U2A beamline of National Synchrotron Light Source (NSLS), Brookhaven National Laboratory and the mid-IR beamline of the Canadian Light Source. The infrared spectra were collected in transmission mode by a Bruker FTIR spectrometer using a nitrogen-cooled mid-band MCT (MCT-A) detector. The recorded frequencies were in the range of 600–8,000 cm⁻¹ with a resolution of 4 cm⁻¹. High-pressure Raman spectra were measured by a Raman spectrometer with a 532.1 nm excitation laser at HPCAT.

For the *ex situ* annealing experiments, the PIA-VO₂(B) samples were removed with the gaskets after depressurization. They were then annealed at different temperatures (200, 250, 300, 350, 400, 450, 500, 550 °C) each for 5 min within a vacuum furnace, and the resulting phases were checked with synchrotron XRD. While in the *in situ* annealing experiments, the bulky PIA-VO₂(B) sample was made using a large volume press apparatus and sealed in a glass tube. Then XRD patterns were taken at 30, 60, 90, 120, 160, 190 and 220 °C with electric heating, respectively. The holding time at each temperature was 5 min. Structure refinements were performed with the FULLPROF programme⁴⁰.

Resistance and magnetic susceptibility measurements. *In situ* electrical resistance was measured by a four-probe resistance measurement system consisting of a Keithley 6,221 current source, a 2182A nanovoltmeter and a 7,001 voltage/current switch system. A DAC device was used to generate pressures up to 30 GPa, and a cubic boron nitride layer was inserted between the steel gasket and diamond anvil to provide electrical insulation between the electrical leads and gasket. Four gold wires were arranged to contact the sample in the chamber for resistance measurements. For the magnetism measurement, 0.1 g sample was made using a large volume press apparatus at 20 GPa for 1 h at room temperature. The DC magnetic susceptibility was measured using a SQUID magnetometer (Quantum Design) with an applied magnetic field of 500 Oe.

DFT calculations. Total energy and pressure–volume equations of state for the four VO₂ crystalline phases were calculated at the atomic level using the first-

principles plane-wave pseudopotential method⁴¹ based on the density functional theory, with the CASTEP package³⁸. The exchange–correlation function is described by the local density approximation⁴². The ion–electron interactions were modelled with ultrasoft pseudopotentials⁴³ for all constituent elements, where the V 4s²3d³ and O 2s²2p⁴ electrons were treated as the valence electrons, respectively. The kinetic energy cut-off of 380 eV and Monkhorst-Pack *k*-point meshes⁴⁴ spanning <0.04 Å⁻³ in the Brillouin zone were chosen. The starting structure models were obtained from the Inorganic Crystal Structure Database (ICSD) for VO₂(A), VO₂(B), VO₂(M) and VO₂(R). The cell parameters and atomic positions within the unit cell of these four phases, under hydrostatic pressure ranging between 0 and 100 GPa (with the interval of 5 GPa), were fully optimized using the quasi-Newton method⁴⁵. The convergence thresholds between the optimization cycles for energy change, maximum force, maximum stress, and maximum displacement were set as 5.0 × 10⁻⁶ eV per atom, 0.01 eV Å⁻¹, 0.02 GPa and 5.0 × 10⁻⁴ Å, respectively. The optimization terminates when all of these criteria are satisfied. All these computational parameters were tested to ensure the sufficient accuracy for the present purposes.

Data availability. The data that support the findings of this study are available from the corresponding author upon request.

References

- Mishima, O., Calvert, L. D. & Whalley, E. 'Melting ice' I at 77 K and 10 kbar: a new method of making amorphous solids. *Nature* **310**, 393–395 (1984).
- Yamanaka, T., Nagai, T. & Tsuchiya, T. Mechanism of pressure-induced amorphization. *Z. Kristallogr.* **212**, 401–410 (1997).
- Machon, D., Meersman, F., Wilding, M. C., Wilson, M. & McMillan, P. F. Pressure-induced amorphization and polyamorphism: inorganic and biochemical systems. *Prog. Mater. Sci.* **61**, 216–282 (2014).
- Sharma, S. M. & Sikka, S. K. Pressure induced amorphization of materials. *Prog. Mater. Sci.* **40**, 1–77 (1996).
- Hemley, R. J., Chen, L. C. & Mao, H. K. New transformations between crystalline and amorphous ice. *Nature* **338**, 638–640 (1989).
- Mishima, O., Takemura, K. & Aoki, K. Visual observations of the amorphous–amorphous transition in H₂O under pressure. *Science* **254**, 406–408 (1991).
- Tse, J. S. *et al.* The mechanisms for pressure-induced amorphization of ice I_h. *Nature* **400**, 647–649 (1999).
- McNeil, L. E. & Grimsditch, M. Pressure-amorphized SiO₂ α-quartz: an anisotropic amorphous solid. *Phys. Rev. Lett.* **68**, 83–85 (1992).
- Hemley, R. J., Jephcoat, A. P., Mao, H. K., Ming, L. C. & Manghnani, M. H. Pressure-induced amorphization of crystalline silica. *Nature* **334**, 52–54 (1988).
- Sato, T. & Funamori, N. Six-fold-coordinated amorphous polymorph of SiO₂ under high pressure. *Phys. Rev. Lett.* **101**, 255502 (2008).
- Jayaraman, A., Wood, D. L. & Mains, Sr R. G. High-pressure Raman study of the vibrational modes in AlPO₄ and SiO₂ (α-quartz). *Phys. Rev. B* **35**, 8316–8321 (1987).
- Winters, R. R. & Hammack, W. S. Pressure-induced amorphization of R-Al₅Li₃Cu: a structural relation among amorphous metals, quasi-crystals, and curved space. *Science* **260**, 202–204 (1993).
- Zhang, J. *et al.* Pressure-induced amorphization and phase transformations in β-LiAlSiO₄. *Chem. Mater.* **17**, 2817–2824 (2005).
- Keen, D. A. *et al.* Structural description of pressure-induced amorphization in ZrW₂O₈. *Phys. Rev. Lett.* **98**, 225501 (2007).
- Perottoni, C. A. & Jornada, J. A. H. Pressure-induced amorphization and negative thermal expansion in ZrW₂O₈. *Science* **280**, 886–889 (1998).
- Varga, T. *et al.* Pressure-induced amorphization of cubic ZrW₂O₈ studied *in situ* and *ex situ* by synchrotron X-ray diffraction and absorption. *Phys. Rev. B* **72**, 024117 (2005).
- Arora, A. K., Okada, T. & Yagi, T. Structural analysis of pressure-amorphized zirconium tungstate. *Phys. Rev. B* **81**, 134103 (2010).
- Zeng, Q. *et al.* Long-range topological order in metallic glass. *Science* **332**, 1404–1406 (2011).
- Fuji, Y., Kowaka, M. & Onodera, A. The pressure-induced metallic amorphous state of SnI₄: I. A novel crystal-to-amorphous transition studied by x-ray scattering. *J. Phys. C: Solid State Phys.* **18**, 789–797 (1985).
- Sankaran, H., Sikka, S. K., Sharma, S. M. & Chidambaram, R. Pressure-induced noncrystalline phase of LiKSO₄. *Phys. Rev. B* **38**, 170–173 (1988).
- Kruger, M. B., Williams, Q. & Jeanloz, R. V. Vibrational spectra of Mg(OH)₂ and Ca(OH)₂ under pressure. *J. Chem. Phys.* **91**, 5910–5915 (1989).
- Tse, J. S., Klug, D. D., Rlpmeester, J. A., Desgreniers, S. & Lagarec, K. The role of non-deformable units in pressure-induced reversible amorphization of clathrasils. *Nature* **369**, 724–727 (1994).
- Tse, J. S. & Klug, D. D. Structural memory in pressure-amorphized AlPO₄. *Science* **255**, 1559–1561 (1992).
- Kruger, M. B. & Jeanloz, R. Memory glass: an amorphous material formed from AlPO₄. *Science* **249**, 647–649 (1990).

25. Lim, H. S., Kwak, D., Lee, D. Y., Lee, S. G. & Cho, K. UV-driven reversible switching of a roselike vanadium oxide film between superhydrophobicity and superhydrophilicity. *J. Am. Chem. Soc.* **129**, 4128–4129 (2007).
26. Geyer, T., Born, P. & Kraus, T. Switching between crystallization and amorphous agglomeration of alkyl thiol-coated gold nanoparticles. *Phys. Rev. Lett.* **109**, 128302 (2012).
27. Popuri, S. R. *et al.* VO₂(A): reinvestigation of crystal structure, phase transition and crystal growth mechanisms. *J. Solid State Chem.* **213**, 79–86 (2014).
28. Oka, Y., Yao, T., Yamamoto, N., Ueda, Y. & Hayashi, A. Phase transition and V⁴⁺–V⁴⁺ pairing in VO₂(B). *J. Solid State Chem.* **105**, 271–278 (1993).
29. Galy, J. & Miehe, G. *Ab initio* structures of (M2) and (M3) VO₂ high pressure phases. *Solid State Sci.* **11**, 433–448 (1999).
30. Leroux, C., Nihoul, G. & Van Tendeloo, G. From VO₂(B) to VO₂(R): Theoretical structures of VO₂ polymorphs and *in situ* electron microscopy. *Phys. Rev. B* **57**, 5111–5121 (1998).
31. Zhang, S. *et al.* From VO₂(B) to VO₂(A) nanobelts: first hydrothermal transformation, spectroscopic study and first principles calculation. *Phys. Chem. Chem. Phys.* **12**, 15873–15881 (2011).
32. Li, H., He, P., Wang, Y., Hosono, E. & Zhou, H. High-surface vanadium oxides with large capacities for lithium-ion batteries: from hydrated aerogel to nanocrystalline VO₂(B), V₆O₁₃ and V₂O₅. *J. Mater. Chem.* **21**, 10999–11009 (2011).
33. Popuri, S. R. *et al.* Rapid hydrothermal synthesis of VO₂(B) and its conversion to thermochromic VO₂(M1). *Inorg. Chem.* **52**, 4780–4785 (2013).
34. Bai, L. *et al.* Pressure-induced phase transitions and metallization in VO₂. *Phys. Rev. B* **91**, 104110 (2015).
35. Hu, Q. Y. *et al.* Polymorphic phase transition mechanism of compressed coesite. *Nat. Commun.* **6**, 6630 (2015).
36. Klotz, S., Chervin, J.-C., Munsch, P. & Marchand, G. L. Hydrostatic limits of 11 pressure transmitting media. *J. Phys. D: Appl. Phys.* **42**, 075413 (2009).
37. Quan, Z. *et al.* Pressure-induced switching between amorphization and crystallization in PbTe nanoparticles. *Nano Lett.* **13**, 3729–3735 (2013).
38. Clark, S. J. *et al.* First principles methods using CASTEP. *Z. Kristallogr.* **220**, 567–570 (2005).
39. Mao, H. K., Xu, J. & Bell, P. M. Calibration of the ruby pressure gauge to 800 kbar under quasi-hydrostatic conditions. *J. Geophys. Res.* **91**, 4673–4676 (1986).
40. Rodriguez-Carvajal, J. Recent advances in magnetic structure determination by neutron powder diffraction. *Phys. B* **192**, 55–69 (1993).
41. Payne, M. C., Teter, M. P., Allan, D. C., Arias, T. A. & Joannopoulos, J. D. Iterative minimization techniques for *ab initio* total-energy calculations: molecular dynamics and conjugate gradients. *Rev. Mod. Phys.* **64**, 1045–1097 (1992).
42. Ceperley, D. M. & Alder, B. J. Ground state of the electron gas by a stochastic method. *Phys. Rev. Lett.* **45**, 566–569 (1980).
43. Lin, J. S., Qteish, A., Payne, M. C. & Heine, V. Optimized and transferable nonlocal separable *ab initio* pseudopotentials. *Phys. Rev. B* **47**, 4174–4180 (1993).
44. Monkhorst, H. J. & Pack, J. D. Special point for Brillouin-zone integrations. *Phys. Rev. B* **13**, 5188–5192 (1976).
45. Pfrommer, B. G., Cote, M., Louie, S. G. & Cohen, M. L. Relaxation of crystals with the quasi-Newton method. *J. Comput. Phys.* **131**, 233–240 (1997).

Acknowledgements

The UNLV High Pressure Science and Engineering Center (HIPSEC) is a DOE–NNSA Center of Excellence supported by Cooperative Agreement DE-NA0001982. HPCAT operations are supported by DOE – NNSA under Award DE-NA0001974 and DOE-BES under Award DE-FG02-99ER45775, with partial instrumentation funding by NSF. U2A beamline was supported by National Science Foundation (EAR 1606856, COMPRES) and DOE/NNSA (DE-NA-0002006, CDAC). The gas loading was performed at GeoSoilEnviroCARS, APS, ANL, supported by EAR-1128799 and DE-FG02-94ER14466. The authors thank Q. Li (JLU), L. Bai (HPCAT), L. Tang, L. Yang and R. Ferry (HPSynC), D. Sneed and Q. Smith (UNLV) for their valuable suggestions and help in the experiments.

Author contributions

W.Y. and Y.Z. conceived the project and designed the experiments. Y.W. and T.W. performed material synthesis, characterizations and high-pressure measurements. J.Z., M.P. and Z.L. performed IR measurements. M.H. and Y.F. synthesized the large volume amorphous sample. J.Z. and C.J. performed the magnetism measurements. L.K. and Z.L. performed the DFT calculation. Y.W., W.Y. and Y.Z. analyzed the data and co-wrote the paper. All authors discussed the results and commented on the manuscript.

Additional information

Supplementary Information accompanies this paper at <http://www.nature.com/naturecommunications>

Competing financial interests: The authors declare no competing financial interests.

Reprints and permission information is available online at <http://npg.nature.com/reprintsandpermissions/>

How to cite this article: Wang, Y. *et al.* Reversible switching between pressure-induced amorphization and thermal-driven recrystallization in VO₂(B) nanosheets. *Nat. Commun.* 7:12214 doi: 10.1038/ncomms12214 (2016).

This work is licensed under a Creative Commons Attribution 4.0 International License. The images or other third party material in this article are included in the article's Creative Commons license, unless indicated otherwise in the credit line; if the material is not included under the Creative Commons license, users will need to obtain permission from the license holder to reproduce the material. To view a copy of this license, visit <http://creativecommons.org/licenses/by/4.0/>

© The Author(s) 2016