ARTICLE

Received 6 Apr 2016 | Accepted 7 Oct 2016 | Published 16 Nov 2016

DOI: 10.1038/ncomms13510

OPEN

Jahn-Teller-induced femtosecond electronic depolarization dynamics of the nitrogen-vacancy defect in diamond

Ronald Ulbricht^{1,2,†}, Shuo Dong², I-Ya Chang^{3,4}, Bala Murali Krishna Mariserla⁵, Keshav M. Dani⁵, Kim Hyeon-Deuk^{3,4} & Zhi-Heng Loh^{1,2,6}

Single-photon emission from the nitrogen-vacancy defect in diamond constitutes one of its many proposed applications. Owing to its doubly degenerate 3E electronic excited state, photons from this defect can be emitted by two optical transitions with perpendicular polarization. Previous measurements have indicated that orbital-selective photoexcitation does not, however, yield photoluminescence with well-defined polarizations, thus hinting at orbital-averaging dynamics even at cryogenic temperatures. Here we employ femtosecond polarization anisotropy spectroscopy to investigate the ultrafast electronic dynamics of the 3E state. We observe subpicosecond electronic dephasing dynamics even at cryogenic temperatures, up to five orders of magnitude faster than dephasing rates suggested by previous frequency- and time-domain measurements. *Ab initio* molecular dynamics simulations assign the ultrafast depolarization dynamics to nonadiabatic transitions and phonon-induced electronic dephasing between the two components of the 3E state. Our results provide an explanation for the ultrafast orbital averaging that exists even at cryogenic temperatures.

¹Division of Chemistry and Biological Chemistry, School of Physical and Mathematical Sciences, Nanyang Technological University, Singapore 637371, Singapore. ²Division of Physics and Applied Physics, School of Physical and Mathematical Sciences, Nanyang Technological University, Singapore 637371, Singapore. ³Department of Chemistry, Kyoto University, Kyoto 606-8502, Japan. ⁴Japan Science and Technology Agency, PRESTO, 4-1-8 Honcho, Kawaguchi, Saitama 332-0012, Japan. ⁵Femtosecond Spectroscopy Unit, Okinawa Institute of Science and Technology Graduate University, 1919-1 Tancha, Onna-son, Kunigami, Okinawa 904-0495, Japan. ⁶Centre for Optical Fibre Technology, The Photonics Institute, Nanyang Technological University, Singapore 639798, Singapore. † Present address: Department of Physics, Department of Chemistry and JILA, University of Colorado, Boulder, Colorado 80309, USA. Correspondence and requests for materials should be addressed to R.U. (email: ronald.ulbricht@colorado.edu) or to K.H.-D. (email: kim@kuchem.kyoto-u.ac.jp) or to Z.-H.L. (email: zhiheng@ntu.edu.sg).

Among the known colour centres of diamond, the negatively charged nitrogen-vacancy (NV^-) defect has attracted the most attention¹, motivated by its potential to serve as a building block for novel quantum technologies. Remarkable advances in their magnetic and optical manipulation, performed even at the single-defect level², herald their application to spin-based quantum computing^{3,4} and photonics⁵, as well as nanoscale magnetic field^{6–8} and temperature sensors^{9–11}.

Buried deep within the band gap of diamond are the NV^- $^3\text{A}_2$ electronic ground state and the doubly degenerate ^3E excited state, which are optically coupled by a narrow zero-phonon line (ZPL) transition at 1.95 eV (637 nm wavelength, Fig. 1a). This optical transition has been identified as a potential quantum emitter for single photons^{1,5}. Vibronic coupling between the ^3E electronic state and a quasi-localized vibrational mode at ~ 68 meV gives rise to a broad phonon sideband¹². The E_x and E_y sublevels of the ^3E state have orthogonal electronic alignment, evidenced by the computed orbital densities in Fig. 1b, hence yielding two perpendicularly polarized $^3\text{A}_2 \rightarrow ^3\text{E}$ transitions¹.

As a result of its orbital degeneracy, the ^3E state couples to a doubly degenerate vibrational mode of e symmetry to form an $E \otimes e$ Jahn-Teller (JT) system¹. The JT-active mode involves the displacement of the carbon atoms that surround the vacancy. The initially degenerate E_x and E_y states are displaced along the JT-active mode Q_{JT} , creating a conical intersection (CI, see Fig. 1b). At the same time, the potential minimum energy is reduced by the JT stabilization energy E_{JT} . For the NV^- defect, the theoretically predicted JT stabilization energy E_{JT} of 25 meV is smaller than the tunnelling splitting of 34 meV, therefore rendering the system a dynamic JT distortion¹³.

In the vicinity of CIs, the Born-Oppenheimer approximation breaks down, allowing exceptionally fast nonadiabatic (NA) transitions between potential energy surfaces^{14,15}. In molecular photochemistry, for example, CIs between electronic excited and ground states are known to promote ultrafast internal conversion on femtosecond timescales¹⁶. In the case of the NV^- defect, the CI exists only between the excited state E_x and E_y orbitals, thereby potentially enabling ultrafast NA transitions between them. In addition, the JT effect has been invoked to explain the asymmetry between the absorption and photoluminescence (PL) lineshapes¹, the broadening of the $^3\text{E} \rightarrow ^3\text{A}_2$ ZPL transition linewidth with increasing temperature and the concomitant reduction in the polarization contrast of its PL¹⁷. These JT effects have important ramifications. The non-unity polarization contrast, observed even at cryogenic temperatures, for example, impairs coupling of NV^- photon sources to plasmonic waveguides and decreases the interference visibility of emitted single photons, thus impeding its use in quantum information processing⁵.

The coherent dynamics of the orbital doublet at the $E \otimes e$ JT CI are encoded in the optical dephasing times. From the PL excitation linewidths of single defects, dephasing times of ~ 10 ns at sub-10 K and < 0.3 ps at temperatures beyond 200 K have been inferred¹⁷. The former is substantiated by an orbital coherence time of ~ 6 –7 ns, directly determined from time-domain Ramsey fringe interferometry¹⁸. However, the low PL polarization contrast of $\lesssim 0.5$ at 4 K indicates the existence of ultrafast dynamics that precede the nanosecond electronic dephasing processes that have been uncovered so far^{17–19}.

Here we use femtosecond polarization anisotropy (PA) spectroscopy to resolve the ultrafast coherent orbital dynamics

Figure 1 | Electronic and optical properties of the NV^- defect and the polarization anisotropy spectroscopy measurement scheme. (a) Optical absorption spectrum of the NV^- sample recorded at 77 K, showing a distinct ZPL, in addition to the one- (1PL) and two-phonon line (2PL) transitions. The spectrum of the pump pulse used to excite the ZPL line is shown in blue. (b) Electronic structure of the NV^- defect, showing the E_x (blue) and E_y (red) components of the ^3E state accessed from the $^3\text{A}_2$ ground state via the ZPL transition at 1.95 eV (637 nm). Structural distortion along a JT-active mode Q_{JT} lowers the symmetry of the doubly degenerate ^3E state, found at the CI, to yield JT-split $^3\text{E}_x$ and $^3\text{E}_y$ states. The JT stabilization energy E_{JT} of 25 meV positions the CI below the $v' = 0$ level, located at 34 meV. In the experiments, a linearly polarized pump excites the ^3E doublet and a time-delayed broadband probe pulse with variable polarization, either parallel or perpendicular relative to the pump, interrogates the time-resolved stimulated emission. The orbital plots show the orbital alignment for the E_x and E_y states, as viewed along the C_3 axis of the NV^- defect. The red regions denote the electron probability distribution and the blue sphere denotes the nitrogen atom. The plots are calculated by density functional theory using the PBE functional and projector-augmented-wave pseudopotentials (see Methods). (c) Spectrally resolved differential transmission $\Delta T/T$, showing contributions from ground-state bleaching (blue side of ZPL) and stimulated emission (red side of ZPL).

of the 3E state. We observe biphasic electronic dephasing dynamics occurring on subpicosecond to few-picosecond timescales, even at cryogenic temperatures, up to five orders of magnitude faster than dephasing rates suggested by previous frequency- and time-domain measurements^{17,19,20}. *Ab initio* molecular dynamics (AIMD) simulations assign the dynamics to NA transitions around the CI and phonon-induced electronic dephasing between components of the 3E state.

Results

PA spectroscopy. The femtosecond PA measurements employ a narrowband linearly polarized pump pulse to excite the ZPL transition of the NV^- defect (Fig. 1a), following which a broadband linearly polarized probe pulse measures the pump-induced change of the normalized transmission spectrum $\Delta T/T$. Excitation of the ZPL as opposed to the phonon sideband avoids complications introduced by ultrafast vibrational relaxation²¹. Varying the pump–probe time delay and relative polarization yields the time-resolved $\Delta T/T$ signal (Fig. 1b) for parallel ($S^{\parallel}$) and perpendicular ($S^{\perp}$) relative polarization between pump and probe pulses. The PA signal $S_{\text{aniso}}(\lambda, t)$ is then obtained from the relation $S_{\text{aniso}}(\lambda, t) = (S^{\parallel} - S^{\perp}) / (S^{\parallel} + 2S^{\perp})$ (see Methods).

Photoexcitation leads to increased transmission of the NV^- sample, as can be seen from the positive $\Delta T/T$ signal over the entire probe spectrum (Fig. 1c). Features on the blue side of the ZPL arise from depletion of the 3A_2 ground state by the photoexcitation pump pulse, resulting in the bleaching of the 3A_2 ground-state absorption spectrum. The positive $\Delta T/T$ signal on the red side of the ZPL is because of Stokes-shifted stimulated emission from the $\nu' = 0$ level of the 3E state, populated by the pump pulse, to the various ν'' levels on the 3A_2 ground state. As such, the former signal is sensitive to ground-state dynamics, whereas the latter is sensitive to excited state dynamics. Note that excited-state absorption from the 3E state, which would give negative $\Delta T/T$ signals, is negligible because of the small oscillator strength of excited-state absorption into the conduction band.

$S_{\text{aniso}}(\lambda, t)$ provides information on the alignment dynamics after photoexcitation (see Methods and Supporting Information). In molecular spectroscopy, for instance, this is used to measure the reorientation of molecules in solution²², an effect that does not occur here because the NV^- defects are fixed in the diamond lattice. In addition, for probe transitions involving doubly degenerate excited states with perpendicular transition dipoles, as is the case here, the PA signals also reflect electronic reorientation. In such instances, the PA signal reports on electron motion around a CI^{23,24}, and its decay yields the dephasing time between the E_x and E_y states²⁵. Since the measurements are performed on an ensemble of differently oriented NV^- centres, linearly polarized photoexcitation does not selectively populate only one component of the orbital doublet, but instead, prepares a coherent superposition of the E_x and E_y states. As such, both population transfer and loss of phase coherence between the orbital doublet states—collectively referred to as orbital dephasing herein—lead to electronic de-alignment and, hence, the decay of the PA^{23,25}. The observation of dephasing dynamics in the time-domain complements frequency-domain measurements, particularly when dephasing is fast and spans multiple timescales, which make the broad linewidths associated with ultrafast depolarization challenging to discern in the frequency domain.

The PA spectrum $S_{\text{aniso}}(\lambda, t)$ collected as a function of pump–probe time delay at 77 K is shown in Fig. 2a. The anisotropy value obtained on the blue side of the ZPL transition, where ground-state bleaching dominates, is found to be constant to within experimental error ($S_{\text{aniso}} \sim 0.1$). On the other hand, a

pronounced decay (Fig. 2b) is observed for the PA recorded at the ZPL (white-dashed line) and to its red side, where stimulated emission occurs. Anisotropy dynamics only appearing through stimulated emission indicates that they originate from the 3E excited state. The PA decay at the ZPL can be fit to the function $S_{\text{aniso}}(t) = A_0 + A_1 e^{-t/\tau_1} + A_2 e^{-t/\tau_2}$, where the offset A_0 , amplitudes A_1 and A_2 , and exponential decay constants τ_1 and τ_2 are all fit parameters. The time constants of both the fast (τ_1) and slow (τ_2) decay components exhibit distinct temperature dependencies (Fig. 2c). Furthermore, τ_2 is evident only below 150 K. τ_1 is constant to within experimental error, varying between 0.15 ± 0.03 and 0.10 ± 0.02 ps for all measured temperatures. On the other hand, τ_2 decreases markedly from 14.4 ± 1.7 ps at 10 K to 0.70 ± 0.11 ps at 150 K. It is noteworthy that S_{aniso} does not completely decay to 0.10 within the maximum time delay of 20 ps employed in our measurements. This asymptotic value of 0.10 for S_{aniso} would be expected for an electronic system that comprises a nondegenerate ground state and a doubly degenerate excited state with orthogonal transition dipoles, as is the case here^{23,25}. We note that S_{aniso} does not vanish to zero, as it would for molecules in solution by rotational diffusion²² because the defects are fixed in the diamond lattice. We believe that the deviation of the final S_{aniso} value from the theoretical isotropic value of 0.10 is indicative of long-lived orbital coherence surviving beyond 20 ps, consistent with nanosecond dephasing dynamics that have been observed at cryogenic temperatures via single-defect lineshape measurements¹⁷ and time-domain Ramsey fringe interferometry¹⁸. The subpicosecond to picosecond dynamics observed herein precede the previously reported dephasing timescales.

Subpicosecond τ_1 electronic depolarization dynamics. NA AIMD simulations are performed to elucidate the origin of the observed subpicosecond depolarization dynamics. The computed decay profiles reveal depolarization via population transfer from the initially populated E_x state to the E_y state (Fig. 2d). The ~ 100 -fs timescale for electronic equilibration (Fig. 2e) is in agreement with the experimental τ_1 values. The inverse relation between the computed τ_1 and the electron–phonon coupling strength (Fig. 2e) indicates that the fast component of the electronic depolarization dynamics is driven by NA transitions. The relatively weak temperature dependence is partly due to the stiff and extended diamond structure, and is qualitatively different from the strong temperature dependence that appears, for example, in semiconductor quantum dots, which have finite nanoscale size and thus a large surface-to-volume ratio²⁶. Fourier transforms of the real-time fluctuations of the E_x and E_y energies yield the frequencies of the phonon modes that mediate the electronic equilibration (Fig. 2f). Within the theoretical framework of AIMD, these phonon-induced fluctuations arise from incoherent vibrational motions of the thermal bath (see Supplementary Figs 1 and 2), unlike coherent phonons launched by impulsive excitation, which manifest themselves as oscillatory features in the $\Delta T/T$ signals. The fast Fourier transform (FFT) power spectrum obtained at 77 K reveals several prominent peaks at 47, 69, 90, 120, 130 and 150–160 meV. These modes have been identified and assigned by earlier *ab initio* calculations to the various quasi-localized vibrational modes of the NV^- defect²⁷, including one at 69 meV that coincides with the energy of the JT-active e mode¹³. Interestingly, the presence of multiple phonon frequencies in the FFT power spectrum suggests that the depolarization dynamics are driven not only by the JT-active modes, but also by a collection of other vibrational modes that are anharmonically coupled to the JT-active modes.

Figure 2 | Ultrafast electronic depolarization dynamics and results of the NA AIMD simulations. (a) Time evolution of the polarization anisotropy spectrum recorded at 77 K after ZPL excitation. (b) Line-out at the ZPL wavelength (white dashed line in a) showing a biexponential decay of the PA with time constants τ_1 and τ_2 . (c) Temperature dependence of τ_1 and τ_2 and fit of the temperature dependence of τ_2 to equation (1); error bars denote the s.e.m. (d) Simulated electronic depolarization trajectories for various temperatures. (e) Time constant τ_1 and electron-phonon coupling strength computed at various temperatures. (f) Simulated FFT power spectrum at 77 K showing the frequencies of phonon modes that mediate ultrafast electronic depolarization. Aniso, anisotropy; norm, normalized.

Picosecond τ_2 electronic depolarization dynamics. The conspicuous temperature dependence of τ_2 suggests phonon-mediated electronic depolarization as its origin. The vanishing NV⁻ defect phonon density of states^{13,27,28} at phonon energies <20 meV prevents one-phonon transitions from effecting population transfer between the E_x and E_y states²⁹. Nevertheless, one-phonon-mediated electronic depolarization is still possible via phonon-induced fluctuations of the orbital doublet, or even transitions from the lowest-energy E_x and E_y vibronic levels of the 3E electronically excited state to higher-lying, nondegenerate vibronic levels of A_1 and/or A_2 symmetry, for which electronic alignment does not exist. In either case, the one-phonon transition rate $\Gamma(T) = 1/\tau_2(T)$ follows the relation³⁰

$$\Gamma(T) = \Gamma_0 + \sigma T + \Gamma_c / (e^{\hbar\omega_c/k_B T} - 1), \quad (1)$$

where Γ_0 is the temperature-independent offset, σ (Γ_c) characterizes the electron-phonon coupling strength for phonon energies $\hbar\omega \ll k_B T$ ($\hbar\omega \gtrsim k_B T$) and ω_c represents the effective frequency of a group of phonons with energies $\hbar\omega \gtrsim k_B T$ that induces depolarization. Fitting the experimental data to equation (1) gives $\Gamma_0 = 0.070 \pm 0.013 \text{ ps}^{-1}$, $\sigma \sim 0$ (to within experimental uncertainty), $\Gamma_c = 9.9 \pm 3.4 \text{ ps}^{-1}$ and $\hbar\omega_c = 26 \pm 3 \text{ meV}$ (Fig. 2c). The vanishing σ coefficient is consistent with the paucity of low-energy phonons with $\hbar\omega \ll k_B T$ in the phonon density of states. Interestingly, ω_c closely approaches the calculated $E-A_1$ tunnelling splitting¹³ of 35 meV, suggesting possible electronic depolarization via the phonon-driven population transfer from the E_x and E_y vibronic

levels to the totally symmetric A_1 vibronic level within the 3E electronically excited state. Excited-state AIMD simulations based on a microcanonical trajectory generated at 10 K furnish a dephasing time of 8 ps, in good agreement with the experimentally measured value of $14.4 \pm 1.7 \text{ ps}$ (see Supplementary Fig. 3). The correlated phonon-induced fluctuations of the E_x and E_y states support the long dephasing time. We note, however, that the experimental uncertainty in the measured τ_2 values does not allow depolarization via one-phonon transitions to be distinguished from two-phonon Raman-type population transfer¹⁷ between the E_x and E_y states (see Supplementary Fig. 4). The latter, whose rate scales as T^5 , has been invoked to explain the temperature-dependent population transfer and electronic dephasing rates obtained from measurements of single-defect linewidths^{17,31}, decoherence of Rabi oscillations²⁹ and ensemble photon-echo spectroscopy³².

Discussion

Previous frequency- and time-domain measurements were performed on high-purity Type 2a diamond samples, which have defect densities that are in the parts-per-billion (p.p.b.) regime, and thus orders of magnitude lower than the Type 1b sample ($\sim 100 \text{ p.p.m.}$) used in the present study. Therefore, a natural question that arises is the extent to which the observed ultrafast dynamics are intrinsic to a single defect. Fluctuations of the charge bath and defect-defect interactions could presumably lead to the enhanced dephasing rates observed herein. First, we note that previous single-defect measurements on samples with

Figure 3 | Ultrafast electronic depolarization dynamics of the NV⁻ defect. (a) Initial polarized photoexcitation leads to the population of the E_x level at $t = 0$. (b) Partial electronic depolarization occurs via NA transitions between E_x and E_y on a timescale of τ_1 . (c) Various possible pathways that drive further electronic depolarization on a timescale of τ_2 include phonon-induced fluctuations of the E_x to E_y levels (wavy arrows), resonant one-phonon excitation to the unaligned A_1 vibronic level (solid arrows) and off-resonant two-phonon population transfer between E_x and E_y (dashed arrows). For simplicity, initial excitation is assumed to populate only the E_x state.

similarly high defect densities^{33,34} yield microsecond timescales for spectral diffusion, orders of magnitude longer than the picosecond and subpicosecond dynamics observed here. Second, considering the quasi-localized nature of the vibrational modes²⁷, the modification of the phonon density of states of a given NV⁻ centre by an adjacent defect is expected to be negligible. Finally, and most importantly, we point out that the AIMD simulations were performed on a 215-atom supercell, which corresponds to an effective defect density of 4,650 p.p.m., $>40\times$ larger than the actual ~ 100 p.p.m. defect density of the sample used in the measurements. The fact that the observed dephasing timescales are reproduced by the AIMD simulations strongly suggests that the ultrafast dephasing dynamics are intrinsic to the isolated NV⁻ centre. This claim can be verified by future measurements on defects with varying NV⁻ densities.

Our combined experimental–theoretical investigation affords the following unified picture of the ultrafast electronic depolarization dynamics following ZPL photoexcitation of the 3E excited state. Photoexcitation by a linearly polarized laser pulse at the ZPL creates a NV⁻ defect that is electronically aligned in the excited state along the polarization axis of the laser field, leading to a coherent superposition of the E_x and E_y states (Fig. 3a). Because of the energetic proximity of the vibronic levels to the JT CI, where the electron–phonon coupling strength is maximal, the non-vanishing phonon velocities of the heat bath promote efficient NA transitions between the E_x and E_y states, leading to rapid electronic depolarization on the $\tau_1 \sim 0.1$ -ps timescale (Fig. 3b). On longer timescales spanning $\tau_2 \sim 1 - 10$ ps, orbital dephasing is promoted by electron–phonon scattering involving phonon-induced fluctuations, transitions to totally symmetric, higher-energy vibronic levels and/or two-phonon population transfer between the E_x and E_y states (Fig. 3c).

The subpicosecond to picosecond electronic depolarization dynamics unravelled here provide an explanation for the hitherto unaccounted loss of polarization fidelity of the NV⁻ defect PL at cryogenic temperatures^{17,19}, that is, the fact that orbital averaging occurs even at such low temperatures. This ultrafast biphasic dephasing could have eluded previous frequency-domain measurements since, insofar as multiple disparate dephasing timescales are involved, it is conceivably challenging to identify in a lineshape analysis the broad pedestal that is associated with subpicosecond dephasing. Note that time-domain photon echo measurements have elucidated similar biphasic dephasing dynamics spanning two to three orders of magnitude for excitons in self-assembled³⁵ and colloidal³⁶ quantum dots. In the case of the NV⁻ centre, our results, together with earlier frequency^{17,19} and time-domain studies^{18,32}, demonstrate that electronic dephasing at a given cryogenic temperature spans an unprecedented five decades in time, from 10^{-13} to 10^{-8} s.

Methods

Sample. The investigated NV⁻ sample is a high-pressure high-temperature-grown Type 1b diamond (Element Six) measuring $4 \times 4 \times 0.3$ mm³. NV⁻ defects are introduced by irradiation with 1-MeV electrons at a flux of 10^{18} cm⁻² and subsequent annealing in vacuum for 2 h at a temperature of 800 °C. The resulting NV⁻ density is ~ 10 p.p.m., whereas the density of remaining N_i defects is 100 p.p.m. The pure diamond used for artefact subtraction is a CVD-grown type IIa diamond of similar size (Element Six).

Ultrafast polarization-resolved optical spectroscopy. Femtosecond PA measurements were performed on two ultrafast transient absorption set-ups: a broadband set-up that furnishes probe pulses spanning 550–750 nm and wavelength-tunable narrowband pump-pulses (10-nm bandwidth), and a two-colour set-up that uses tunable narrowband pulses (10-nm bandwidth) for both the pump and probe. The narrow pump-pulse bandwidth of both set-ups allows the selective excitation of the ZPL transition at 637 nm, after which the linearly polarized probe pulse measures the pump-induced change of the normalized transmission spectrum $\Delta T/T$. The time resolution is 80 fs (Supplementary Fig. 5). Signals for parallel ($S^{\parallel}$) and perpendicular ($S^{\perp}$) relative polarization between pump and probe pulses are recorded. The PA signal $S_{\text{aniso}}(\lambda, t)$ is then obtained from the relation $S_{\text{aniso}}(\lambda, t) = (S^{\parallel} - S^{\perp}) / (S^{\parallel} + 2S^{\perp})$. The typical pump fluence is ~ 1 mJ cm⁻², which yields a $\Delta T/T$ signal of 0.036 at the ZPL transition wavelength (Fig. 1c). Such a small $\Delta T/T$ value confirms that our measurements are performed in the weak-perturbative limit and higher-order contributions to the signal are negligible. The sample was mounted in either a liquid-nitrogen-cooled cryostat (broadband set-up, 77–400 K) or a closed-cycle helium-cooled cryostat (two-colour set-up, 10–300 K). Further details on the experimental set-up, as well as data processing and analysis procedures, can be found in the Supplementary Methods and Supplementary Figs 4–8.

AIMD simulations. We performed real-time atomistic simulations for anisotropy decay of an initially created dipole moment in the NV⁻ defect. The electronic structures of both ground and excited states as well as their state-specific MD simulations were obtained with the VASP software package using the Perdew–Burke–Ernzerhof (PBE) density functional and projector-augmented-wave pseudopotentials. The geometry of the NV⁻ defect comprises 1 nitrogen atom and 214 carbon atoms with an additional single electron to achieve the negatively charged NV⁻ centre. The NV⁻ defect was heated up to various temperatures ranging from 10 to 300 K by repeated velocity rescaling, and a 5-ps microcanonical trajectory at each temperature was calculated on the ground and excited E_x states using the Verlet algorithm with a 1-fs time step. In the excited state, we forced a spin-down electron to be located at the $\bar{e}_x$ orbital and removed symmetry constraints of the geometry. Real-time simulations for the PA decay were performed with the time-dependent NA electron–phonon coupling and orbital energies updated at every time step. Further details on the simulations can be found in the Supplementary Methods and Supplementary Figs 1–3, 9 and 10.

Data availability. The data that support the findings of this study are available from the corresponding authors upon reasonable request.

References

- Doherty, M. W. *et al.* The nitrogen-vacancy colour centre in diamond. *Phys. Rep.* **528**, 1–45 (2013).
- Hanson, R. & Awschalom, D. D. Coherent manipulation of single spins in semiconductors. *Nature* **453**, 1043–1049 (2008).
- Dobrovitski, V. V. *et al.* Quantum control over single spins in diamond. *Annu. Rev. Condens. Matter Phys.* **4**, 23–50 (2013).

4. Neumann, P. *et al.* Multipartite entanglement among single spins in diamond. *Science* **320**, 1326–1329 (2008).
5. Aharonovich, I., Greentree, A. D. & Prawer, S. Diamond photonics. *Nat. Photon.* **5**, 397–405 (2011).
6. Balasubramanian, G. *et al.* Nanoscale imaging magnetometry with diamond spins under ambient conditions. *Nature* **455**, 648–651 (2008).
7. Maze, J. R. *et al.* Nanoscale magnetic sensing with an individual electronic spin in diamond. *Nature* **455**, 644–647 (2008).
8. Schirhagl, R., Chang, K., Loretz, M. & Degen, C. L. Nitrogen-vacancy centers in diamond: nanoscale sensors for physics and biology. *Annu. Rev. Phys. Chem.* **65**, 83–105 (2014).
9. Acosta, V. M. *et al.* Temperature dependence of the nitrogen-vacancy magnetic resonance in diamond. *Phys. Rev. Lett.* **104**, 070801 (2010).
10. Laraoui, A. *et al.* Imaging thermal conductivity with nanoscale resolution using a scanning spin probe. *Nat. Commun.* **6**, 8954 (2015).
11. Neumann, P. *et al.* High-precision nanoscale temperature sensing using single defects in diamond. *Nano Lett.* **13**, 2738–2742 (2013).
12. Davies, G. & Hamer, M. F. Optical studies of 1.945 eV vibronic band in diamond. *Proc. R. Soc. Lond. A* **348**, 285–298 (1976).
13. Abtew, T. A. *et al.* Dynamic Jahn-Teller effect in the NV[−] center in diamond. *Phys. Rev. Lett.* **107**, 146403 (2011).
14. Domcke, W. & Yarkony, D. R. Role of conical intersections in molecular spectroscopy and photoinduced chemical dynamics. *Annu. Rev. Phys. Chem.* **63**, 325–352 (2012).
15. Yarkony, D. R. Diabolical conical intersections. *Rev. Mod. Phys.* **68**, 985–1013 (1996).
16. Worth, G. A. & Cederbaum, L. S. Beyond Born-Oppenheimer: molecular dynamics through a conical intersection. *Annu. Rev. Phys. Chem.* **55**, 127–158 (2004).
17. Fu, K. M. *et al.* Observation of the dynamic Jahn-Teller effect in the excited states of nitrogen-vacancy centers in diamond. *Phys. Rev. Lett.* **103**, 256404 (2009).
18. Bassett, L. C. *et al.* Ultrafast optical control of orbital and spin dynamics in a solid-state defect. *Science* **345**, 1333–1337 (2014).
19. Kaiser, F. *et al.* Polarization properties of single photons emitted by nitrogen-vacancy defect in diamond at low temperature. Preprint at <https://arxiv.org/abs/0906.3426> (2009).
20. Rogers, L. J., McMurtrie, R. L., Sellars, M. J. & Manson, N. B. Time-averaging within the excited state of the nitrogen-vacancy centre in diamond. *New J. Phys.* **11**, 063007 (2009).
21. Huxter, V. M., Oliver, T. A. A., Budker, D. & Fleming, G. R. Vibrational and electronic dynamics of nitrogen-vacancy centres in diamond revealed by two-dimensional ultrafast spectroscopy. *Nat. Phys.* **9**, 744–749 (2013).
22. Fleming, G. R. *Chemical Applications of Ultrafast Spectroscopy* (Oxford University Press, 1986).
23. Farrow, D. A. *et al.* Polarized pump-probe measurements of electronic motion via a conical intersection. *J. Chem. Phys.* **128**, 144510 (2008).
24. Qian, W. & Jonas, D. M. Role of cyclic sets of transition dipoles in the pump-probe polarization anisotropy: application to square symmetric molecules and perpendicular chromophore pairs. *J. Chem. Phys.* **119**, 1611–1622 (2003).
25. Wynne, K. & Hochstrasser, R. M. Coherence effects in the anisotropy of optical experiments. *Chem. Phys.* **171**, 179–188 (1993).
26. Hyeon-Deuk, K., Kobayashi, Y. & Tamai, N. Evidence of phonon-assisted Auger recombination and multiple exciton generation in semiconductor quantum dots revealed by temperature-dependent phonon dynamics. *J. Phys. Chem. Lett.* **5**, 99–105 (2014).
27. Zhang, J., Wang, C.-Z., Zhu, Z. Z. & Dobrovitski, V. V. Vibrational modes and lattice distortion of a nitrogen-vacancy center in diamond from first-principles calculations. *Phys. Rev. B* **84**, 035211 (2011).
28. Davies, G. Vibronic spectra in diamond. *J. Phys. C* **7**, 3797–3809 (1974).
29. Goldman, M. L. *et al.* Phonon-induced population dynamics and intersystem crossing in nitrogen-vacancy centers. *Phys. Rev. Lett.* **114**, 145502 (2015).
30. Shah, J. *Ultrafast Spectroscopy of Semiconductors and Semiconductor Nanostructures* (Springer, 1999).
31. Plakhotnik, T., Doherty, M. W. & Manson, N. B. Electron-phonon processes of the nitrogen-vacancy center in diamond. *Phys. Rev. B* **92**, 081203 (2015).
32. Leneff, A. *et al.* Electronic structure of the N-V center in diamond: experiments. *Phys. Rev. B* **53**, 13427–13440 (1996).
33. Acosta, V. M. *et al.* Dynamic stabilization of the optical resonances of single nitrogen-vacancy centers in diamond. *Phys. Rev. Lett.* **108**, 206401 (2012).
34. Wolters, J. *et al.* Measurement of the ultrafast spectral diffusion of the optical transition of nitrogen vacancy centers in nano-size diamond using correlation interferometry. *Phys. Rev. Lett.* **110**, 027401 (2013).
35. Borri, P. *et al.* Ultralong dephasing time in InGaAs quantum dots. *Phys. Rev. Lett.* **87**, 157401 (2001).
36. Accanto, N. *et al.* Engineering the spin-flip limited exciton dephasing in colloidal CdSe/CdS quantum dots. *ACS Nano* **6**, 5227–5233 (2012).

Acknowledgements

This work is supported by a start-up grant from NTU, funding from the A*Star Science and Engineering Research Council (122-PSF-0011 and 122 360 0008) and the Ministry of Education (MOE2014-T2-2-052), and the award of a Nanyang Assistant Professorship to Z.-H.L. K.H.-D. thanks the financial support from JST (PRESTO) and Grant-in-Aids for Scientific Research from Japan Society for the Promotion of Science (KAKENHI), Grant No 15K05386. R.U. acknowledges support by a Rubicon Grant of the Netherlands Organization for Scientific Research (NWO). We are grateful to D.M. Jonas, O.V. Prezhdo, H. Köppel, A. Gali, W. Peters and M. Cho for useful discussions, to R.U.A. Khan, Z. Wang and C. Soci for experimental assistance and to J. Schwartz for providing the sample.

Author contributions

R.U. and Z.-H.L. conceived and designed the project. R.U., S.D. and B.M.K.M. performed the experiments. R.U. and Z.-H.L. analysed the data. I.-Y.C. and K.H.-D. performed the simulations. R.U., K.H.-D. and Z.-H.L. wrote the manuscript, with input from all authors.

Additional information

Supplementary Information accompanies this paper at <http://www.nature.com/naturecommunications>

Competing financial interests: The authors declare no competing financial interests.

Reprints and permission information is available online at <http://npg.nature.com/reprintsandpermissions/>

How to cite this article: Ulbricht, R. *et al.* Jahn-Teller-induced femtosecond electronic depolarization dynamics of the nitrogen-vacancy defect in diamond. *Nat. Commun.* **7**, 13510 doi: 10.1038/ncomms13510 (2016).

Publisher's note: Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.

This work is licensed under a Creative Commons Attribution 4.0 International License. The images or other third party material in this article are included in the article's Creative Commons license, unless indicated otherwise in the credit line; if the material is not included under the Creative Commons license, users will need to obtain permission from the license holder to reproduce the material. To view a copy of this license, visit <http://creativecommons.org/licenses/by/4.0/>

© The Author(s) 2016