ARTICLE

Received 29 Nov 2012 | Accepted 14 Mar 2013 | Published 16 Apr 2013

DOI: 10.1038/ncomms2736

Optical visualization of individual ultralong carbon nanotubes by chemical vapour deposition of titanium dioxide nanoparticles

Rufan Zhang¹, Yingying Zhang², Qiang Zhang¹, Huanhuan Xie^{1,2}, Haidong Wang³, Jingqi Nie¹, Qian Wen¹ & Fei Wei¹

Direct visualization and manipulation of individual carbon nanotubes in ambient conditions is of great significance for their characterizations and applications. However, the observation of individual carbon nanotubes usually requires electron microscopes under high vacuum. Optical microscopes are much more convenient to be used, yet their resolution is low. Here we realize the visualization and manipulation of individual ultralong carbon nanotubes under optical microscopes by deposition of TiO₂ nanoparticles on them. The strong scattering of TiO₂ nanoparticles to visible light renders them visible by optical microscopes. Micro-Raman-spectroscopy measurement of individual carbon nanotubes is greatly facilitated by their optical visualization. With the assistance of TiO₂ nanoparticles, individual carbon nanotubes can be easily manipulated under an optical microscope at macroscopic scale and in ambient conditions. Based on our approach, various manipulation of ultralong carbon nanotubes, including cutting, transfer, fabrication of structures/devices and pulling out inner shells of multiwalled carbon nanotubes, are demonstrated.

¹Department of Chemical Engineering, Beijing Key Laboratory of Green Chemical Reaction Engineering and Technology, Tsinghua University, Beijing 100084, China. ²Center for Nano and Micro Mechanics, Tsinghua University, Beijing 100084, China. ³Key Laboratory for Thermal Science and Power Engineering of Ministry of Education, School of Aerospace, Tsinghua University, Beijing 100084, China. Correspondence and requests for materials should be addressed to Y.Y.Z. (email: yingyingzhang@tsinghua.edu.cn) or to F.W. (email: wf-dce@tsinghua.edu.cn).

The advance of material science always benefits from the development of modern characterization or operation techniques. Carbon nanotubes (CNTs) are undoubtedly one of the most attractive materials in the past two decades because of their superior properties and potential applications in many fields. Particularly, ultralong CNTs, with their perfect one-dimensional nanostructures and excellent properties, such as extraordinary mechanical strength, ultrahigh electron mobility and excellent electrical conductivity^{1–3}, are promising building blocks for high-performance fibres and nanodevices. However, the direct visualization, location and manipulation of individual CNTs, especially single or few-walled CNTs, is extremely difficult because of their nanosized diameters. Advanced analytical equipment, such as scanning electron microscope (SEM), transmission electron microscope (TEM) and atomic force microscope (AFM) and so on, has been employed to characterize the location, morphology and structure of CNTs. The *in-situ* manipulation of individual CNTs with the help of the above equipment has also been realized^{4–8}. However, all the above-mentioned techniques cannot guarantee the efficient location and manipulation of ultralong CNTs, because of their characteristics such as limited accessibility, requiring high vacuum, narrow field of view and/or small operating space.

Optical microscopes are routine facilities in many laboratories. Combining with the open-operation space of optical microscopes, if individual CNTs can be directly observed with an optical microscope, the *in-situ* observation and manipulation of ultralong CNTs will become much easier. However, the resolution of optical microscopes is much lower than that of SEM, TEM and AFM. Recently, various methods were proposed to 'see' CNTs optically, such as near-field Raman spectroscopy⁹ and fluorescence microscopy^{10–14}. However, the preparation of the samples and the identification of individual CNTs are quite complex and time-consuming by these techniques. Besides, an electro-deposition process of Ag nanoparticles (NPs)¹⁵ and a seeded electroless deposition process of Au NPs¹⁶ have been used to visualize individual CNTs on substrates under an optical microscope. Compared with CNTs sitting on substrates, suspended CNTs possess the pristine properties of CNTs and are convenient to be manipulated. However, the above strategies cannot be applied on suspended CNTs because of the fact that these processes are conducted in liquid phases that will destroy the suspended CNTs. Therefore, to explore the full potential of CNTs towards their future applications, a facile and nondestructive visualization method for individual suspended CNTs, especially for those with length up to several centimeters, is in great demand.

In this contribution, a facile and effective method to visualize individual suspended ultralong CNTs by deposition of TiO₂ NPs in a vapour phase is proposed. The strong scattering of TiO₂ NPs to visible light enables the CNTs to be easily observed under optical microscopes even at low magnification, which allows the direct manipulation of individual CNTs, even ultralong ones with length up to centimeters, under optical microscopes. Based on that, we demonstrate various manipulations of individual ultralong CNTs under an optical microscope.

Results

Deposition of TiO₂ NPs on individual ultralong CNTs. The process of depositing TiO₂ NPs on ultralong CNTs is illustrated in Fig. 1a–d and Supplementary Fig. S1. Suspended ultralong CNTs were grown by chemical vapour deposition^{1,17,18} on a silicon substrate containing many trenches (0.5–1 mm in width and 0.5 mm in depth). The as-grown CNTs were brought into contact with TiCl₄ vapour for *in-situ* deposition of TiO₂ NPs (see Methods section for details).

After the suspended CNTs contacted TiCl₄ for 1–7 s, many TiO₂ NPs deposited on the CNTs. Figure 1e–h show the necklace-like CNT TiO₂ hybrids. Most of the large TiO₂ NPs have spheric morphologies with diameters of 100–1,000 nm. Most of these spherical TiO₂ NPs completely wrap the suspended CNTs, forming coaxial structures (Fig. 1f–h). In contrast, other particles, especially those with small diameters (20–100 nm), usually adhere to the outer wall of suspended CNTs (Fig. 1e,f). Small TiO₂ NPs are distributed between adjacent large TiO₂ NPs. The interspace of the small NPs usually ranges from 20 to 1000 nm, whereas the interspace of larger NPs usually ranges from 1 to 5 μ m. Pristine CNT segments can be clearly observed between the particles. The ultralong CNT shown in Fig. 1f is a triple-walled CNT with a diameter of 3.5 nm (see the inset in Fig. 1f).

Compared with the deposition methods of TiO₂ NPs on CNTs reported previously^{19–25}, the vapour phase-directed deposition reported here is easy to be conducted and does not require the CNT surfaces to be pre-modified. Although a series of covalent and non-covalent methods have been reported to deposit metal^{26–30} or metal oxide NPs^{19–25,30–42} on CNTs, most of these methods require the CNTs to be functionalized or modified with surfactants^{39,42}, and the processes are conducted in liquid phases^{17–39,41,42}. These strategies cannot be applied on individual suspended ultralong CNTs because of the fact that they will destroy the suspended CNTs. Besides, atomic layer deposition⁴³, which avoids the use of liquid phases, has been used to conformably coat CNTs sitting on substrates^{41,43} or pre-functionalized suspended CNTs⁴⁴ with metal oxide films. In comparison, we realized the deposition of TiO₂ NPs on as-prepared suspended CNTs in a vapour phase. TiCl₄, which is a highly volatile metal halide, was used as the precursor for TiO₂ NPs. TiCl₄ forms misty smog of TiO₂ and HCl upon contact with humid air⁴⁵. When TiCl₄ vapour gets into contact with suspended CNTs, tiny TiO₂ NPs nucleate on the CNTs (Fig. 1b). The suspended CNTs have a role of templates in tailoring the size of TiO₂ NPs³⁵. The TiO₂ NPs are hydrophilic⁴⁶, whereas the pristine CNTs are hydrophobic⁴⁷. As a result, the following formed TiO₂ in the vapour phase prefers to deposit on the preformed TiO₂ nucleus. The –OH groups on the surface of TiO₂ NPs also catalyse TiCl₄ hydrolysis⁴⁸, resulting in the vapour phase epitaxial growth of the preformed TiO₂ NPs. The small TiO₂ NPs attached on the outer wall of the suspended CNTs gradually grow large and wrap the CNTs with the continuously growth, forming coaxial structures. Meanwhile, a large amount of newly nucleated TiO₂ NPs formed and adhered to the suspended CNTs. Therefore, small and large TiO₂ NPs coexist on the suspended CNTs. The interactions between the TiO₂ NPs and the CNTs is dominated by van der Waals force^{22,35}.

The contact time of CNTs with the TiCl₄ vapour and the air humidity have important roles in determining the diameter and number distribution of the TiO₂ NPs deposited on the suspended CNTs as reported previously²². As shown in Supplementary Fig. S2, the diameter and number of the TiO₂ NPs are proportional with the contact time and the relative air humidity. The size of the TiO₂ NPs on CNTs obeys a typical logarithmic normal distribution as shown in Supplementary Fig. S2a. Supplementary Table S1 shows the diameter and interspace distribution of TiO₂ NPs with different contact time. With the increase of contact time, the mean diameter of TiO₂ NPs (μ) increases, whereas the particle interspace decreases (Supplementary Fig. S2b). No matter what the interspace is, the variance of the interspace is $<0.1 \mu\text{m}^2$, indicating that the interspace of the TiO₂ NPs is uniform. The air humidity affects the hydrolysis rate of TiCl₄. The higher the air humidity, the larger the hydrolysis rate is. As a result, μ increases with the increase of air humidity (Supplementary Fig. S2c). When the relative air humidity is $>70\%$, the increasing trend of μ gradually slows down because of the hydrolysis rate reaching its limit.

Figure 1 | Deposition of TiO₂ NPs on ultralong CNTs. (a–d) Schematic illustration for depositing TiO₂ NPs on suspended CNTs. (e) TEM images of CNTs with small TiO₂ NPs prepared with contact time of 0.1–0.3 s. Scale bar, 200 nm. (f) TEM image of CNT with TiO₂ NPs with various sizes prepared with contact time of 7.0 s. Scale bar, 500 nm. Inset: high-resolution TEM image of the CNT shown in panel f. Scale bar, 5 nm. (g,h) SEM images of suspended CNTs decorated with TiO₂ NPs prepared with contact time of 5.0 s. Scale bar, 10 μ m (in g); 2 μ m (in h).

Optical visualization of individual ultralong CNTs. The diameters of most TiO₂ NPs (100–1,000 nm) are comparative with the wavelength of visible light (300–700 nm), rendering the TiO₂ NPs a strong Mie-scattering ability^{49–51}. The CNTs decorated with TiO₂ NPs can be easily observed and tracked under an optical microscope. Figure 2 shows typical optical images of suspended CNTs decorated with TiO₂ NPs. We can easily locate and track the suspended CNTs with the aid of TiO₂ NPs. Even when the suspended CNTs with TiO₂ NPs are broken and finally fall down onto the substrate, they can still be clearly observed (shown by the red arrow in Fig. 2a). No matter for what incident light intensity, the TiO₂ NPs always have a strong scattering ability to the incident light (Fig. 2a–c), especially in the dark field mode (Fig. 2b). The suspended CNTs decorated with TiO₂ NPs can be clearly observed even with a very low magnification ($\times 50$) of microscopes (Fig. 2d,e). Particularly, TiO₂ NPs as small as 100 nm (Fig. 2f, shown by arrow ‘3’) are still visible under the optical microscope. Furthermore, the TiO₂ NPs can be removed through an acid-washing method to facilitate their further characterizations and applications (Supplementary Fig. S3).

Discussion

Micro-Raman spectra measurement of individual CNTs is greatly facilitated by the optical visualization of individual CNTs. With the assistance of TiO₂ NPs, the position and orientation of the ultralong suspended CNTs can be easily identified under the optical microscope of micro-Raman-spectroscopy equipment. The laser spot can be focused on the pristine CNTs between two adjacent TiO₂ NPs (Fig. 3a,b), where strong Raman scattering signals are usually obtained. The deposition of TiO₂ NPs does not influence the Raman spectra of CNTs. Figure 3c shows the

Raman G-band of a CNT before and after deposition of TiO₂ NPs. The Raman spectra measured with and without TiO₂ NPs were almost the same (see Supplementary Discussion and Supplementary Fig. S4).

Furthermore, the visualization of individual CNTs under optical microscopes enabled by the deposition of TiO₂ NPs greatly facilitates the manipulation of individual CNTs in macro scale and ambient conditions. For example, with the assistance of TiO₂ NPs, ultralong CNTs can be cut and the as-obtained CNT segments can be used as samples for further characterization. Figure 4a shows a process of cutting and transferring a CNT segment. The cut-off CNT segments can be used for structural or property measurements, such as micro-Raman spectra measurement, TEM characterization and electrical measurement, facilitating the characterization of ultralong CNTs. Moreover, the CNT segments can be employed to fabricate complicated CNT architectures. Figure 4b shows a process to fabricate a CNT cross-structure, which can be completed within several minutes. More complicated CNT architectures could be fabricated in the same way. Note that all the above procedures were carried out under an optical microscope, which provides an open space for the manipulation of individual CNTs.

The optical visualization of individual CNTs also facilitates the design and fabrication of various devices. Figures 5a,b show that a suspended CNT can be bent by a gas flow, which can be used to monitor external gas flows. Accordingly, given a known gas velocity, this phenomenon can be used to measure the tensile strength and Young’s modulus of the suspended CNTs. Figure 5c,d show that a suspended CNT/TiO₂ chain oscillates under a sound wave, which can be monitored by an optical microscope. This phenomenon can be used to test the fatigue life of the suspended CNTs. Besides, an external electric field can also

Figure 2 | Optical images of suspended CNTs. (a,c) Bright field modes. The red arrow in panel **a** shows a broken CNT falling on the substrate. Scale bar, 100 μm (in **a**); 20 μm (in **c**). (b) Dark field mode. Scale bar, 100 μm . (d,e) Optical images with low magnification ($\times 50$). Scale bar, 1 mm. The light source in panel **d** is green laser, whereas the light source in panel **e** is visible light. (f) High-resolution optical image of a suspended CNT decorated with TiO_2 NPs. The small TiO_2 NPs indicated by the red arrows have diameters < 200 nm. Scale bar, 1 μm .

Figure 3 | TiO_2 NP-assisted micro-Raman spectra measurement of a suspended CNT. (a) Illustration for micro-Raman spectra measurement. (b) Optical image showing the position of laser spot (yellow circle) on the suspended CNTs for micro-Raman spectra measurement. Scale bar, 1 μm . (c) Raman spectra of the same CNT before (the red line) and after (the blue line) deposition of TiO_2 NPs.

be used to manipulate suspended CNT/ TiO_2 chain, exhibiting interesting behaviours (Supplementary Fig. S5). Similarly, more devices based on individual CNTs could be fabricated and more properties of individual CNTs could be measured with the TiO_2 NP-assisted optical visualization of CNTs.

Moreover, with the aid of TiO_2 NPs, the intershell sliding behaviours of ultralong multiwalled CNTs can be tracked and investigated in macroscopic scale under an optical microscope. Figure 6a shows a suspended double-walled CNT (DWCNT) (see its high-resolution TEM image in the upper inset in Fig. 6e) and a probe for manipulation. With the probe approaching and finally contacting with the CNT, the CNT firmly fixed to the probe due to the strong van der Waals force between them (Fig. 6b) (binders such as silver paste could be used for a better fixation effect). Then, the suspended CNT could be stretched by moving the probe in a certain direction. The TiO_2 NPs deposited on the suspended CNT are excellent markers to locate the outer shell of the CNT. During the process, the interspace of two adjacent NPs

(shown by two red arrows in Fig. 6c) suddenly had an increase, indicating that the outer shell of the DWCNT was broken. Although the pulled-out inner shell could not be observed directly under an optical microscope, its location and length could be determined from the broken ends of the outer shell. Figure 6d–e shows that the inner shell of the suspended DWCNT had been continuously pulled out, resulting in a 3.43-mm-long singlewalled CNT. Note that this is the longest inner tube pulled out from a multiwalled CNT, at least two orders of magnitude longer than that of previous reported results⁵². Moreover, if we fix a force cantilever onto the probe, the external force needed for pulling out the inner shell of the CNT and the friction between shells of the CNT could be measured. The tensile strength, breaking strain of the CNTs, could also be obtained.

In conclusion, the optical visualization of individual CNTs was realized by deposition of TiO_2 NPs on suspended ultralong CNTs in a vapour phase. TiO_2 NPs were uniformly deposited on suspended CNTs using TiCl_4 as the precursor, forming

Figure 4 | Cutting and transferring of individual CNTs and fabrication of a CNT cross-structure. (a) Cutting and transferring of individual CNTs (left: schematic illustration; right: optical images). (1) A suspended CNT with TiO₂ NPs. Scale bar, 50 μ m. (2) Four probes were moved onto the CNT to cut a CNT segment. Scale bar, 50 μ m. (3–6) A CNT segment (ca. 70 μ m) was cut off from the CNT. Scale bar, 50 μ m. Then the probes served as tweezers to transfer the CNT segment. (b) Cutting a CNT segment and fabricating a CNT cross-structure. (1) Cutting a CNT segment from a suspended CNT using two probes. Scale bar, 50 μ m. (2) Changing the position and orientation of the CNT segment. Scale bar, 50 μ m. (3) Moving the CNT segment onto another CNT and fabricating a CNT cross-structure. Scale bar, 50 μ m. (4) Deforming the CNT cross-structure by moving the probes. Scale bar, 50 μ m.

Figure 5 | Gas-flow-induced bending and sound-wave-induced oscillation of suspended CNTs. (a) A suspended CNT. Scale bar, 100 μ m. (b) Gas-flow-induced bending of the CNT. Scale bar, 100 μ m. (c) Illustration of oscillating a suspended CNT with sound wave. (d) Snapshot images of an oscillating CNT under sound wave. Scale bar, 100 μ m.

necklace-like CNT TiO₂ hybrids. With the strong scattering to visible light, the TiO₂ NPs could be easily observed under optical microscopes, enabling the facile location and tracking individual CNTs. Micro-Raman spectra measurement was greatly facilitated by the optical visualization of individual CNTs. Besides, with the assistance of TiO₂ NPs, direct manipulation of individual ultralong CNTs in macro scale and under ambient conditions could be easily carried out. We showed that, individual CNTs could be cut, transferred and fabricated into structures/devices. Moreover, we demonstrated the pulling out of an inner shell with a length up to 3.43 mm from a DWCNT under an optical microscope. Our results indicate that the TiO₂ NP-assisted optical visualization of individual CNTs greatly facilitates the characterization and manipulation of individual CNTs, and opens opportunities to explore macro-scale properties of individual

CNTs. Note that the NP-assisted optical visualization of CNTs could be easily applied on other nanomaterials, especially one-dimensional, suspended ones. More studies related to the macro-scale mechanical properties of individual ultralong CNTs based on this technique are under way in our laboratory.

Methods

Deposition of TiO₂ NPs on CNTs. The deposition process was conducted at room temperature in a fume hood, where there was a humidity controller to regulate and measure the relative air humidity (Supplementary Fig. S1). TiCl₄ liquid was controllably introduced into a beaker. The TiCl₄ liquid immediately formed misty smog of TiO₂ and HCl upon contact with humid air. The substrates with suspended CNTs were taken into contact with TiCl₄ vapour and TiO₂ smog for deposition of TiO₂ NPs. The contact time usually ranged from 3.0 to 7.0 s. After that, the substrates with suspended CNTs were taken away to terminate the deposition process.

Figure 6 | Pulling out the inner tube from a DWCNT. (a,b) Approaching a probe to a DWCNT and then contacting it. Scale bar, 100 μm . (c,d) Stretching the DWCNT and then pulling out its inner shell. Scale bar, 200 μm . (e) A 3.43-mm-long singlewalled CNT being pulled out from the DWCNT. Scale bar, 20 μm ; 2 nm (lower inset); 2 nm (upper inset).

Characterization. The CNTs were characterized by SEM (JSM 7401F, 1.0 kV), high-resolution TEM (JEM 2010, 120.0 kV) and Raman spectroscopy (Horiba HR 800, 632.8 nm). An optical microscope (long working distance metallography microscope, FS-70Z) was used for the optical characterization and manipulation of individual CNTs.

Cutting and transferring CNT segments. The substrate with suspended CNTs was put on the stage of an optical microscope. Four probes were fixed on two pedestals on the microscope framework. The probes could be moved precisely in X, Y and Z directions by wheeling the knobs fixed on the pedestals. The four probes were taken into contact with the suspended CNTs, forming two scissor-like structures to cut the CNT. After a CNT segment was cut off, the probes then served as tweezers to transfer the CNT segment.

Pulling out the inner tube from an individual DWCNT. When the suspended DWCNTs decorated with TiO_2 NPs were placed under an optical microscope, the probes were taken into contact with the suspended DWCNTs. Then, the DWCNT was stretched by moving the probes in a certain direction. The deformation of the DWCNT could be directly monitored under the optical microscope. AFM cantilevers could be fixed onto the probes by silver paste to measure the forces applied on the DWCNTs.

Gas-flow-induced bending of suspended CNTs. A steady air flow was introduced through a glass tube (5 cm in length and 1 mm in diameter) to blow the suspended CNTs decorated with TiO_2 NPs. The fixed ends of the CNTs remained fixed when the suspended part was stretched. The elongation of the suspended CNTs was recorded by a digital camera (Carnon, SX500 IS). The gas velocity of the air flow was controlled by a mass flow metre (Sevenstar, CS200A 100SCC).

Sound-wave-induced oscillation of suspended CNTs. The suspended CNT/ TiO_2 hybrids could be excited to oscillate by a sound wave from a loudspeaker linked to a signal generator (Tektronix, AFG3000C). The oscillation of the suspended CNTs was recorded by a digital camera (Carnon, SX500 IS).

Manipulation of suspended CNTs in an electric field. A minus voltage was applied on a suspended CNT, and a probe (with positive voltage) was used to attract the suspended CNT (Supplementary Fig. S5a). The suspended CNT is served as an electric field sensor and shows a quick response. Another example is shown in Supplementary Fig. S5b; a 60- μm long free-drooping CNT was fixed on a metal probe with another probe placed 120 μm away. When a voltage was applied between the two probes (left: 2 V; right: -2 V), the suspended CNT was immediately attracted to the left probe (Supplementary Fig. S5b (2)). Once the voltage was removed, the CNT immediately fell down back to a drooping state (Supplementary Fig. S5b (3)). However, when an equal voltage was applied between the two probes (for example, 2 V for both probes), the strong electric repulsion between the two probes immediately repelled the freely drooping CNT away to the right side (Supplementary Fig. S5b (4)). Once the voltage between the two probes was removed, the repelled CNT became drooping again. If the voltage difference between the two probes was applied again, the CNT would be immediately attracted to the left probe.

Removing of the TiO_2 NPs from CNT. A substrate with many TiO_2 NPs and short CNTs was put into a beaker containing 20 ml sulphuric acid solution (concentration 65%). $(\text{NH}_4)_2\text{SO}_4$ powder of 8 g was added into the sulphuric acid solution as a dissolving promoter. Then the solution was heated to boil for 2 h. Then the substrate out was taken out and the TiO_2 NPs could be completely removed.

References

- Zhang, R. F. *et al.* Superstrong ultralong carbon nanotubes for mechanical energy storage. *Adv. Mater.* **23**, 3387–3391 (2011).
- Wen, Q. *et al.* 100 mm long, semiconducting triple-walled carbon nanotubes. *Adv. Mater.* **22**, 1867–1871 (2010).
- Wang, X. S. *et al.* Fabrication of ultralong and electrically uniform single-walled carbon nanotubes on clean substrates. *Nano Lett.* **9**, 3137–3141 (2009).
- Thelander, C. & Samuelson, L. AFM manipulation of carbon nanotubes: realization of ultra-fine nanoelectrodes. *Nanotechnology* **13**, 108–113 (2002).
- Demczyk, B. G. *et al.* Direct mechanical measurement of the tensile strength and elastic modulus of multiwalled carbon nanotubes. *Mater. Sci. Eng. A* **334**, 173–178 (2002).
- Postma, H. W. C., Sellmeijer, A. & Dekker, C. Manipulation and imaging of individual single-walled carbon nanotubes with an atomic force microscope. *Adv. Mater.* **12**, 1299–1302 (2000).
- Yu, M. F. *et al.* Strength and breaking mechanism of multiwalled carbon nanotubes under tensile load. *Science* **287**, 637–640 (2000).
- Yu, M. F. *et al.* Three-dimensional manipulation of carbon nanotubes under a scanning electron microscope. *Nanotechnology* **10**, 244–252 (1999).
- Anderson, N., Hartschuh, A. & Novotny, L. Chirality changes in carbon nanotubes studied with near-field Raman spectroscopy. *Nano Lett.* **7**, 577–582 (2007).
- Duggal, R. & Pasquali, M. Dynamics of individual single-walled carbon nanotubes in water by real-time visualization. *Phys. Rev. Lett.* **96**, 246104 (2006).
- Chaudhary, S., Kim, J. H., Singh, K. V. & Ozkan, M. Fluorescence microscopy visualization of single-walled carbon nanotubes using semiconductor nanocrystals. *Nano Lett.* **4**, 2415–2419 (2004).
- Didenko, V. V., Moore, V. C., Baskin, D. S. & Smalley, R. E. Visualization of individual single-walled carbon nanotubes by fluorescent polymer wrapping. *Nano Lett.* **5**, 1563–1567 (2005).
- Otobe, K. *et al.* Fluorescence visualization of carbon nanotubes by modification with silicon-based polymer. *Nano Lett.* **2**, 1157–1160 (2002).
- Tsyboulski, D. A., Bachilo, S. M. & Weisman, R. B. Versatile visualization of individual single-walled carbon nanotubes with near-infrared fluorescence microscopy. *Nano Lett.* **5**, 975–979 (2005).
- Huang, S. *et al.* Identification of the structures of superlong oriented single-walled carbon nanotube arrays by electrodeposition of metal and Raman spectroscopy. *J. Am. Chem. Soc.* **130**, 11860–11861 (2008).
- Chu, H., Cui, R., Wang, J., Yang, J. & Li, Y. Visualization of individual single-walled carbon nanotubes under an optical microscope as a result of decoration with gold nanoparticles. *Carbon* **49**, 1182–1188 (2011).
- Wen, Q. *et al.* Growing 20 cm long DWNTs/TWNTs at a rapid growth rate of 80–90 $\mu\text{m/s}$. *Chem. Mater.* **22**, 1294–1296 (2010).
- Huang, S. M., Woodson, M., Smalley, R. & Liu, J. Growth mechanism of oriented long single walled carbon nanotubes using "fast-heating" chemical vapour deposition process. *Nano Lett.* **4**, 1025–1028 (2004).
- Llobet, E. *et al.* Carbon nanotube–TiO₂ hybrid films for detecting traces of O₂. *Nanotechnology* **19**, 375501 (2008).
- Eder, D. & Windle, A. H. Carbon–inorganic hybrid materials: the carbon–nanotube/TiO₂ interface. *Adv. Mater.* **20**, 1787–1793 (2008).
- Darányi, M. *et al.* Layer-by-layer assembly of TiO₂ nanowire/carbon nanotube films and characterization of their photocatalytic activity. *Nanotechnology* **22**, 195701 (2011).
- Eder, D. & Windle, A. H. Morphology control of CNT–TiO₂ hybrid materials and rutile nanotubes. *J. Mater. Chem.* **18**, 2036–2043 (2008).
- Zhao, Y. *et al.* Super-long aligned TiO₂/carbon nanotube arrays. *Nanotechnology* **21**, 505702 (2010).
- Mishra, A., Banerjee, S., Mohapatra, S. K., Graeve, O. A. & Misra, M. Synthesis of carbon nanotube–TiO₂ nanotubular material for reversible hydrogen storage. *Nanotechnology* **19**, 445607 (2008).
- Liang, Y., Wang, H., Sanchez Casalongue, H., Chen, Z. & Dai, H. TiO₂ nanocrystals grown on graphene as advanced photocatalytic hybrid materials. *Nano Res.* **3**, 701–705 (2010).
- Aksel, S. & Eder, D. Catalytic effect of metal oxides on the oxidation resistance in carbon nanotube–inorganic hybrids. *J. Mater. Chem.* **20**, 9149–9154 (2010).
- Guldi, D. M. *et al.* CNT–CdTe versatile donor–acceptor nanohybrids. *J. Am. Chem. Soc.* **128**, 2315–2323 (2006).
- Li, H. *et al.* A general and efficient route to fabricate carbon nanotube–metal nanoparticles and carbon nanotube–inorganic oxides hybrids. *Adv. Funct. Mater.* **20**, 3864–3873 (2010).
- Tang, H. *et al.* High dispersion and electrocatalytic properties of platinum on well-aligned carbon nanotube arrays. *Carbon* **42**, 191–197 (2004).
- Lee, Y., Song, H. J., Shin, H. S., Shin, H. J. & Choi, H. C. Spontaneous formation of transition-metal nanoparticles on single-walled carbon nanotubes anchored with conjugated molecules. *Small* **1**, 975–979 (2005).
- Eder, D. Carbon nanotube–inorganic hybrids. *Chem. Rev.* **110**, 1348–1385 (2010).
- Tasis, D., Tagmatarchis, N., Bianco, A. & Prato, M. Chemistry of carbon nanotubes. *Chem. Rev.* **106**, 1105–1136 (2006).
- Han, W. Q. & Zettl, A. Coating single-walled carbon nanotubes with tin oxide. *Nano Lett.* **3**, 681–683 (2003).
- Krissanasraerane, M., Wongkasemjit, S., Cheetham, A. K. & Eder, D. Complex carbon nanotube–inorganic hybrid materials as next-generation photocatalysts. *Chem. Phys. Lett.* **496**, 133–138 (2010).
- Georgakilas, V. *et al.* Decorating carbon nanotubes with metal or semiconductor nanoparticles. *J. Mater. Chem.* **17**, 2679–2694 (2007).
- Li, H., Ha, C. S. & Kim, I. Fabrication of carbon nanotube/SiO₂ and carbon nanotube/SiO₂/Ag nanoparticles hybrids by using plasma treatment. *Nano. Res. Lett.* **4**, 1384–1388 (2009).
- Neocleus, S., Pattinson, S., Motta, A. M. M., Windle, A. & Eder, D. Hierarchical carbon nanotube–inorganic hybrid structures involving CNT arrays and CNT fibres. *Funct. Mater. Lett.* **4**, 83–89 (2011).
- Shan, Y. & Gao, L. Multiwalled carbon nanotubes/Co₃O₄ nanocomposites and its electrochemical performance in lithium storage. *Chem. Lett.* **33**, 1560–1561 (2004).
- Li, X., Qin, Y., Picraux, S. & Guo, Z. X. Noncovalent assembly of carbon nanotube–inorganic hybrids. *J. Mater. Chem.* **21**, 7527–7547 (2011).
- Zhan, Y. *et al.* A novel carbon nanotubes/Fe₃O₄ inorganic hybrid material: synthesis, characterization and microwave electromagnetic properties. *J. Magn. Magn. Mater.* **323**, 1006–1010 (2011).
- Javey, A. *et al.* Self-aligned ballistic molecular transistors and electrically parallel nanotube arrays. *Nano Lett.* **4**, 1319–1322 (2004).
- Holzinger, M. *et al.* Sidewall functionalization of carbon nanotubes. *Angew. Chem. Int. Ed.* **40**, 4002–4005 (2001).
- Hausmann, D. M., Kim, E., Becker, J. & Gordon, R. G. Atomic layer deposition of hafnium and zirconium oxides using metal amide precursors. *Chem. Mater.* **14**, 4350–4358 (2002).
- Farmer, D. B. & Gordon, R. G. Atomic layer deposition on suspended single-walled carbon nanotubes via gas-phase noncovalent functionalization. *Nano Lett.* **6**, 699–703 (2006).
- Rigo, M., Canu, P., Angelin, L. & Della Valle, G. Kinetics of TiCl₄ hydrolysis in a moist atmosphere. *Ind. Eng. Chem. Res.* **37**, 1189–1195 (1998).
- Sakai, N., Wang, R., Fujishima, A., Watanabe, T. & Hashimoto, K. Effect of ultrasonic treatment on highly hydrophilic TiO₂ surfaces. *Langmuir* **14**, 5918–5920 (1998).
- Hummer, G., Rasaiah, J. C. & Noworyta, J. P. Water conduction through the hydrophobic channel of a carbon nanotube. *Nature* **414**, 188–190 (2001).
- Li, Y., Fan, Y. & Chen, Y. A novel method for preparation of nanocrystalline rutile TiO₂ powders by liquid hydrolysis of TiCl₄. *J. Mater. Chem.* **12**, 1387–1390 (2002).
- Mishchenko, M. I., Travis, L. D. & Lacis, A. A. *Scattering, Absorption, and Emission of Light by Small Particles* (Cambridge university press, 2002).
- Kerker, M. *The Scattering of Light* (Academic Press, New York, 1969).
- Huber, E. & Frost, M. Light scattering by small particles. *Aqua* **47**, 87–94 (1998).
- Hong, B. H. *et al.* Extracting subnanometer single shells from ultralong multiwalled carbon nanotubes. *Proc. Natl Acad. Sci. USA* **102**, 14155–14158 (2005).

Acknowledgements

The work is supported by the Foundation for the National Basic Research Program of China (2011CB932602 and 2013CB934200).

Author contributions

F.W. proposed and supervised the project. R.Z. designed and performed the experiments and wrote the manuscript. Y.Y.Z. co-supervised the project and designed the outline of the manuscript. Q.Z. and Q.W. participated in data analysis and the manuscript preparation. H.X. participated in the synthesis of ultralong CNTs. H.W. conducted the Raman characterization. J.N. helped with the TEM characterization.

Additional information

Supplementary Information accompanies this paper at <http://www.nature.com/naturecommunications>

Competing financial interests: The authors declare no competing financial interests.

Reprints and permission information is available online at <http://npg.nature.com/reprintsandpermissions/>

How to cite this article: Zhang, R. *et al.* Optical visualization of individual ultralong carbon nanotubes by chemical vapour deposition of titanium dioxide nanoparticles. *Nat. Commun.* 4:1727 doi: 10.1038/ncomms2736 (2013).