NEWS & VIEWS

Open Access

Towards next generation white LEDs: optics-electronics synergistic effect in a single-layer heterophase halide perovskite

Andrey L. Rogach ¹

Abstract

A novel concept of the *heterophase optics-electronics synergistic effect* has been demonstrated in a single-layer α/δ -heterophase perovskite CsPbI₃ in order to realize white LEDs featuring only one broadband emissive layer.

Light sources have been under steady development all the way throughout the human existence, from ancient times to the modern technology, and sources of lighting experienced changes from fire to electricity. Since the dawn of the first semiconductor light-emitting diodes (LEDs), these devices showed many advantages over traditional incandescent or fluorescent lighting, such as high luminous efficiency, energy saving, and color quality¹. Traditional approach to realize white LEDs (WLEDs) relies on the down-conversion of light emitted by a combination of red (R) and green (G) phosphors excited by blue (B) light, or on electrical excitation of RGB emitters arranged into LED arrays^{2,3}. However, the use of the rare-earth elements in down-conversion devices faces issues of high cost and scarcity, and the most common blue-emitting component of such LEDs (GaN) is fabricated through rather expensive epitaxial growth techniques. Thus, exploring new technologies for lighting which may lead to more cost-efficient WLEDs is highly desired.

Halide perovskites have recently attracted a lot of attention as promising monochromatic bright emitters able to offer high-quality light in LEDs⁴. External quantum efficiencies (EQE) of perovskite-based green and red LEDs already exceeded 20%^{5,6}. Despite a great progress on monochromatic perovskite LEDs, development of perovskite WLEDs has been rather slow, so far, and mostly relied on the doping with other elements^{7,8}. High rate of

anion diffusion in mixed-halide perovskite materials, combined with non-balanced degradation under working conditions severely hinder the use of the LED arrays due to the rapid change of emission color⁹. Moreover, efficiencies and stabilities of blue perovskite LEDs still lag behind their red and green counterparts¹⁰, so that more efforts are needed for their development. Very recently, Chen and co-workers used an advanced device structure that could efficiently suppress the trapped optical modes¹¹. It comprised a layer of red-emitting perovskite nanocrystals acting as a down-converter, coated on a blue perovskite LED with an ultra-thin transparent top electrode. An efficient extraction of the trapped waveguide mode and surface plasmon polariton mode in the blue LED was realized, leading to over 50% improvement in a light-extraction efficiency, and also efficient blue-to-red light conversion, resulting in a complementary white light emission with a high EQE of 12%.

In another approach, Zeng's group at Nanjing University of Science and Technology (NJUST) in collaboration with D. Ginger at the University of Washington proposed a new concept of WLEDs relying on a *single emissive layer* of CsPbI₃ perovskite which combined α and δ -phases (Fig. 1a)¹². EQE and current efficiency of these WLEDs which were conveniently fabricated by all-solution processing and featured only one broadband perovskite emitting layer reached 6.5% and 12,200 cd/m², respectively. Importantly, by adjusting the annealing processes of α -CsPbI₃, the ratio of the two phases could be controlled to tailor the color temperature of white emission (Fig. 1b).

Correspondence: Andrey L. Rogach (andrey.rogach@cityu.edu.hk)

¹Department of Materials Science and Engineering, and Centre for Functional Photonics (CFP), City University of Hong Kong, Hong Kong SAR, PR China

Fig. 1 WLEDs relying on a single emissive layer of a heterophase cesium lead halide perovskite. **a** Scheme of the WLED structure relying on a synergistic effect of α - and δ -CsPbI₃ perovskite heterophases. **b** Broad electroluminescence spectrum of the WLED; photograph in the inset shows its uniform white emission. **c** Charge transfer and recombination mechanism operative in the α/δ -CsPbI₃ heterophase WLED (STE stays for “self-trapped exciton”)

The major idea of operation of these WLEDs relied on a synergistic effect between α/δ -CsPbI₃ phases (Fig. 1c): charge carrier injection occurred in the α -CsPbI₃ phase, which was followed by charge transfer from α - to δ -phases, and white light emission by δ -CsPbI₃. The interfacial states which are energetically closer to the valence band (VB) level of α -CsPbI₃ assisted hole transfer from α -CsPbI₃ to δ -CsPbI₃, while the conduction band (CB) alignment between α -CsPbI₃ and δ -CsPbI₃ phases allowed for an optimum electron injection and an efficient radiative recombination. The authors have termed this mechanism “*heterophase optics-electronics synergistic effect*”.

The strategy used in ref. ¹² relying on a single emitting perovskite layer to achieve white emission can greatly decrease the cost of production of WLEDs, and further

push the development of next-generation flexible displays and lighting. This approach, as well as the one suggested in ref. ¹¹ may also have important implications not only for LEDs but for perovskite optoelectronics in general, such as for solar cells and displays.

Published online: 01 March 2021

References

1. Cho, J. et al. White light-emitting diodes: history, progress, and future. *Laser Photonics Rev.* **11**, 1600147 (2017).
2. Ma, Z. Z. et al. High color-rendering index and stable white light-emitting diodes by assembling two broadband emissive self-trapped excitons. *Adv. Mater.* **33**, 2001367 (2021).
3. Liu, S. N. et al. A controllable and reversible phase transformation between all-inorganic perovskites for white light emitting diodes. *J. Mater. Chem. C* **8**, 8374–8379 (2020).

4. Song, J. Z. et al. Quantum dot light-emitting diodes based on inorganic perovskite cesium lead halides (CsPbX_3). *Adv. Mater.* **27**, 7162–7167 (2015).
5. Lin, K. B. et al. Perovskite light-emitting diodes with external quantum efficiency exceeding 20 per cent. *Nature* **562**, 245–248 (2018).
6. Cao, Y. et al. Perovskite light-emitting diodes based on spontaneously formed submicrometre-scale structures. *Nature* **562**, 249–253 (2018).
7. Hou, S. C. et al. Efficient blue and white perovskite light-emitting diodes via manganese doping. *Joule* **2**, 2421–2433 (2018).
8. Sun, R. et al. Samarium-doped metal halide perovskite nanocrystals for single-component electroluminescent white light-emitting diodes. *ACS Energy Lett.* **5**, 2131–2139 (2020).
9. Mao, J. et al. All-perovskite emission architecture for white light-emitting diodes. *ACS Nano* **12**, 10486–10492 (2018).
10. Lu, M. et al. Metal halide perovskite light-emitting devices: promising technology for next-generation displays. *Adv. Funct. Mater.* **29**, 1902008 (2019).
11. Chen, Z. M. et al. Utilization of trapped optical modes for white perovskite light-emitting diodes with efficiency over 12%. *Joule* <https://doi.org/10.1016/j.joule.2020.12.008> (2021).
12. Chen, J. W. et al. Efficient and bright white light-emitting diodes based on single-layer heterophase halide perovskites. *Nat. Photonics* <https://doi.org/10.1038/s41566-020-00743-1> (2020).