Author Correction: Effect of polymer type on the performance of a nanofiber mat actuator

Hanako Asai¹ · Tomotaka Okumura¹ · Hiroaki Sakamoto¹ · Koji Nakane¹

Published online: 25 March 2019
© The Society of Polymer Science, Japan 2019

Correction to: Polymer Journal;

<https://doi.org/10.1038/s41428-018-0160-5>;
published online 17 December 2018

In the original published version of Table 1 and Table S1, the conductivity values are incorrect. The corrected Tables are as shown below.

Table 1 Characteristics of the three nanofiber mat electrodes

Polymer type	Diameter of the fiber [μm]	Conductivity [S/m]	Specific surface area [m ² g ⁻¹]
PU	0.425 ± 0.087	3.0 × 10 ²	4.94
PMMA	1.35 ± 0.18	2.0 × 10 ²	3.23
PVDF-HFP	0.501 ± 0.130	50	4.09

Table S1 The effect of additives on the conductivity of PMMA nanofiber mat

DMSO	Surfactant	Conductivity [S/m]
—	—	0.13
—	○	30
○	—	29
○	○	2.0 × 10 ²

✉ Hanako Asai
h_asai@u-fukui.ac.jp

¹ Frontier Fiber Technology and Science, Graduate School of Engineering, University of Fukui, 3-9-1 Bunkyo, Fukui 910-8507, Japan