ARTICLE OPEN

Coexistence of metallic and nonmetallic properties in the pyrochlore $\text{Lu}_2\text{Rh}_2\text{O}_7$ Alannah M. Hallas^{1,2}, Arzoo Z. Sharma³, Cole Mauws³, Qiang Chen⁴, Haidong D. Zhou⁴, Cui Ding⁵, Zizhou Gong⁶, Makoto Tachibana⁷, Paul M. Sarte^{8,9}, J. Paul Attfield^{8,9}, Graeme M. Luke^{1,10,11} and Christopher R. Wiebe^{1,3,11,12}

Transition metal oxides of the 4d and 5d block have recently become the targets of materials discovery, largely due to their strong spin–orbit coupling that can generate exotic magnetic and electronic states. Here, we report the high-pressure synthesis of $\text{Lu}_2\text{Rh}_2\text{O}_7$, a new cubic pyrochlore oxide based on $4d^5 \text{Rh}^{4+}$, and characterizations via thermodynamic, electrical transport, and muon spin relaxation measurements. Magnetic susceptibility measurements reveal a large temperature-independent Pauli paramagnetic contribution, while heat capacity shows an enhanced Sommerfeld coefficient, $\gamma = 21.8(1) \text{ mJ/mol-Rh K}^2$. Muon spin relaxation measurements confirm that $\text{Lu}_2\text{Rh}_2\text{O}_7$ remains paramagnetic down to 2 K. Taken in combination, these three measurements suggest that $\text{Lu}_2\text{Rh}_2\text{O}_7$ is a correlated paramagnetic metal with a Wilson ratio of $R_W = 2.5$. However, electric transport measurements present a striking contradiction as the resistivity of $\text{Lu}_2\text{Rh}_2\text{O}_7$ is observed to monotonically increase with decreasing temperature, indicative of a nonmetallic state. Furthermore, although the magnitude of the resistivity is that of a semiconductor, the temperature dependence does not obey any conventional form. Thus, we propose that $\text{Lu}_2\text{Rh}_2\text{O}_7$ may belong to the same novel class of non-Fermi liquids as the nonmetallic metal FeCrAs .

npj Quantum Materials (2019)4:9; <https://doi.org/10.1038/s41535-019-0148-1>

INTRODUCTION

The electronic and magnetic properties of many transition metal oxides can be understood by considering three energy scales: (i) the on-site Coulomb repulsion, Hubbard U , (ii) the band width, W , and (iii) the spin–orbit coupling, λ . The strong-coupling limit of this paradigm occurs for 3d oxides where Hubbard repulsion dominates ($U/W \gg 1$) and spin–orbit coupling ($\lambda \propto Z^4$) is negligible. As a consequence, Mott insulating states are observed in many materials that one would expect to be metals from band theory, as exemplified by the parent compounds of the high-temperature cuprate superconductors.¹ The opposing limit occurs for 5d oxides, where the d electron orbitals are far more spatially delocalized such that U decreases while W increases ($U/W \approx 1$). At the same time, the large mass enhancement brings spin–orbit coupling to the forefront, giving rise to remarkable correlated states such as topological insulators, Weyl semi-metals, and spin–orbit assisted Mott insulators.² Intermediate to these two limits is the 4d oxides, where U , W , and λ can all be comparable in magnitude.

The chemically versatile pyrochlore oxides, $A_2B_2O_7$, are an excellent family of materials to explore the competition between U , W , and λ . In this structure, the A site is usually occupied by a rare earth cation, while the B site can be occupied by transition or post-transition metals from the 3d, 4d, or 5d block. Consequently, a wide assortment of electronic behaviors are observed, ranging from band insulators to correlated metals. Pyrochlores are also of

significant interest for their magnetic properties. The corner-sharing tetrahedral arrangement of the A and B cation sublattices is prone to intense geometric frustration, which has been extensively studied in the insulating families.³ The metallic pyrochlore oxides provide an intriguing platform for studying the interplay of geometric frustration and metallic degrees of freedom, an emerging topic that has begun to garner significant attention.^{4–9} Whereas frustration in local moment systems can straightforwardly be identified via the so-called frustration index, $f = |\theta_{CW}|/T_N$,¹⁰ no equivalent metric has yet been established for itinerant magnetic materials. Hence, how to unambiguously identify the presence of frustration in an itinerant system remains an open problem. A recent study broached this topic by using inelastic neutron scattering to extract exchange couplings which were then compared to a local moment picture.⁹

In the rare earth pyrochlores, the 4f electrons from the A -site cation are highly localized and do not participate in electrical conduction. Thus, the electronic properties of pyrochlore materials are largely governed by the choice of B -site cation.¹¹ Insulating states are expected and observed in cases where there are no partially filled d -electron orbitals, such as when $B = \text{Ti}^{4+}$, Ge^{4+} , Sn^{4+} , and Zr^{4+} . Due to their dominant Hubbard U , insulating or semiconducting states are also found in the majority of cases where B has a partially occupied 3d shell, such as $B = \text{Mn}^{4+}$ and Cr^{4+} . Semiconducting states are found for a number of pyrochlores with partially filled 4d or 5d-shells, such as those

¹Department of Physics and Astronomy, McMaster University, Hamilton, ON L8S 4M1, Canada; ²Department of Physics and Astronomy and Rice Center for Quantum Materials, Rice University, Houston, TX 77005, USA; ³Department of Chemistry, University of Manitoba, Winnipeg, MB R3T 2N2, Canada; ⁴Department of Physics and Astronomy, University of Tennessee-Knoxville, Knoxville, TN 37996-1220, USA; ⁵Department of Physics, Zhejiang University, Hangzhou 310027, China; ⁶Department of Physics, Columbia University, New York, NY 10027, USA; ⁷National Institute for Materials Science, 1-1 Namiki, Tsukuba 305-0044 Ibaraki, Japan; ⁸School of Chemistry, University of Edinburgh, Edinburgh EH9 3FJ, UK; ⁹Centre for Science at Extreme Conditions, University of Edinburgh, Edinburgh EH9 3FD, UK; ¹⁰TRIUMF, 4004 Wesbrook Mall, Vancouver, BC V6T 2A3, Canada; ¹¹Canadian Institute for Advanced Research, Toronto, ON M5G 1Z7, Canada and ¹²Department of Chemistry, University of Winnipeg, Winnipeg, MB R3B 2E9, Canada
Correspondence: Alannah M. Hallas (alannah.hallas@gmail.com) or Christopher R. Wiebe (chris.r.wiebe@gmail.com)

Received: 26 October 2018 Accepted: 3 February 2019

Published online: 01 March 2019

with $B = \text{Mo}^{4+}$, Ru^{4+} , and Pt^{4+} . Pyrochlores with metallic states are fewer in number, with notable examples being found amongst the $B = \text{Os}^{5+}$, Re^{5+} , and Ir^{4+} families. In these systems, large spin-orbit coupling results in fascinating correlated electron phenomena. For instance, the iridate family of pyrochlores have been lauded as candidates for topological electronic states.¹² Meanwhile, $\text{Cd}_2\text{Re}_2\text{O}_7$ is a moderately heavy fermion metal, $\gamma = 13.3 \text{ mJ/mol-Re K}^2$,¹³ with a superconducting transition at $T_C = 1.47 \text{ K}$.¹⁴ In the case of $\text{Cd}_2\text{Os}_2\text{O}_7$, the entanglement of spin, orbital, and lattice degrees of freedom drives a metal-to-insulator transition at 226 K concomitant with antiferromagnetic order.^{15–18} Here, we introduce a new $4d$ pyrochlore, $\text{Lu}_2\text{Rh}_2\text{O}_7$, where we expect that U , W , and λ are all comparable in magnitude, giving rise to an exotic non-Fermi liquid state.

The magnetism in $\text{Lu}_2\text{Rh}_2\text{O}_7$ originates from $4d^5 \text{ Rh}^{4+}$ while $4f^{14} \text{ Lu}^{3+}$ is non-magnetic. Although several $4d^5$ rhodate pyrochlores have been previously reported,^{19,20} their characterization has been negligible, especially in contrast to their $5d^5$ iridate analogs. This can, in part, be attributed to the difficulty in stabilizing rhodium in its $4+$ oxidation state, which we overcome using high-pressure methods. In the pyrochlore lattice, Rh^{4+} sits at the center of a trigonally distorted octahedral oxygen environment with D_{3d} point group symmetry. As schematically presented in Fig. 1a, the crystal electric field and moderately strong spin-orbit coupling ($\lambda = 0.19 \text{ eV}$ for Rh in contrast with $\lambda = 0.40 \text{ eV}$ for Ir ²¹) split the d electron states into a filled $j_{\text{eff}} = 3/2$ band and a half-occupied $j_{\text{eff}} = 1/2$ band. Thus, akin to the $5d^5$ iridates,²² the $4d^5$ rhodates can have a $j_{\text{eff}} = 1/2$ magnetic degree of freedom, leading to a spin-orbit induced Mott insulating state.²³ Both theoretical calculations and direct spectroscopic measurements have confirmed the applicability of the $j_{\text{eff}} = 1/2$ picture in other rhodate

materials.^{17,24} However, even in cases where λ is not large enough to reach the pure $j_{\text{eff}} = 1/2$ limit, as is likely the case in $\text{Lu}_2\text{Rh}_2\text{O}_7$, the influences of spin-orbit coupling are still strongly felt.^{25,26} We have characterized the magnetic and electronic properties of $\text{Lu}_2\text{Rh}_2\text{O}_7$ with magnetic susceptibility, heat capacity, resistivity, and muon spin relaxation (μSR) measurements. These measurements reveal an apparent contradiction: magnetic susceptibility, heat capacity, and μSR are consistent with a strongly correlated paramagnetic metal. Resistivity data on the other hand suggests an unconventional semiconducting state and hence, a gap in the density of states. Thus, we propose that $\text{Lu}_2\text{Rh}_2\text{O}_7$ belongs to the class of “nonmetallic metals” a term coined to describe the behavior of FeCrAs .^{27,28}

RESULTS

Under strongly oxidizing conditions, $\text{Lu}_2\text{Rh}_2\text{O}_7$ crystallizes in the pyrochlore structure (space group $Fd\bar{3}m$). The powder x-ray diffraction pattern, which is presented in Fig. 1b, was analyzed via Rietveld refinement, giving a cubic lattice parameter of $a = 10.0265(1) \text{ \AA}$. The ratio of the ionic radii for Lu^{3+} (86.1 pm) and Rh^{4+} (60 pm) is within the stability range for the pyrochlore structure.¹¹ Thus, significant levels of A/B site mixing are neither expected nor observed. The only adjustable coordinate within the pyrochlore structure is the $\text{O}2x$ position, which we refine to $x = 0.3296(5)$. When $x = 0.3125$, the oxygen environment at the B -site is an ideal octahedron (point group O_h). Deviations from this value induce a compression along the local $[111]$ axis, as shown in Fig. 1a, such that the six equidistant oxygen ions have alternating bond angles of 93.5° and 86.5° with the central Rh^{4+} cation (point group D_{3d}). A small RhO_2 impurity, comprising $2.1(2)\%$ of the total sample volume, was included as a second phase in the Rietveld refinements (a tetragonal structure with space group $P4_2/mnm$).^{29,30} RhO_2 is a high-pressure metallic oxide phase which is insoluble in aqua regia and could not be removed from our samples. The results of the Rietveld refinement, including the goodness-of-fit parameters, are listed in Table 1.

The magnetic susceptibility of $\text{Lu}_2\text{Rh}_2\text{O}_7$ measured in an $H = 1 \text{ T}$ field is presented in Fig. 2. We have corrected the data for core diamagnetism using the values tabulated in ref. ³¹, which gives $\chi_D = -1.54 \cdot 10^{-4} \text{ emu/F.U.}$ There is no appreciable difference between data collected under zero-field cooled or field cooled conditions. $\text{Lu}_2\text{Rh}_2\text{O}_7$ is paramagnetic down to the lowest measured temperature, with no evidence for magnetic ordering or spin freezing down to 2 K . The susceptibility is dominated by a large nearly temperature independent Pauli paramagnetic contribution. Below 10 K , the intrinsic susceptibility is obscured by a Curie-tail. We observe a shallow, broad hump in the susceptibility centered near 50 K . As can be seen in Fig. 2, the inverse susceptibility between 100 and 300 K is reasonably well-described by a Curie-Weiss equation, $\chi = \frac{C}{T - \theta}$, where we obtain $\theta = -1393(2) \text{ K}$ and $\mu_{\text{eff}} = \sqrt{8C} = 3.1(1) \mu_B$. Clearly, this magnitude of θ is not physically meaningful as the susceptibility is dominated by the Pauli paramagnetic contribution. However, attempts to model the susceptibility to a modified Curie-Weiss

Fig. 1 **a** The $4d^5 \text{ Rh}^{4+}$ cations in $\text{Lu}_2\text{Rh}_2\text{O}_7$ sit at the center of a trigonally distorted (D_{3d}) octahedral oxygen environment. Strong spin-orbit coupling will further split the t_{2g} states into a filled $j_{\text{eff}} = 3/2$ and a half-filled $j_{\text{eff}} = 1/2$ state; however, this limit may not be fully reached for Rh^{4+} with moderate spin-orbit coupling. **b** Powder x-ray diffraction pattern and Rietveld refinement for $\text{Lu}_2\text{Rh}_2\text{O}_7$ measured at $T = 300 \text{ K}$ with a copper $K_{\alpha 1}$ wavelength ($\lambda = 1.5406 \text{ \AA}$). The Bragg peak positions for the $Fd\bar{3}m$ pyrochlore phase are indicated by the upper set of crosses. The lower set of crosses are from a minor RhO_2 impurity accounting for 2% of the sample volume. The results of the refinement are shown in Table 1

Table 1. Refined lattice positions and temperature factors for $\text{Lu}_2\text{Rh}_2\text{O}_7$ where the goodness of fit parameters are $R_p = 7.34$, $R_{wp} = 10.9$, $R_{exp} = 6.27$ and $\chi^2 = 3.02$

	x	y	z	B_{iso}	site
Lu	0.5	0.5	0.5	0.52(4)	16d
Rh	0	0	0	0.28(5)	16c
O1	0.375	0.375	0.375	0.4(2)	8b
O2	0.3296(5)	0.125	0.125	0.4(2)	48f

law, $\chi = \frac{C}{T-\theta} + \chi_0$, failed to produce a unique solution. Instead, we proceed by subtracting the Curie-tail contribution, which we fit to $\chi \propto \frac{C}{T}$, allowing us to estimate the low-temperature Pauli paramagnetic contribution as $\chi_P = 7.6 \cdot 10^{-4}$ emu/mol-Rh. This value is nearly an order of magnitude larger than in typical metals, signaling strong electron correlation effects. The induced magnetization at 2 K and 7 T is only $0.01 \mu_B/\text{Rh}^{4+}$, consistent with an itinerant paramagnetic state (inset of Fig. 2). The susceptibility and magnetization data for $\text{Lu}_2\text{Rh}_2\text{O}_7$ bear a striking resemblance to that of SrRhO_3 , another Rh^{4+} -based paramagnetic metal.³² The unusual properties of SrRhO_3 have been argued to emerge as the result of proximity to a quantum critical point.³³

The heat capacity of $\text{Lu}_2\text{Rh}_2\text{O}_7$ is presented in Fig. 3, where no phase transitions are observed between 2 and 300 K. For

Fig. 2 The magnetic susceptibility of $\text{Lu}_2\text{Rh}_2\text{O}_7$, which was measured at $H=1\text{ T}$, is dominated by a largely temperature independent Pauli paramagnetic contribution. The full symbols and the left hand axis are the susceptibility, χ , while the open symbols and the right hand axis give the inverse susceptibility, χ^{-1} . The yellow dashed line is the as-measured susceptibility data, prior to the Curie tail subtraction. The red line is a fit to the Curie-Weiss equation. The inset shows magnetization measurements at $T=2$ and 25 K

Fig. 3 The heat capacity of $\text{Lu}_2\text{Rh}_2\text{O}_7$ measured in zero field, with the scaled heat capacity of $\text{Lu}_2\text{Ti}_2\text{O}_7$ from ref.³⁴ shown for reference. The inset shows a fit of $C/T = \gamma + \beta T^2$ over the shaded region, which yields a large Sommerfeld coefficient, $\gamma = 21.8(1)\text{ mJ/mol-Rh K}^2$

comparison, we plot alongside this data the scaled heat capacity of $\text{Lu}_2\text{Ti}_2\text{O}_7$, which is an insulating lattice analog with no unpaired d electrons.³⁴ The heat capacity of $\text{Lu}_2\text{Ti}_2\text{O}_7$ was scaled by $\mu = \sqrt{M_{\text{LRO}}/M_{\text{LTO}}}$ where M_{LRO} and M_{LTO} are the molecular weights of $\text{Lu}_2\text{Rh}_2\text{O}_7$ and $\text{Lu}_2\text{Ti}_2\text{O}_7$, respectively. These two data sets are largely consistent, confirming that the high-temperature heat capacity of $\text{Lu}_2\text{Rh}_2\text{O}_7$ can be accounted for by lattice degrees of freedom. The scaled heat capacity of $\text{Lu}_2\text{Ti}_2\text{O}_7$ is observed to slightly exceed that of $\text{Lu}_2\text{Rh}_2\text{O}_7$ below 50 K . This difference can be understood to originate from anharmonic effects, which are known to be significant in rare earth pyrochlores,³⁵ and will vary between compounds dependent on the details of the phonon interactions. Indeed, the heat capacity of $\text{Lu}_2\text{Ti}_2\text{O}_7$ is also observed to exceed that of $\text{Dy}_2\text{Ti}_2\text{O}_7$ in the same temperature interval.³⁴ At the lowest temperatures, Fermi liquid behavior is observed for $\text{Lu}_2\text{Rh}_2\text{O}_7$, where C/T is linear with respect to T^2 up to $T=10\text{ K}$ (inset of Fig. 3). The fitted value for the Sommerfeld coefficient is $\gamma = 21.8(1)\text{ mJ/mol-Rh K}^2$, which is large and comparable to values observed in other strongly correlated rhodates and ruthenates.^{36–38}

Enhanced electron masses are most commonly associated with heavy fermion physics in f -electron metals.³⁹ However, there are several notable examples of d -electron systems with anomalously large Sommerfeld coefficients, including $\text{Y}_{1-x}\text{Sc}_x\text{Mn}_2$ ⁴⁰ and LiV_2O_4 .⁴¹ In both $\text{Y}_{1-x}\text{Sc}_x\text{Mn}_2$ (a cubic Laves phase) and LiV_2O_4 (a spinel), the underlying magnetic sublattice is a pyrochlore-like network of corner-sharing tetrahedra. It has been proposed that geometric frustration plays a central role in their electronic properties. Frustration tends to suppress conventional magnetic order, giving rise to strong spin fluctuations, while the itinerant nature of the electrons results in large spin disorder entropy at low temperatures, which gives rise to an enhanced linear contribution to the specific heat.⁴² Indeed, the values for γ in $\text{Y}_{1-x}\text{Sc}_x\text{Mn}_2$ (140 mJ/mol K^2 for $x=0.03$ ⁴³) and LiV_2O_4 (420 mJ/mol K^2 ⁴⁴) are comparable to some of the best known examples of f -electron heavy fermion systems, such as URu_2Si_2 (180 mJ/mol K^2 ⁴⁵) and UPt_3 (420 mJ/mol K^2 ⁴⁶). Given that the magnetic sublattice of $\text{Lu}_2\text{Rh}_2\text{O}_7$ shares this frustrated architecture, similar mechanisms may be responsible for its enhanced Sommerfeld coefficient.

We have also performed zero field μSR measurements on $\text{Lu}_2\text{Rh}_2\text{O}_7$. While the bulk probes employed thus far all indicate the absence of magnetic order, muons as a local probe are highly sensitive to very small ordered moments, even those below $0.1 \mu_B$. Muon decay asymmetry spectra were collected between 2 and 250 K , and several representative data sets are presented in Fig. 4a. The relaxation, which is weak at all measured temperatures, is observed to gradually increase with decreasing temperature. We do not observe any sharp increase in relaxation or spontaneous oscillations, as would be expected in the case of long-range magnetic order. As a function of temperature, the relaxation evolves from more Gaussian-like at high temperatures to Lorentzian at the lowest temperatures. Thus, we fitted the asymmetry spectra to a stretched exponential function

$$A(t) = A_0 \cdot \exp(-\lambda t)^\beta + A_{BG} \quad (1)$$

where λ is the relaxation rate and the stretching parameter was constrained to lie between $\beta=1$ (Lorentzian) and $\beta=2$ (Gaussian). The non-relaxing background asymmetry, A_{BG} , accounts for muons which land outside the sample. The total asymmetry was constrained by fitting the precessing signal at high temperature in a weak field applied transverse to the muon's spin. The temperature dependence of both λ and β are presented in Fig. 4b. The relaxation rate gradually grows below 200 K , reaching a maximum value of $0.15\text{ }\mu\text{s}^{-1}$ at 2 K . There is a concomitant decrease of the stretching parameter, which plateaus at $\beta=1$ below 20 K . This can be understood in terms of a crossover, where at high temperatures more Gaussian relaxation is observed due to

Fig. 4 **a** Several representative asymmetry spectra from muon spin relaxation measurements on $\text{Lu}_2\text{Rh}_2\text{O}_7$. Error bars are derived from $\sqrt{N}$ counting statistics. The solid lines are fits to a stretched exponential function. **b** The temperature dependence of the fitted relaxation rate, λ , and the stretching parameter, β , reveal weak spin dynamics and a crossover from more Gaussian-like relaxation to Lorentzian relaxation

Fig. 5 The electrical resistivity of $\text{Lu}_2\text{Rh}_2\text{O}_7$ is typical of a semiconductor in magnitude but with an abnormal temperature dependence. The inset shows $\ln(\rho)$ vs. T^{-1} , where the red line indicates a fit to thermally activated Arrhenius behavior yielding a gap of $\Delta = 37(1)$ meV

fluctuating nuclear dipoles whereas at lower temperatures the signal is dominated by slowing spin dynamics. The decrease in β may share an origin with the broad hump in the susceptibility in the same temperature interval. Moreover, these μSR measurements confirm that $\text{Lu}_2\text{Rh}_2\text{O}_7$ remains paramagnetic, with no evidence for magnetic order or spin freezing down to 2 K.

Electrical resistivity measurements were carried out using a conventional four-terminal method on a cold-pressed pellet⁴⁶ of $\text{Lu}_2\text{Rh}_2\text{O}_7$, which was annealed in air at 600 °C for 10 h to minimize grain boundary effects. X-ray diffraction measurements were performed before and after the annealing protocol to confirm that it did not result in any degradation of the sample. In striking contrast to the magnetic susceptibility and heat capacity, which would both suggest a metallic state, the room temperature resistivity is 0.36 Ω-cm, which is typical of a semiconducting state. Furthermore, the temperature dependence of the resistivity monotonically increases with decreasing temperature (i.e., $dp/dT < 0$). The resistivity is observed to diverge below 10 K. The inset of Fig. 5 shows that this resistivity does not obey a thermally activated Arrhenius behavior for a very large range of temperatures. The data can be fit between 200 and 300 K to $\rho \propto \rho_a \cdot \exp$

$(-\Delta/2k_B T)$, yielding a very small gap of $\Delta = 37(1)$ meV. There are several factors worth considering in the quantitative interpretation of this data. First is that this sample is a pressed pellet and thus, scattering from grain boundaries may be expected to uniformly increase the resistivity. However, the cold-pressing and annealing protocol followed here has been demonstrated to provide nearly intrinsic transport measurements in other transition metal oxides, including samples that are far softer and more porous than the one measured here.⁴⁶ Moreover, even without the cold-pressing technique, conventional metallic resistivity (i.e., $dp/dT > 0$) has been measured in numerous polycrystalline samples of rhodates synthesized via the same high-pressure techniques used here.^{32,47–50} It is also worth mentioning that our minor impurity phase, RhO_2 , is known to be a metal.³⁰ Thus, the nonmetallic resistivity is clearly intrinsic to $\text{Lu}_2\text{Rh}_2\text{O}_7$, a remarkable result in a material that all other probes suggest is metallic.

DISCUSSION

Our characterizations have revealed that $\text{Lu}_2\text{Rh}_2\text{O}_7$ possesses a highly unusual non-Fermi liquid state. While both heat capacity and magnetic susceptibility indicate a finite density of states at the Fermi energy, the temperature dependence of the resistivity appears more consistent with a semiconducting gap. Moreover, even for a semiconductor, the temperature dependence of the resistivity is unconventional. It is instructive to consider a comparison with the “nonmetallic metal” FeCrAs . First, an important structural commonality is that in both materials, the magnetic constituent(s) are connected in triangular motifs that can be prone to geometric magnetic frustration. In the case of $\text{Lu}_2\text{Rh}_2\text{O}_7$ this is the corner-sharing tetrahedral pyrochlore sublattice and in the case of FeCrAs the non-magnetic Fe atoms occupy a triangular network of trimers while the magnetic Cr atoms form a distorted Kagome network. In regards to their electronic properties, the magnetic susceptibility of both materials is dominated by a largely temperature independent Pauli paramagnetic contribution.²⁷ Secondly, both materials have a Sommerfeld coefficient, as determined by heat capacity measurements, significantly larger than typically expected for a d electron system, $\gamma = 21.8(1)$ mJ/mol-Rh K² and 31.6 mJ/mol K² for $\text{Lu}_2\text{Rh}_2\text{O}_7$ and FeCrAs , respectively. However, the Wilson ratio ($R_W = 4\pi^2 k_B^2 \chi_P / 3(g\mu_B)^2 \gamma$) for FeCrAs , $R_W = 4–5$ ²⁷ is larger than our computed value of $R_W = 2.5$ for $\text{Lu}_2\text{Rh}_2\text{O}_7$. A third commonality is the temperature dependence of the resistivity, where dp/dT

is negative, nominally indicative of a gap in the density of states. However, the room temperature resistivity for FeCrAs is approximately $0.4 \text{ m}\Omega\text{-cm}$, approximately three orders of magnitude smaller than our value of $0.4 \text{ }\Omega\text{-cm}$. Another significant difference between these two materials is that the Cr moments in FeCrAs undergo a long-range antiferromagnetic ordering transition at $T_N = 125 \text{ K}$,²⁷ while no magnetic order is observed in $\text{Lu}_2\text{Rh}_2\text{O}_7$ down to at least 2 K .

Several compelling explanations have been put forward to explain the nonmetallic metallic state in FeCrAs, which are worth examining in the current context of our results on $\text{Lu}_2\text{Rh}_2\text{O}_7$. The first proposal, which comes from Rau and Kee, suggests a hidden spin liquid state for the non-magnetic Fe trimers.⁵¹ They propose that the electrons residing on these trimers are close to a metal-insulator quantum critical point, such that charge fluctuations strongly renormalize the transport behavior while only minimally affecting the thermodynamic properties. A second proposal that does not rely on proximity to a Mott insulating state, but instead attributes the unusual qualities of FeCrAs to it being a Hund's metal.⁵² In a Hund's metal, non-Fermi liquid properties emerge due to strong intra-atomic exchange in a multiorbital material, such as ruthenates and iron pnictides.⁵³ The result of strong Hund's coupling in these materials is that a subset of the d orbitals are pushed towards the local limit while maintaining strong coupling to other itinerant electrons. Several arguments make this second scenario less favorable in the case of $\text{Lu}_2\text{Rh}_2\text{O}_7$. First, Hund's coupling generally plays a weaker role in $4d^5 \text{ Rh}^{4+}$.⁵³ Secondly, this model is expected to give a large Wilson ratio,²⁸ as indeed observed in FeCrAs where $R_W = 4\text{--}5$,²⁷ whereas in $\text{Lu}_2\text{Rh}_2\text{O}_7$, $R_W = 2.5$. Recent inelastic neutron scattering experiments have revealed high energy itinerant-like spin excitations, which Plumb et al. propose may account for the nonmetallic resistivity.⁵⁴ Further study of the spin dynamics in $\text{Lu}_2\text{Rh}_2\text{O}_7$ are called for, a task which would be greatly benefited by the availability of large single crystal samples. While no single crystals of rhodate pyrochlores have been reported to date, a route similar to that used for Sr_2RhO_4 may prove fruitful.³⁸

Using high-pressure methods, we have synthesized a new pyrochlore $\text{Lu}_2\text{Rh}_2\text{O}_7$, in which $j_{\text{eff}} = 1/2 \text{ Rh}^{4+}$ occupies a frustrated corner-sharing tetrahedral lattice. No magnetic order is observed down to 2 K in μSR measurements. Heat capacity and magnetic susceptibility measurements both indicate strong electron correlations, with a large temperature independent Pauli paramagnetic response and an enhanced Sommerfeld coefficient, $\gamma = 21.8(1) \text{ mJ/mol-Rh K}^2$. Resistivity measurements, in contrast, suggest nonmetallic behavior ($dp/dT < 0$) in the full measured temperature range, $2\text{--}300 \text{ K}$. Thus, $\text{Lu}_2\text{Rh}_2\text{O}_7$ has a non-Fermi liquid state, sharing many commonalities with the nonmetallic metal FeCrAs.

METHODS

High-pressure synthetic techniques are often required to stabilize Rh^{4+} compounds,^{19,20,29,30,32,47,48} as Rh^{3+} is the more common oxidation state. The cubic pyrochlore $\text{Lu}_2\text{Rh}_2\text{O}_7$ was prepared using a belt-type high-pressure apparatus at the National Institute for Materials Science in Tsukuba, Japan. Lu_2O_3 was thoroughly dried prior to the reaction. Rhodium metal was first oxidized to Rh_2O_3 by reacting under flowing oxygen at 1000°C for 72 h . The reaction into the pyrochlore phase was completed using KClO_4 as an oxidizing agent to promote the Rh^{4+} oxidation state. The precursors (Lu_2O_3 , Rh_2O_3 , KClO_4 in a $1:1:3/8$ ratio) were thoroughly ground together and sealed in a platinum capsule. The reaction was completed at 1700°C and 6 GPa of applied pressure for 2 h , after which the sample was quenched to room temperature before the pressure was released. The final product was repeatedly washed with water to remove KCl and then dried. The resulting 0.5 g sample is made up of sub-micron sized black crystallites. Once prepared, this material is stable in air on a timescale of years.

X-ray diffraction measurements were performed using a PANalytical diffractometer with copper $\text{K}\alpha_1$ radiation, $\lambda = 1.540560 \text{ \AA}$. Rietveld

refinement was performed using FullProf.⁵⁵ Magnetic susceptibility, resistivity, and heat capacity measurements between 2 and 300 K were completed using a Quantum Design Physical Property Measurement System. Zero field μSR measurements were performed at the M20 surface muon channel at TRIUMF in the LAMPF Spectrometer. The μSR data were fitted over the full measured time interval, up to $9.5 \text{ }\mu\text{s}$, using the muSRfit software package.

DATA AVAILABILITY

The crystal structure of $\text{Lu}_2\text{Rh}_2\text{O}_7$, as determined by Rietveld refinement of the powder x-ray diffraction data, is available at the Cambridge Crystallographic Data Centre with deposition number CSD 1895045. All other data is available from the authors on reasonable request.

ACKNOWLEDGEMENTS

The authors gratefully acknowledge useful conversations with Yipeng Cai, Jonathan Gaudet, John Greedan, Chien-Lung Huang, and Murray Wilson. The authors thank Bassam Hitti and Gerald Morris from TRIUMF for their support with the μSR experiment. A.M.H. thanks the National Institute for Materials Science (NIMS) for their hospitality and support through the NIMS Internship Program. This work was supported by the Natural Sciences and Engineering Research Council of Canada (NSERC) and Canada Foundation for Innovation. C.R.W. is additionally supported by the Canada Research Chair (Tier II) program and the Canadian Institute for Advanced Research. Q.C. and H.D.Z. are supported by the National Science Foundation (NSF-DMR-1350002).

AUTHOR CONTRIBUTIONS

The high-pressure synthesis and x-ray diffraction were performed by A.M.H. and M.T. Magnetic susceptibility and electric resistivity measurements, and their analysis, were performed by Q.C., H.D.Z., C.M., P.M.S., J.P.A., A.M.H., and C.R.W. Heat capacity measurements were performed by A.Z.S. and C.R.W. μSR measurements were performed and analyzed by A.M.H. and G.M.L. with assistance from C.D. and Z.G. The manuscript was written by A.M.H. and C.R.W. with input from all authors.

ADDITIONAL INFORMATION

Competing interests: The authors declare no competing interests.

Publisher's note: Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.

REFERENCES

- Lee, P. A., Nagaosa, N. & Wen, X.-G. Doping a Mott insulator: physics of high-temperature superconductivity. *Rev. Mod. Phys.* **78**, 17–85 (2006).
- Witczak-Krempa, W., Chen, G., Kim, Y. B. & Balents, L. Correlated quantum phenomena in the strong spin-orbit regime. *Annu. Rev. Condens. Matter Phys.* **5**, 57–82 (2014).
- Gardner, J. S., Gingras, M. J. P. & Greedan, J. E. Magnetic pyrochlore oxides. *Rev. Mod. Phys.* **82**, 53–107 (2010).
- Nakatsuji, S. et al. Metallic spin-liquid behavior of the geometrically frustrated kondo lattice $\text{Pr}_2\text{Ir}_2\text{O}_7$. *Phys. Rev. Lett.* **96**, 087204 (2006).
- Lacroix, C. Frustrated metallic systems: a review of some peculiar behavior. *J. Phys. Soc. Jpn.* **79**, 011008 (2010).
- Julian, S. & Kee, H. Y. Frustrated metallic magnets. *Phys. Can.* **68**, 95–98 (2012).
- Paddison, J. A. M. et al. Emergent frustration in co-doped $\beta\text{-Mn}$. *Phys. Rev. Lett.* **110**, 267207 (2013).
- Billington, D. et al. Magnetic frustration, short-range correlations and the role of the paramagnetic fermi surface of PdCrO_2 . *Sci. Rep.* **5**, 12428 (2015).
- Sapkota, A. et al. Effective one-dimensional coupling in the highly frustrated square-lattice itinerant magnet $\text{CaCo}_{1-x}\text{As}_2$. *Phys. Rev. Lett.* **119**, 147201 (2017).
- Ramirez, A. P. Strongly geometrically frustrated magnets. *Annu. Rev. Mater. Sci.* **24**, 453–480 (1994).
- Subramanian, M. A., Aravamudan, G. & Subba Rao, G. V. Oxide pyrochlores: a review. *Prog. Solid State Chem.* **15**, 55–143 (1983).
- Wan, X., Turner, A. M., Vishwanath, A. & Savrasov, S. Y. Topological semimetal and Fermi-arc surface states in the electronic structure of pyrochlore iridates. *Phys. Rev. B* **83**, 205101 (2011).
- Blacklock, K. & White, H. W. Specific heats of the pyrochlore compounds $\text{Cd}_2\text{Re}_2\text{O}_7$ and $\text{Cd}_2\text{Ru}_2\text{O}_7$. *J. Chem. Phys.* **71**, 5287–5289 (1979).

14. Sakai, H. et al. Superconductivity in a pyrochlore oxide, $\text{Cd}_2\text{Re}_2\text{O}_7$. *J. Phys. Condens. Matter* **13**, L785–L790 (2001).
15. Sleight, A. W., Gillson, J. L., Weiher, J. F. & Bindloss, W. Semiconductor–metal transition in novel $\text{Cd}_2\text{Os}_2\text{O}_7$. *Solid State Commun.* **14**, 357–359 (1974).
16. Mandrus, D. et al. Continuous metal–insulator transition in the pyrochlore $\text{Cd}_2\text{Os}_2\text{O}_7$. *Phys. Rev. B* **63**, 195104 (2001).
17. Calder, S. et al. Spin–orbit-driven magnetic structure and excitation in the 5d pyrochlore $\text{Cd}_2\text{Os}_2\text{O}_7$. *Nat. Commun.* **7**, 11651 (2016).
18. Sohn, C. H. et al. Strong spin–phonon coupling mediated by single ion anisotropy in the all-in-all-out pyrochlore magnet $\text{Cd}_2\text{Os}_2\text{O}_7$. *Phys. Rev. Lett.* **118**, 117201 (2017).
19. Sleight, A. W. & Gillson, J. L. Platinum metal pyrochlores of the type $\text{Ti}_2\text{M}_2\text{O}_7$. *Mater. Res. Bull.* **6**, 781–784 (1971).
20. Lazarev, V. B. & Shaplygin, I. S. Electrical properties of mixed oxides containing a platinum metal and a non-noble metal. *Russ. J. Inorg. Chem.* **23**, 163–170 (1978).
21. Martins, C., Aichhorn, M. & Biermann, S. Coulomb correlations in 4d and 5d oxides from first principles or how spin–orbit materials choose their effective orbital degeneracies. *J. Phys. Condens. Matter* **29**, 263001 (2017).
22. Uematsu, D. et al. Large trigonal-field effect on spin–orbit coupled states in a pyrochlore iridate. *Phys. Rev. B* **92**, 094405 (2015).
23. Rau, J. G., Lee, E. K. H. & Kee, H.-Y. Spin–orbit physics giving rise to novel phases in correlated systems: iridates and related materials. *Annu. Rev. Condens. Matter Phys.* **7**, 195–221 (2016).
24. Birol, T. & Haule, K. $J_{\text{eff}} = 1/2$ Mott-insulating state in Rh and Ir fluorides. *Phys. Rev. Lett.* **114**, 096403 (2015).
25. Martins, C., Aichhorn, M., Vaugier, L. & Biermann, S. Reduced effective spin-orbital degeneracy and spin-orbital ordering in paramagnetic transition-metal oxides: Sr_2IrO_4 versus Sr_2RhO_4 . *Phys. Rev. Lett.* **107**, 266404 (2011).
26. Luo, Y. et al. Li_2RhO_3 : a spin-glassy relativistic Mott insulator. *Phys. Rev. B* **87**, 161121 (2013).
27. Wu, W., McCollam, A., Swainson, I., Rancourt, D. G. & Julian, S. R. A novel non-Fermi-liquid state in the iron-pnictide FeCrAs . *Europhys. Lett.* **85**, 17009 (2009).
28. Akrap, A., Dai, Y. M., Wu, W., Julian, S. R. & Homes, C. C. Optical properties and electronic structure of the nonmetallic metal FeCrAs . *Phys. Rev. B* **89**, 125115 (2014).
29. Muller, O. & Roy, R. Formation and stability of the platinum and rhodium oxides at high oxygen pressures and the structures of Pt_3O_4 , $\beta\text{-PtO}_2$ and RhO_2 . *J. Less Common Met.* **16**, 129–146 (1968).
30. Shannon, R. D. Synthesis and properties of two new members of the rutile family RhO_2 and PtO_2 . *Solid State Commun.* **6**, 139–143 (1968).
31. Bain, G. A. & Berry, J. F. Diamagnetic corrections and Pascal's constants. *J. Chem. Educ.* **85**, 532–536 (2008).
32. Yamaura, K. & Takayama-Muromachi, E. Enhanced paramagnetism of the 4d itinerant electrons in the rhodium oxide perovskite SrRhO_3 . *Phys. Rev. B* **64**, 224424 (2001).
33. Singh, D. J. Prospects for quantum criticality in perovskite SrRhO_3 . *Phys. Rev. B* **67**, 054507 (2003).
34. Saha, S. et al. Temperature-dependent Raman and x-ray studies of the spin-ice pyrochlore $\text{Dy}_2\text{Ti}_2\text{O}_7$ and nonmagnetic pyrochlore $\text{Lu}_2\text{Ti}_2\text{O}_7$. *Phys. Rev. B* **78**, 214102 (2008).
35. Maczka, M. et al. Temperature-dependent Raman scattering studies of the geometrically frustrated pyrochlores $\text{Dy}_2\text{Ti}_2\text{O}_7$, $\text{Gd}_2\text{Ti}_2\text{O}_7$ and $\text{Er}_2\text{Ti}_2\text{O}_7$. *J. Raman Spectrosc.* **39**, 537–544 (2008).
36. Maeno, Y. et al. Two-dimensional Fermi liquid behavior of the superconductor Sr_2RuO_4 . *J. Phys. Soc. Jpn.* **66**, 1405–1408 (1997).
37. Park, J. et al. Robust singlet dimers with fragile ordering in two-dimensional honeycomb lattice of Li_2RuO_3 . *Sci. Rep.* **6**, 25238 (2016).
38. Perry, R. S. et al. Sr_2RhO_4 : a new, clean correlated electron metal. *New J. Phys.* **8**, 175 (2006).
39. Stewart, G. R. Heavy-fermion systems. *Rev. Mod. Phys.* **56**, 755–787 (1984).
40. Shiga, M., Fujisawa, K. & Wada, H. Spin liquid behavior of highly frustrated $\text{Y}(\text{Sc})\text{Mn}_2$ and effects of nonmagnetic impurity. *J. Phys. Soc. Jpn.* **62**, 1329–1336 (1993).
41. Kondo, S. et al. LiV_2O_4 : a heavy fermion transition metal oxide. *Phys. Rev. Lett.* **78**, 372–373 (1997).
42. Lacroix, C. Heavy-fermion behavior of itinerant frustrated systems: $\beta\text{-Mn}$, $\text{Y}(\text{Sc})\text{Mn}_2$, and LiV_2O_4 . *Can. J. Phys.* **79**, 1469–1473 (2001).
43. Wada, H. et al. Spin fluctuations of $\text{Y}(\text{Mn}_{1-x}\text{Al}_x)_2$ and $\text{Y}_{1-x}\text{Sc}_x\text{Mn}_2$. *J. Magn. Magn. Mater.* **70**, 17–19 (1987).
44. Palstra, T. T. M. et al. Superconducting and magnetic transitions in the heavy-fermion system URu_2Si_2 . *Phys. Rev. Lett.* **55**, 2727–2730 (1985).
45. Frings, P. H., Franse, J. J. M., De Boer, F. R. & Menovsky, A. Magnetic properties of U_xPt_y compounds. *J. Magn. Magn. Mater.* **31**, 240–242 (1983).
46. Zhou, J.-S., Goodenough, J. B. & Dabrowski, B. Transition from Curie–Weiss to enhanced Pauli paramagnetism in RNiO_3 ($R = \text{La, Pr, Gd}$). *Phys. Rev. B* **67**, 020404 (2003).
47. Yamaura, K., Huang, Q., Young, D. P., Noguchi, Y. & Takayama-Muromachi, E. Crystal structure and electronic and magnetic properties of the bilayered rhodium oxide $\text{Sr}_3\text{Rh}_2\text{O}_7$. *Phys. Rev. B* **66**, 134431 (2002).
48. Yamaura, K., Huang, Q., Young, D. P. & Takayama-Muromachi, E. Crystal structure and magnetic properties of the trilayered perovskite $\text{Sr}_4\text{Rh}_3\text{O}_{10}$: a new member of the strontium rhodate family. *Chem. Mater.* **16**, 3424–3430 (2004).
49. Yamaura, K. et al. High-pressure synthesis, crystal structure determination, and a Ca substitution study of the metallic rhodium oxide NaRh_2O_4 . *Chem. Mater.* **17**, 359–365 (2005).
50. Yamaura, K. & Takayama-Muromachi, E. High-pressure synthesis of the perovskite rhodate CaRhO_3 . *Phys. C* **445**, 54–56 (2006).
51. Rau, J. G. & Kee, H.-Y. Hidden spin liquid in an antiferromagnet: applications to FeCrAs . *Phys. Rev. B* **84**, 104448 (2011).
52. Nevidomskyy, A. H. & Coleman, P. Kondo resonance narrowing in d - and f -electron systems. *Phys. Rev. Lett.* **103**, 147205 (2009).
53. Georges, A., de Medici, L. & Mravlje, J. Strong correlations from Hunds coupling. *Annu. Rev. Condens. Matter Phys.* **4**, 137–178 (2013).
54. Plumb, K. W. et al. From mean-field localized magnetism to itinerant spin fluctuations in the nonmetallic metal FeCrAs . *Phys. Rev. B* **97**, 184431 (2018).
55. Rodriguez-Carvajal, J. Recent advances in magnetic structure determination by neutron powder diffraction. *Phys. B Condens. Matter* **192**, 55–69 (1993).

Open Access This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons license, and indicate if changes were made. The images or other third party material in this article are included in the article's Creative Commons license, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons license and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder. To view a copy of this license, visit <http://creativecommons.org/licenses/by/4.0/>.

© The Author(s) 2019