OPEN

Liquid state properties and solidification features of the pseudo binary BaS-La₂S₃

Charles Boury & Antoine Allanore

The high temperature thermodynamic properties of chalcogenides materials based on BaS remain elusive. Herein the pseudo binary BaS-La₂S₃ is investigated above 1573 K. The liquid properties of BaS-La₂S₃ are measured by means of high resolution in-situ visualization coupled with thermal arrest measurements in a thermal imaging furnace. This enables to report the first observation of such melts in a container-less setting. The melting points of BaS and La₂S₃ are revisited at 2454 K and 2004 K respectively. La₂S₃ demonstrates a high stability in its liquid state, in strike difference with the sublimation observed for BaS. BaS is however partially stabilized with the addition of few percents of La₂S₃. The remarkable chemical and thermal stability of La₂S₃-rich samples contrasts with the partial decomposition and high vapor pressure observed for BaS-rich samples. Observations and analysis of the solidified samples suggest three different solid solutions. Solid and liquid densities are investigated along the different compositions, supporting a first estimate of the volumetric thermal expansion coefficient for La₂S₃.

Sulfides are common compounds on earth and govern society access to a myriad of metals such as copper, nickel, cobalt or even precious metals. As inorganic chemical materials, metal sulfides however have found relatively limited breadth of applications, in part due to their chemical reactivities and the difficulties in their processing. This is in strike difference with the range of properties that they can exhibit, as illustrated by their band-gap which ranges from 1.65 to 3.75 eV¹. The high temperature behavior of sulfides, in particular those with promising optical properties, remains a frontier that needs to be explored in the context of materials processing. Often, binary or ternary compounds based on mixtures of sulfides are looked for, offering a tunable but unique set of properties. Unfortunately, the most basic high temperature information such as melting point, evaporation rate or range of miscibility are scarce, hindering the development of manufacturing processes.

Barium (+ 2) sulfide (BaS) has been previously investigated for its possible applications in optics, from the stabilization of host glasses² to the generation of luminescent materials when combined with Indium or Gallium sulfides In₂S₃, Ga₂S₃³. The position of Ba in the periodic table makes BaS the most ionic alkaline rare earth sulfide with a band gap of 2.1 eV⁴ suggesting application in iono-conduction⁵. The standard melting point of BaS has been reported several times at 2508, 2480, 2475, 2470 and 2430 K (respectively^{6–10}). Livey *et al.*⁹ mentioned an important volatility for BaS at high temperature impeding the obtention of a stable thermal trace or a good optical visualization. BaS is characterized by a face centered cubic structure (FCC, e.g. NaCl). In contrast with La₂S₃, the crystal structure of BaS seems invariant with temperature until its vaporization. The high sensitivity of BaS to air and moisture contamination leads to difficulties in the precise measurements of basic properties such as its melting point as *pure* BaS. In 1968, Bonnivard described the instability of BaS in ambient air¹¹. As a white salt when pure, it easily oxidizes at ambient temperature and dissolves in water to a maximum of 500 g per liter. A shift of its color toward yellow is indicative of its oxidation. The overall oxidation products of BaS in ambient air remain uncertain, considering the multiple oxidized compounds possible such as oxysulfides, sulfates, oxides, carbonates....

Stinn *et al.*⁶ investigated the pseudo binary of BaS combined with dicopper (+2) sulfide (Cu₂S) using a combination of differential thermal analysis and in-situ thermal imaging furnace. This study indicates a large depression of the melting point of BaS by the addition of as little as 5 mol% Cu₂S. A broad liquid miscibility gap is found, the two-liquids being optically distinct: the BaS-rich liquid exhibits optical features of an ionic melt while the Cu₂S-rich melt displays optical features closer to Cu₂S. The results demonstrate the ability to stabilize a melt with up to 95 mol% BaS, which supported a new electrochemical processing technique using BaS-based sulfides electrolytes with un-precedent solubility and electrical conductivity. Cu₂S is a solid and liquid semiconductor,

Department of Materials Science and Engineering, Massachusetts Institute of Technology, Cambridge, MA, USA.
✉ email: allanore@mit.edu

while BaS is an insulating, ionic compound. It is therefore of interest to evaluate if the electronic nature of the second compound added to BaS affects the melting behavior. This requires to investigate a pseudo-binary system with an ionic second compound, and lanthanum (+3) sesquisulfide (La_2S_3) is a good candidate.

Unfortunately, knowledge about La_2S_3 is also scarce. Flahaut *et al.* discovered the remarkable homogeneity of rare-earth ceric sulfides (ceric elements: La, Ce, Pr, Nd, Pm, Sm, Eu)^{12–17} demonstrating commonalities in crystal structures, melting points and oxidation. Andreev *et al.* experimentally explored the pseudo-binary phase diagrams of metallic (+2) sulfides - rare earth (+3) sulfides, describing similarities and differences in properties^{18–25}.

For La_2S_3 and other ceric (+3) sesquisulfides, different solid phases, α , β , γ , have been reported²⁶. α - La_2S_3 , with an orthorhombic structure, is stable until 1173 K. β - La_2S_3 has a stability domain from 1173 K to 1573 K and exhibits a tetragonal structure, similar to the oxysulfide $\text{La}_{10}\text{S}_{14+x}\text{O}_{1-x}$. The high-temperature stable phase, γ - La_2S_3 has a cubic Th_3P_4 -type structure, with composition $\text{La}_{3-x}\text{V}_x\text{S}_4$ ($0 \leq x \leq 1/3$, ranging between La_3S_4 and La_2S_3), where V represents La vacancies. The β and γ phases are unstable at room temperature, however γ - La_2S_3 can be stabilized by introducing alkali ions²⁷ or europium²⁸. Furthermore Kumta *et al.* found a process to generate and stabilize fine β - La_2S_3 and γ - La_2S_3 powder at high temperature²⁹. Two other phases δ (monoclinic) and ϵ (rhombohedral) exist for some sesquisulfides but have not been reported for La_2S_3 ¹. Prior studies of La_2S_3 intended to determine its chemical stability with respect to oxygen and sulfur as a function of temperature. In 1981, Kamarzin *et al.* studied lanthanum (+3) sesquisulfides from LaS to La_2S_3 ³⁰. In 1984, Kay *et al.* proposed a phase stability diagram for lanthanum versus the vapor pressure of O_2 and S_2 at 1100 K³¹. Vasilyeva described the thermodynamic of the La_2S_3 - LaS_2 system in 2010³².

The melting point of La_2S_3 has been investigated several times^{10,15,30,33,34}, reported between 2133 and 2350 K. The potential reactivity with crucibles might have affected the accuracy of the results. In addition, the vaporization of La_2S_3 before its melting has been reported at around 2000 K. Flahaut and Picon investigated the lanthanum oxide (La_2O_3) and oxysulfides ($\text{La}_2\text{O}_2\text{S}$) and concluded their formation from sulfide was kinetically slow^{35,36}. Sulfates $\text{La}_2(\text{SO}_4)_3$ and oxysulfates $(\text{LaO})_2\text{SO}_4$ require specific conditions to be formed from sulfides, unattained herein^{37,38}.

La_2S_3 has found applications in certain glasses, β - La_2S_3 potentially exhibits properties of phosphorous material³⁹. La_2S_3 also found usage as an electrode in its α phase for its pseudo-capacitive behavior when immersed into a Na_2SO_4 electrolyte^{40,41}. From the common crystal structure between La_2S_3 and La_3S_4 at low temperature (α phase), superconducting properties has been observed with a Curie point varying with the metal vacancy concentration⁴². The transformation of La_2S_3 to La_3S_4 leads to drastic changes in the sulfide electrical properties; Wood *et al.* reported an insulator behavior of La_2S_3 , compared to La_3S_4 which acts as a semi-metal⁴³.

The combination BaS- La_2S_3 , despite very limited prior art, supported the extension of molten sulfides electrolyte based on BaS, in particular for copper electrowinning from Cu_2S ⁴⁴. BaS- La_2S_3 was postulated to bring two essential properties for the electrolysis of Cu_2S into $\text{Cu}_{(l)}$ and $\text{S}_{2(g)}$: the wide band-gap of BaS allows ionic conduction and the addition of La_2S_3 decreases the melting point of the electrolyte.

Herein, the liquid state properties and solid phases found upon solidification of the pseudo binary BaS- La_2S_3 are investigated. The use of a container-less thermal imaging furnace allows to observe unique features such as molten state stability, melt density and evaporation processes. The liquidus line and melting points of BaS and La_2S_3 are reported and compared to the literature. Mass loss, porosity and liquid state behavior are investigated to highlight the differences between BaS-rich samples and La_2S_3 -rich samples. Following solidification, different solid solutions are observed and compared to the literature, allowing to propose a preliminary version of the pseudo binary BaS- La_2S_3 phase diagram. Some hypothesis regarding the oxidation processes of alkaline sulfides (BaS) and rare-earth sulfides (La_2S_3) are proposed to compare the analyzed phases with the literature. Preliminary results for densities of molten and solidified samples are reported. In closing, an attempt to determine the volumetric isobaric thermal expansion coefficient of La_2S_3 is presented.

Experimental and analysis

Samples preparation. The melting behavior is investigated along the pseudo-binary system $(\text{BaS})_x(\text{La}_2\text{S}_3)_{1-x}$, with increments x of 10 mol%. The isothermal melt stability over long durations is studied for several temperatures for two specific compositions: $(\text{BaS})_{0.25}(\text{La}_2\text{S}_3)_{0.75}$ and $(\text{BaS})_{0.75}(\text{La}_2\text{S}_3)_{0.25}$. Four samples of both compositions are set at different temperatures (2133, 2023, 1896, 1889 K and 2233, 2160, 2129, 2093 K respectively) to investigate the melt long term stability.

BaS and La_2S_3 powders come from Alfa Aesar with a respective purity of 99.97 % and 99.99 % (metal basis). Each sample is prepared in a glove box with atmosphere control using argon, indicating a maximum oxygen content of 10 ppm. Each powder is weighed, mixed and milled into a mortar and pestle. The homogeneous mix is poured into a cleaned rubber balloon. The balloon is stretched and compressed to obtain a rod-like shape of homogeneous density and diameter, then a knot is tight at both ends. With both ends attached to a stainless steel support to maintain a rod-like shape, the balloon is placed into an hydrostatic press and compressed to 30000 psi (2068 bar). After compression, the rod is removed with care by cutting along the rubber balloon with a stainless-steel scalpel in a fume hood. The rod is maintained at the end of a moveable and rotating central shaft of a thermal imaging furnace by means of a tungsten or molybdenum wire. The time required to assemble the rod and set it up in the furnace involves contact with ambient atmosphere for around 1 hour. The compacted rods are slightly friable prior to melting, influencing to a certain extend the repeatability of mass loss measurements.

Thermal imaging furnace. Both BaS and La_2S_3 are compounds with melting temperature above 1900 K, requiring special attention with respect to materials compatibility, few refractory materials being compatible. Instead herein a container-less configuration is used in a thermal imaging furnace (Crystal Systems Corp., model TX-12000-I-MIT-PC). It is equipped with four Xenon lamps of 3 kW of power each. The lamps irradiate

Figure 1. Picture of a liquid La_2S_3 droplet pending from its solid formed in the Thermal Imaging Furnace. (Camera Canon Inc., EOS Rebel T5i DSLR, EF-S 18–135 mm).

Figure 2. Example of the thermal trace obtained from the thermocouple located into BaS sample. The two dotted lines are used to evaluate the melting point.

a center cone of light of around 1 cm^3 , in which the lower end of the sample is placed by moving the central shaft down. There, the sample is heated up by light/matter interaction. Temperatures greater than 3300 K have been obtained on a tungsten sample. A view of a liquid sample in place (La_2S_3) is shown in Fig. 1. Compared to traditional furnaces based on resistance heating, high temperatures can be reached «instantaneously» avoiding long heating processes and as evidenced from Fig. 1 observation and mechanical access to a droplet is relatively straightforward.

Visual access to the samples is possible between the lamps on the 4 sides of the thermal imaging furnace. A camera (Watec, WAT-233 1/3", Extender EX2C, Computar Co., Fujinon TF4XA-1) equipped with a UV filter is fixed to the front door and used to observe samples live. A second camera (Canon Inc., EOS Rebel T5i DSLR) equipped with a zoom lens (Canon Inc., EF-S 18–135 mm) is set up on a tripod orthogonal to the front door. Melting and solidification processes are observable, either in live mode or recorded. A feed-through at the bottom of the quartz tube allows to insert a type C thermocouple (W-Re 5%, W-Re 26%) for direct temperature measurement of the melt. The thermocouple signal is converted into temperature following the Reference Tables N.I.S.T. Monograph 175- Revised to ITS-90. The reference junction temperature is corrected by 17 K to consider the actual room temperature. The thermocouple signal limits of error is 1 % of the read value in the range 273 K to 2600 K. A frequency acquisition of 3 Hz is typically used, increased to 1000 Hz when monitoring rapid cooling. Simple thermometry⁴⁵ is used to study the liquidus temperature as illustrated in Fig. 2. Other methods were not found yet compatible with the thermal imaging furnace. For a given sample, the liquidus temperature is crossed several times from visual observation, and several traces are then used to provide an average value.

Method for (BaS)_x-La₂S₃. When the furnace is turned on at the minimum attainable power (0 % power), the Xenon lamps are already emitting light leading to a minimum temperature of around 1550 K to 1650 K for the samples investigated herein. This value is dependent on the specific sample materials, its geometry, and the furnace configuration. Herein, 1% of power increment leads to 30 to 40 K increase when the sample is solid. A first slow increase at around 1 % power min⁻¹ is used to reach the melting point and not overheat the sample. When interested in the solid-phases, the power is decreased gradually to 0 % power and samples solidify up to 400 K.s⁻¹ when the furnace is turned off. For the investigation of the liquidus, the ramp rates range from 0.2 to 4% min⁻¹. The melting point or liquidus temperature are measured by repeating heating and cooling processes across the phase transition until the thermal trace shows a reproducible profile.

For all samples, a gaseous volume is formed inside the liquid droplet during a first melting of a sample. This gaseous volume has several origins, from the initial porosity consequence of the rod processing, to the chemical generation of a sulfuric gaseous phase composed of elemental sulfur S and including traces of metallic elements. The sulfuric gas phase has a yellowish color and is mainly observed for BaS-rich samples. Primary vacuum is applied several times during each experiments to extract this gas phase and ensure a fully liquid composition of the droplet for liquid density measurements. In the case of BaS-rich samples, the formation of a neck is observed at the solid/liquid interface when the sample stay in its liquid state for more than half an hour. The formed neck can be re-melted by slightly lowering the sample into the hot zone, for example for liquid density measurements. The droplet is considered deprived of gaseous phase when no visible effect is observable during the application of primary vacuum.

Density measurements. Pictures from camera recordings along with pixel size determination are used to calculate the equivalent volume of liquid, based on the method detailed by Wu *et al.*⁴⁶. Four pictures per sample are analyzed to average the volume and minimize the possible departure from axi-symmetry. After the experiment, the solidified droplet is separated from the rest of the sample with a stainless-steel scalpel, and weighed. The distinction between the melted and non-melted part is clear on the La₂S₃-rich samples. The neck formation with the BaS-rich samples makes this distinction more tedious. The weighted mass of solidified droplet and the liquid volume from the pictures provide an estimate of the liquid density. Archimedes' law is used to evaluate the density of the solidified droplet (specific gravity kit from Mineralab, using air and ethanol).

Elemental analysis. This work does not have as primary objective the determination of the solid-state phases for the pseudo-binary phase diagram. However, important observations on the elemental composition of the solidified phases are reported. Droplet samples are cast in epoxy and grounded along to gravity with silicon carbide paper (Grit 4000) using ethanol as a lubricant. BaS and La₂S₃ samples were polished down to 1 micrometer. Elemental analysis for those samples is conducted with a scanning electron microscope equipped with Wavelength Dispersive Spectroscopy microprobes (WDS, JEOL JXA-8200 Super-probe). Other samples were observed and analyzed on a scanning electron microscope (SEM, JEOL JSM- 6610LV, JEOL Ltd.) equipped with a single Energy Dispersive Spectroscopy detector (EDS, Sirius SD detector, SGX Sensor-tech Ltd.). Several factors are important when considering elemental analysis of the solids phases as reported herein:

1. Solidified BaS-La₂S₃ samples have a low electronic conductivity and despite the use of conductive tapes, high definition images proved difficult to obtain at a greater than 20,000x.
2. Ba and La have characteristics X-rays close to each other (La: 4.465 keV, 4.650 keV and M: 0.972 keV, 0.833 keV respectively).

Oxidation. BaS-La₂S₃ samples are unstable in air, leading to potential oxidation after exposure to atmosphere, and some oxygen content was found with EDS or WDS. As found from the literature, oxygen contamination of lanthanum sulfides is mainly due to the formation of La₂O₃ or La₂O₂S while the oxidation of BaS mostly lead to BaO. Without known mixed Ba-La oxide or oxysulfides, the elemental ratio Ba / La is considered constant and independent of the oxidation state so that elemental analysis results are reported as the ratio ([Ba]/([Ba]+[La])). WDS, contrary to EDS, can provide quantitative elementary analysis of S and O, and oxidation is assumed to lead to a stoichiometric substitution of S by O. The elemental concentration of S + O is then equal to the concentration of S from the as-solidified sample recovered from the furnace.

A small quantity of powdery material from condensation on the quartz tubes is recovered and analyzed. Its difficult acquisition leads to high uncertainty in its composition. The presence or absence of metallic compound can however be discussed.

Results

Lanthanum (+3) sulfide and barium (+2) sulfide. Pure La₂S₃ generates a small volume of visible gas during the first heating process. A mass loss of 1.5 wt% is observed. S, and La in a minor extent are detected with EDS on the condensate recovered on the quartz tube. After this first melting, La₂S₃ demonstrates a stunning stability as a liquid phase, never reported before in the literature. Pure BaS generates a non-quantifiable volume of visible gas both as solid upon heating or as liquid. BaS decomposes before melting, producing barium and sulfur vapors that condensate on the quartz tube. No metallic barium is found inside the sample droplet, indicative of a vaporization of both Ba and S, in agreement with the composition of the condensates. As described in the literature, BaS_(l) cannot be stabilized under argon at atmospheric pressure.

Figure 3. Study of the variation of the shape of the droplets during an experiment at constant temperature. Pictures of $(\text{BaS})_{0.25}-(\text{La}_2\text{S}_3)_{0.75}$ droplet shape (a) at the beginning, (b) during, (c) at the end of the experiment; $(\text{BaS})_{0.75}-(\text{La}_2\text{S}_3)_{0.25}$ droplet shape (d) at the beginning, (e) during, (f) at the end of the experiment. (Camera Wattec equipped with a UV filter).

La_2S_3 -rich samples. La_2S_3 -rich samples exhibit thermal features that lead to prompt homogenization of the temperature inside the droplet. Analogous melting behavior is found for 50 to 90 mol% La_2S_3 , and results for $(\text{BaS})_{0.25}-(\text{La}_2\text{S}_3)_{0.75}$ are specifically presented. Views of the droplet at 3 stages during a 45 min experiment are found in Fig. 3a–c. The gaseous halo is of mild intensity and observed for a short amount of time (from a minute at 1889 K to twenty minutes for 2133 K). The mass loss is low, and moderately sensitive to temperature, with 3 % at 1903 K and 4 % at 2123 K. Traces of Ba and La have been collected on the quartz tube for all four experiments. The shape of the stabilized liquid droplets, as shown in Fig. 3a–c is very similar to that of pure La_2S_3 shown in Fig. 1.

Figure 4a,b shows the secondary electron images of the cross section of the solidified droplet observed in the SEM. Macroscopically, a single phase as well as a macropore of few millimeters are observed for all La_2S_3 -rich compositions, regardless of the temperature. This macropore is not found on solidified samples if the droplet is exposed to several cycles of controlled vacuum/atmospheric melting. The small porosity observed at the bottom of the pictures is always present and attributed to the initial solid-rod porosity.

BaS-rich samples. BaS-rich samples do not exhibit favorable thermal properties and are difficult to melt. A thermal gradient is present and it proved possible to observe a liquid surface while the thermocouple remains mechanically entrapped in the core solid. BaS-rich liquid behavior is complex and cannot be described only through the analysis of $(\text{BaS})_{0.75}-(\text{La}_2\text{S}_3)_{0.25}$ samples, representing long term stability liquid behavior. The mass loss during $(\text{BaS})_{0.75}-(\text{La}_2\text{S}_3)_{0.25}$ experiments reaches 10 % for the lowest temperature (2103 K) and increases to 15 % at higher temperature (2233 K). Mass loss observed with other experiments on BaS-rich samples is not representative, droplets often fell or exploded. A larger quantity of powder is deposited on the quartz tube for BaS-rich samples than La_2S_3 -rich samples. Ba has been rejected on the quartz tube, no La has been found.

Figure 3d–f represent the shape of the molten droplet $(\text{BaS})_{0.75}-(\text{La}_2\text{S}_3)_{0.25}$ at three different times of the experiment. The neck forms slowly along with a diminution of the volume of liquid compared to its initial volume. For a constant lamp power, the neck melts instantaneously when the upper part of the sample is lowered into the hot zone. Figure 4c–d are SEM/EDS images of the $(\text{BaS})_{0.75}-(\text{La}_2\text{S}_3)_{0.25}$ samples at 2233 K and 2129 K, illustrating the final flattened shape, the neck position and the presence of multiple macrophases. The neck forms at the initial frontier of the solid and the liquid.

For $(\text{BaS})_{0.75}-(\text{La}_2\text{S}_3)_{0.25}$ long term experiment, as show on Fig. 4c–d, a porosity consisting on a sporadic repartition of pores with diameters of one-tens of a millimeter is observable. Increasing the temperature enhances the volume of visible gas generated. If no vacuum is applied during a long experiment, the porosity seems to decrease with the increase of temperature or time spent in the liquid state. However when BaS-rich samples are melted for few minutes and the neck formation is at its initial stage, the fast solidification without the application of vacuum leads to a macropore similar to the one observed for La_2S_3 -rich samples. This macropore is not found with repeated application of vacuum.

Composition of the solidified droplets. Three solid phases, named ϕ_1 , ϕ_2 and ϕ_3 are observed, distinguished by their relative barium content presented in Table 1. ϕ_1 is characterized by a maximum ratio of barium to the other metallic elements of 9 %. In ϕ_2 this ratio is at minimum 90 %. ϕ_3 is characterized by a ratio between

Figure 4. SEM (JEOL JSM- 6610LV, JEOL Ltd.) images of $(\text{BaS})_{0.25}\text{-(La}_2\text{S}_3)_{0.75}$ solidified droplets maintained at (a) 2023 K and (b) 1896 K; $(\text{BaS})_{0.75}\text{-(La}_2\text{S}_3)_{0.25}$ droplets maintained at (c) 2233 K and (d) 2129 K.

Phase ϕ_i	$[\text{Ba}]/([\text{Ba}]+[\text{La}])$
ϕ_1	0 to 9%
ϕ_2	90 to 100%
ϕ_3	23 to 42%

Table 1. Phases observed over the BaS- La_2S_3 pseudo-binary phase diagram.

23 to 42 %. La_2S_3 -rich samples are characterized by a single macrophase, as represented on Fig. 5a. The sample containing 50 mol% La_2S_3 is mostly the single homogeneous ϕ_3 solid solution, with traces of ϕ_1 and ϕ_2 present throughout the sample. Unfortunately, $(\text{BaS})_{0.4}\text{-(La}_2\text{S}_3)_{0.6}$ sample could not be characterized. Samples containing from 70 to 80 mol% La_2S_3 are composed of two phases, ϕ_1 and ϕ_3 with grain size of few tens of micrometers as shown on Fig. 5b. Sample containing 90 mol% of La_2S_3 is mainly composed of ϕ_1 , with some traces of ϕ_3 . The ratio of barium to metallic elements increases in ϕ_1 and ϕ_3 with the increase of the initial BaS concentration. The duration of the experiment and the operating temperature does not seem to affect the composition of the different solid solutions observed.

For BaS-rich samples, different macrophases are observed as shown on Figs. 4c,d and 6a. The presence of ϕ_1 , ϕ_2 , and ϕ_3 solid solutions have been observed in the BaS-rich samples and their presence are highly dependent of the parameters of the experiment (i.e. duration, cooling rate, remelt of the neck). For long term stability experiments conducted with $(\text{BaS})_{0.75}\text{-(La}_2\text{S}_3)_{0.25}$ samples (Fig. 4c,d), the neck region is in majority ϕ_2 with some ϕ_3 , whereas the molten region is mostly ϕ_3 solid solution with some ϕ_2 . Traces of ϕ_1 are observable mostly in the sintered region as seen in Fig. 6b.

Between 10 and 40 mol La_2S_3 , the sample is lowered by few millimeters in the hot zone to melt the neck and primary vacuum is applied several times in order to take liquid density measurements. BaS-rich samples exhibit a majority of ϕ_2 , and ϕ_3 solid solutions. However at 30 and 40 % La_2S_3 , ϕ_1 and ϕ_2 are largely observed while the presence of ϕ_3 solid solution tends to decrease. As shown in Fig. 6c the solidification of $(\text{BaS})_{0.70}\text{-(La}_2\text{S}_3)_{0.30}$ sample led to a phase separation in ϕ_1 and ϕ_2 solid solutions.

Figure 5. (a) SEM equipped with a single EDS detector images of $(\text{BaS})_{0.25}\text{-(La}_2\text{S}_3)_{0.75}$ sample acknowledging a single macrophase; (b) zoom on the red rectangle to observe the ϕ_1 and ϕ_3 phase separation on a microscale for $(\text{BaS})_{0.25}\text{-(La}_2\text{S}_3)_{0.75}$ sample.

WDS results. The average composition over 20 WDS points for the lanthanum sulfide leads to $\text{La}_{0.394}\text{S}_{0.606}$, close to the theoretical $\text{La}_{0.4}\text{S}_{0.6}$. The standard deviation for La is 0.445 mol% and the sum of the standard deviations of S and O reaches 2.167 mol%. The oxidation of La_2S_3 seems slow, with only few percent of oxygen found. A single point showed a high concentration of oxygen, likely representing a fully oxidized inclusion.

Figure 6. (a) SEM equipped with a single EDS detector images of $(\text{BaS})_{0.30}\text{-(La}_2\text{S}_3)_{0.70}$ sample acknowledging different macrophases; (b) example of ϕ_1 , ϕ_2 and ϕ_3 phase separation for $(\text{BaS})_{0.25}\text{-(La}_2\text{S}_3)_{0.75}$ samples; (c) example of ϕ_1, ϕ_2 phase separation for $(\text{BaS})_{0.30}\text{-(La}_2\text{S}_3)_{0.70}$ samples.

mol% La ₂ S ₃	0	10	20	30	40	50	60	70	80	90	100
Temperature (K)	2454	2149	1948	1824	1888	1921	1938	1928	1856	1843	2004
Standard deviation (K)	49	44	36	26	31	27	38	32	31	36	37
Solid density (g cm ⁻³)	3.29	4.26	4.68	4.78	4.67	5.14	-	5.18	5.12	5.21	5.17
Liquid density (g cm ⁻³)	-	-	3.54	3.5	-	3.63	-	-	3.75	3.69	3.69

Table 2. Liquidus temperature (K) and densities (g cm⁻³) for the initial concentration of La₂S₃ (mol%), «-» values not accessible.

The results are more scattered for BaS, with an atomic concentration between 37 to 51 mol% Ba, 2 to 30 mol% for O, and 31 to 47 mol% for S. The formation of different barium oxides, oxysulfides and oxysulfates support this range of variation. Only the results with a low percentage of oxygen are further considered. The average experimental composition is then Ba_{0.506}S_{0.493}, quite close to BaS. The standard deviation for Ba is 1.237 mol% and the sum of the standard deviations of S and O reaches 1.297 mol%.

Liquidus (Table 2). Table 2 represents the liquidus temperature measured for the BaS-La₂S₃ pseudo-binary compounds. The mean value for the melting point of BaS is 2454 K and 2004 K for La₂S₃. The addition of few percent of La₂S₃ into BaS leads to an important decrease of the liquidus temperature. The minimal melting temperatures are around 25 mol% and between 86 mol% La₂S₃, representative of two eutectic behaviors. For La₂S₃-rich samples, the gas generation is visibly limited, and the final elemental composition is close to the initial one. However, for BaS-rich samples, the important gas generation and sensibility to ambient air may lead to a slight shift of the initial BaS composition. Liquidus measurements are conducted as promptly as possible to stay close to the initial composition.

Densities (Table 2). Table 2 reports the solid and liquid density estimates obtained for the different compositions. A slightly closed porosity is observable at the bottom of the droplets, but has not been taken into account in those estimates. La₂S₃ has a measured solid density of 5.2 g cm⁻³, lowered to 3.7 g cm⁻³ around 2050 K in its liquid state. The solid density of BaS post experiment is 3.3 g cm⁻³, however this value is highly affected by the presence of porosity. The liquid density is not reported here due to the decomposition of BaS in temperature.

From 50 to 100 mol% La₂S₃, the solid densities are approximately independent of composition at around 5.2 g cm⁻³ while the liquid density is around 3.7 g cm⁻³. From 10 to 40 mol% La₂S₃, the solid density varies from 4.3 to 4.8 g cm⁻³, and is around 4.7 g cm⁻³ at 40 mol% La₂S₃. The liquid density in the range 10 to 40 mol% La₂S₃ fluctuates around 3.5 g cm⁻³. However values obtained for solid and liquid densities in the case of BaS-rich samples are impacted by the difficulty to determine the frontier between the solid and the liquid.

Thermodynamic approach of the volumetric isobaric thermal expansion coefficient α_p for La₂S₃. Figure 7 shows La₂S₃ sample at four different temperatures above the melting point. The temperatures considered are only reaching 60 K above the melting point. In order to maintain a quantity of matter constant at different temperatures, the origin of the considered droplet is set up at the solid/liquid interface of the highest measured temperature. This involves the consideration of a small solidified part for the lower temperature as observable in Fig. 7b–d. The results indicate a volumetric isobaric thermal coefficient of $3.4 \times 10^{-3} \text{ K}^{-1}$ with a standard deviation of $3 \times 10^{-4} \text{ K}^{-1}$.

Discussion

To the authors' best knowledge, for the first time this experimental design is used in the study of liquid state properties of high temperature sulfide compounds. Herein is demonstrated the range of possibilities of the thermal imaging furnace in the study of liquid state properties of high temperature compounds hardly attainable with other apparatus.

BaS and La₂S₃. The melting point of BaS reported here is in good agreement with the range of values reported in the literature: 2508, 2480, 2475, 2470 and 2430 K (respectively^{6–10}). The small shift found in the literature can be due to the uncertainty of measurements, the high instability of BaS_(l) and the possible presence of impurities. Ba_(l) and S_{2(l)} vaporize at 2170 K and 713 K respectively; BaS_(s) therefore decomposes directly into Ba_(g) and S_{2(g)} above 2454 K. The absence of liquid Ba_(l) into the remaining sample in the present study confirms this.

Regarding La₂S₃, the observed melting point here at 2004 K is a few hundred Kelvins lower than the values indicated in the literature^{10,33,34}. Notwithstanding, Bolgar *et al.* reported in 1986 the change of enthalpy with temperature for La₂S₃⁴⁷. A change of slope is noticeable at 2000 K, matching with the melting point reported herein. Unfortunately Bolgar *et al.* did not address melting or boiling points. The few volume of gas generated and the marginal mass loss indicate a boiling point higher than the melting point and a low partial pressure around 2000 K. The small volume of gas generated herein could be the consequence of the unknown saturation vapor pressure or the presence of impurities. La₂S₃ demonstrates a high stability in its liquid phase not described yet in the literature. From the conclusions presented by Flahaut *et al.*¹² regarding the strong similarities of ceric sulfides, it can be supposed that all ceric (+3) sulfides exhibit high stability in their liquid state.

Figure 7. Pictures of La_2S_3 droplet at (a) 2063 K, (b) 2051 K, (c) 2032 K, (d) 2017 K allowing the visualization of the variation of volume in temperature above the melting point and therefore the determination of the volumetric isobaric thermal expansion coefficient. (Camera Watec equipped with a UV filter).

BaS-rich and La_2S_3 -rich liquid behavior. The addition of BaS into La_2S_3 , from 10 to 40 mol% leads to remarkably stable La_2S_3 -rich melts, similar to pure La_2S_3 . The thin frontier between the solid and liquid, and the fast homogenization of the temperature inside the droplet indicate good thermal conduction. Added to a mass loss of a few percent, it can be concluded that La_2S_3 could be used as a liquid host to stabilize less stable compounds such as BaS.

The addition of few percent of La_2S_3 into BaS leads to an important decrease of the liquidus. Several studies^{3,6,7} make the case for a similar phenomenon for other additions to BaS. The addition of La_2S_3 favorably stabilizes BaS with temperature, however the presence of two immiscible liquids is not observed as in the case of BaS- Cu_2S ⁶. The liquid phase has a longer lifetime than pure BaS, nevertheless the formation of a neck at the solid-liquid frontier is visible over time.

A strong thermal gradient is observed in the case of BaS-rich samples. Figure 4 demonstrates different regions as a function of the distance from the hot zone. A important sintering process is also observed at the top, likely a consequence of the thermal gradient. The neck formation over time could be directly linked to the low thermal diffusion of BaS-rich samples 4[c-d]. Gravity might also play a key role in the non-homogeneous melting. Complementary studies are required to undertake the complex liquid behavior of BaS-rich samples.

Porosity. A macropore is observed for La_2S_3 -rich samples and regardless of the temperature. During the first heat up, the chemical formation of a sulfuric gaseous compound lead to the formation of microbubbles in addition to the micropores. These microbubbles can reach the surface and leave the system or agglomerate in the center of the molten droplet. The surface tension being too high, the trapped bubble cannot escape and result in a macropore.

For BaS-rich samples, a macropore is also observed for short term experiments and has the same origin as for La_2S_3 -rich samples. During long term experiments such as for $(\text{BaS})_{0.75}-(\text{La}_2\text{S}_3)_{0.25}$ samples, the decrease of the liquid volume by the neck formation potentially leads to an expulsion of the gaseous phase. The remaining porosity in $(\text{BaS})_{0.75}-(\text{La}_2\text{S}_3)_{0.25}$ experiments would certainly leave and thus create a porosity free sample if the experiments were conducted for a longer time. The elimination of the porosity in BaS-rich sample seems to be a slow process, equivalent to the neck formation.

BaS and La_2S_3 phase diagram. Ideally, experiments should be conducted with slow temperature variations in order to observe only thermodynamic stable phases. In addition, X-Rays Diffraction (XRD) and WDS analysis would bring the complementary information to conclude about the solid state nature, the sulfur concentration and the ratio of metallic elements in the different solid solutions. From the study of the ratio of metallic elements and the literature, assumptions have been made regarding the stoichiometric number of elemental

Figure 8. Liquidus temperature for the BaS- La_2S_3 pseudo binary system and definition of the potential domains of phase stability and proposed eutectic points (25 and 86 mol% of La_2S_3).

sulfur. The relatively fast cooling processes seen herein may lead to metastable phases, possibly explaining the presence of ϕ_1 , ϕ_2 and ϕ_3 solid solutions with variable compositions within a same sample.

ϕ_1 could be characteristic of La_2S_3 solid solution with insertion of BaS within a minimum concentration of 83 mol% La_2S_3 . Andreev and Khritohin already demonstrated the presence of a solid solution of La_2S_3 containing few percents of MnS and MgS^{20,21}. When combined with SrS or EuS however, La_2S_3 may demonstrate a large solubility reaching 50 mol%^{22,23}.

ϕ_2 potentially describes BaS solid-solution with addition of La_2S_3 within a maximum concentration of 5 mol% La_2S_3 . Andreev and Khritohin also confirmed the presence of a solid solution of BaS containing few percents of Lu_2S_3 , Pr_2S_3 , Sm_2S_3 , Tb_2S_3 , Y_2S_3 or Nd_2S_4 : rare earth sesquisulfides with properties similar to La_2S_3 ^{8,24}.

ϕ_3 is a third solid solution with a composition ranging from 41 to 63 mol% La_2S_3 . The median composition of this solid solution is around 50 mol% La_2S_3 , leading to a potential ϕ_3 solid solution built around BaLa_2S_4 . However, BaLa_2S_4 has not been reported and is not observed here. The phase diagrams of BaS- Sm_2S_3 and SrS- Tb_2S_3 also show a third solid solution. But these phases have a shorter stability domain than observed herein and occur where MLn_2S_4 (M = Ba, Sr; Ln = Sm, Tb) represents a limit and not the median composition^{24,25}.

Figure 8 represents the liquidus temperature over the BaS- La_2S_3 pseudo-binary composition range. ϕ_1 , ϕ_2 and ϕ_3 solid solutions are represented in their stability domain observed through the experiments. Traces of ϕ_1 in the BaS-rich samples and those of ϕ_3 at 90 mol% La_2S_3 are not considered. These traces may be the consequence of a fast cooling process, leading to thermodynamic unstable phases. Two eutectic points are hypothesized at 25 mol% and 86 mol% La_2S_3 .

Solid density. The solid density of La_2S_3 , herein 5.2 g cm^{-3} , is higher than the 5.0 g cm^{-3} reported literature value¹⁷. An experiment with another density measurement apparatus and a study of the crystal structure by XRD would be able to confirm or deny the result. A possible explanation to this difference could be the generation of a new crystal structure for La_2S_3 : the solidification process from its liquid state does not crystallize in the γ , β or α - La_2S_3 form, but into another unreported crystal structure denser than the ones reported so far. The solid density of BaS post experiment reaches 3.3 g cm^{-3} , a value highly affected by the porosity hence discarded.

Except for La_2S_3 and BaS, the presence of at least two solid solutions involves an apparent density function of the proportion of each solid solution and their respective composition. The solid density along the La_2S_3 -rich samples seems constant around 5.2 g cm^{-3} . The values calculated on the BaS-rich samples are impacted by the presence of open and closed porosity. In addition the thermal insulator behavior of BaS-rich samples makes the frontier between the molten part and the rest of the rod difficult to determine.

Liquid density. No literature discussing the density of rare earth sulfide in temperature has been found. As in the case of metallic sulfide⁴⁸, BaS- La_2S_3 density decreases with the increase of temperature. The difference between solid and liquid densities fluctuate between 1 and 1.5 g cm^{-3} , which are typical values reported for metallic sulfides. The small sample size, imperfect radial homogeneity, neck formation and porosity affect the results. A study with larger samples may be beneficial to increase the precision in the liquid density estimation.

Volumetric isobaric thermal expansion coefficient α_p for La_2S_3 . Using two different samples, the isobaric thermal expansion coefficient was estimated around $3.4 \times 10^{-3} \text{ K}^{-1}$ with a standard deviation of $3 \times 10^{-4} \text{ K}^{-1}$. The authors did not find any existing literature discussing this coefficient for liquid rare-earth sulfides.

Conclusion

High temperature liquid sulfide compounds were analyzed using a container-less thermal imaging furnace. Direct visualization of melting and solidification processes allowed to verify the thermal trace obtained from simple thermometry. Liquid properties such as stability, evaporation rate and liquid density were investigated. The melting point of BaS and La_2S_3 were re-evaluated to 2454 K and 2004 K respectively. The high stability of liquid La_2S_3 was observed while the sublimation of BaS was visually confirmed. BaS, unstable in its liquid state, partially stabilized with the addition of La_2S_3 . Degassing and neck formation created difficulties in the study of BaS-rich samples. La_2S_3 -rich liquids demonstrated for their part a stunning stability.

Received: 15 March 2021; Accepted: 17 June 2021

Published online: 14 September 2021

References

- Yuan, H., Zhang, J., Yu, R. & Su, Q. Synthesis of rare earth sulfides and their UV-vis absorption spectra. *J. Rare Earths* **27**, 308–311 (2009). [https://doi.org/10.1016/S1002-0721\(08\)60239-2](https://doi.org/10.1016/S1002-0721(08)60239-2).
- Méresse, Y., Fonteneau, G. & Lucas, J. New chalcogenide glasses in the system BaS-CdS-GeS₂. *J. Non-Cryst. Solids* **213–214**, 55–57 (1997). [https://doi.org/10.1016/S0022-3093\(96\)00661-8](https://doi.org/10.1016/S0022-3093(96)00661-8).
- Hidaka, C., Goto, M., Kubo, M. & Takizawa, T. Phase diagrams of the pseudo-binary systems of BaS-Ln₂S₃ and BaS-Ga₂S₃. *J. Crystal Growth* **275** (2005). <https://doi.org/10.1016/j.jcrysgro.2004.11.016>.
- Grattidge, W. & John, H. The electronic properties of barium sulfide. *J. Appl. Phys.* **23**, 1145–1151 (1952). <https://doi.org/10.1063/1.1701999>.
- Egami, A., Onoye, T. & Narita, K. Electrical conductivities of alkaline earth sulfides. *Trans. Japan Inst. Metals* **22**, 399–409 (1981).
- Stinn, C., Nose, K., Okabe, T. & Allanore, A. Experimentally determined phase diagram for the barium sulfide-copper(I) sulfide system above 873K (600 °C). *Metall. Mater. Trans. B.* **48**, 2922–2929 (2017). <https://doi.org/10.1007/s11663-017-1107-5>.
- Holcombe, C. E. Tentative CeF₃-BaS phase diagram. *J. Less-Common Metals* **102**, L1–L3 (1984).
- Andreev, O. V., Miodushevsky, P. V., Serlenga, R. & Parsukov, N. N. Phase equilibria in the BaS-Ln₂S₃-Ln₂S₃ systems. *J. Phase Equilib. Diffus.* **26**, 109–114 (2005). <https://doi.org/10.1007/s11669-005-0129-x>.
- Lively, D. T. The high temperature stability of oxides and sulfides. *J. Less-Common Metals* **1**, 145–151 (1959).
- Kertman, A. V. *Sulfides and fluorosulfide infrared materials, phase diagrams, structure and properties of sulfide compounds of gallium, indium, lanthanides*. Ph.D. thesis, GOU VPO Tyumen State University (2010).
- Bonnivard, G., Carly, R. & Lorang, M. Barytine de Chaillac (Indre) / Confidential. Technical Report, Bureau de recherches géologiques et minières; Département Valorisation des Minerais (1968).
- Flahaut, J., Guittard, M., Loriers, J. & Patrie, M. Sur les sulfures et oxysulfures de gadolinium, dysprosium et erbium. *Comptes rendus hebdomadaires des séances de l'Académie des Sciences* **2291–2293** (1957).
- Flahaut, J. & Guittard, M. Sur les sulfures d'Yttrium. *Comptes rendus hebdomadaires des séances de l'Académie des Sciences* **1210–1212** (1956).
- Flahaut, J. & Guittard, M. Sur les sulfures et le polysulfure de cérium. *Comptes rendus hebdomadaires des séances de l'Académie des Sciences* **1419–1422** (1956).
- Picon, M. & Patrie, M. Sur les sulfures et polysulfures des terres rares cériques. *Comptes rendus hebdomadaires des séances de l'Académie des Sciences* **561–567** (1956).
- Flahaut, J. & Guittard, M. Sur les sous-sulfures de cérium et d'yttrium. *Comptes rendus hebdomadaires des séances de l'Académie des Sciences* **1318–1321** (1956).
- Picon, M. & Patrie, M. Sur les sous-sulfures des terres rares cériques. *Comptes rendus hebdomadaires des séances de l'Académie des Sciences* **1321–1324** (1956).
- Andreev, O. V. Trend Analysis of Interactions in BaS-Ln₂S₃ systems. *Zurnal neorganiceskoj himii* **44**, 825–827 (1999). <https://doi.org/10.1080/10643389.2012.728825>.
- Andreev, O. V. & Monina, L. N. Acidities of 3d and 4f element sulfides are the key factor governing the type of phase diagram in MS-Ln₂S₃ (M = Mn, Fe; Ln = La-Lu) systems. *Russ. J. Inorg. Chem.* **59**, 971–978 (2014). <https://doi.org/10.1134/S0036023614090034>.
- Andreev, O. V. & Monina, L. N. MnS-Ln₂S₃ (Ln = La, Nd, or Gd) phase diagrams; thermodynamics of phase transitions. *Russ. J. Inorg. Chem.* **57**, 1393–1397 (2012). <https://doi.org/10.1134/S0036023612100026>.
- Khritohin, N. A. Thermodynamics of the phase transitions in the MgS-Ln₂S₃ (Ln=La, Gd, Dy) systems. *Zurnal neorganiceskoj himii* **47**, 129–131 (2002).
- Andreev, O. V. Phase Equilibrium in the SrS-Ln₂S₃ (Ln = La, Gd, Nd) systems. *Zurnal neorganiceskoj himii* **36**, 253–256 (1991).
- Andreev, O. V. & Ruseikina, A. V. Phase diagrams of the Ln₂S₃-EuS (Ln = La-Gd) systems. *Russ. J. Inorg. Chem.* **58**, 1561–1566 (2013). <https://doi.org/10.1134/S0036023613120036>.
- Khritohin, N. A., Andreev, O. V., Mitroshin, O. V. & Korotkov, A. S. Thermodynamics of phase changes in systems BaS-Ln₂S₃ (Ln = Pr, Sm, Gd, Tb, Er, Lu). *J. Phase Equilib. Diffus.* **25**, 515–519 (2004). <https://doi.org/10.1361/15477020421241>.
- Andreev, O. V. Interaction in the systems SrS-Ln₂S₃ (Ln=Tb, Dy, Er) and general features of phase formation in the series of the systems SrS-Ln₂S₃. *Zurnal neorganiceskoj himii* **43**, 1223–1228 (1998).
- Zhang, X., Gui, W., Wu, Q. & Zeng, Q. Structural, phonon, mechanical, optical, and thermodynamic properties of stable β-La₂S₃ from first-principles calculations. *J. Rare Earths* **35**, 271–279 (2017). [https://doi.org/10.1016/S1002-0721\(17\)60910-4](https://doi.org/10.1016/S1002-0721(17)60910-4).
- Biswas, K. & Varadaraju, U. V. Stabilization of γ-La₂S₃ by alkali metal ion doping. *Mater. Res. Bull.* **42**, 385–388 (2007). <https://doi.org/10.1016/j.materresbull.2006.05.029>.
- Luo, X., Zhang, M., Ma, L. & Peng, Y. Preparation and stabilization of γ-La₂S₃ at low temperature. *J. Rare Earths* **29**, 313–316 (2011). [https://doi.org/10.1016/S1002-0721\(10\)60450-4](https://doi.org/10.1016/S1002-0721(10)60450-4).
- Kumta, P. N. & Risbud, S. H. Low temperature synthesis of cubic lanthanum sulfide (La₂S₃) powders. *Mater. Sci. Eng. B* **2**, 281–286 (1989). [https://doi.org/10.1016/0921-5107\(89\)90005-6](https://doi.org/10.1016/0921-5107(89)90005-6).
- Kamarzin, A. A., Mironov, K. E., Sokolov, V. V., Malovitsky, Y. N. & Vasilyeva, I. G. Growth and properties of lanthanum and rare-earth metal sesquisulfide crystals. *J. Cryst. Growth* **52**, 619–622 (1981).
- Kay, D. A. R., Subramanian, S. V., Kumar, V., Meng, V. & Dwivedi, R. K. The use of RE-O-S phase stability diagrams in gaseous desulfurisation and iron and steel production. *Inorg. Chim. Acta* **94**, 132–134 (1984). [https://doi.org/10.1016/S0020-1693\(00\)94597-3](https://doi.org/10.1016/S0020-1693(00)94597-3).
- Vasilyeva, I. G. & Nikolaev, R. E. The La₂S₃-La₂S₃ system: thermodynamic and kinetic study. *J. Solid State Chem.* **183**, 1747–1751 (2010). <https://doi.org/10.1016/j.jssc.2010.05.026>.
- Nikolaev, P. E. & Vasilyeva, I. G. Vapor pressure determination for solid and liquid La₂S₃ using boiling points. *Inorg. Mater.* **44**, 1367–1371 (2008). <https://doi.org/10.1134/S0020168508120194>.

34. Vasilyeva, I. G. & Nikolaev, R. E. High temperature solid-vapor and liquid-vapor transitions in binary and ternary chalcogenides La_2S_3 , MoS_2 , Mo_2S_3 , LiInSe_2 . *J. Alloy. Compd.* **452**, 89–93 (2008).
35. Flahaut, J. & Guittard, M. Sur les oxysulfures de cérium et d'yttrium. *Comptes rendus hebdomadaires des séances de l'Académie des Sciences* 1775–1778 (1955).
36. Picon, M. & Patrie, M. Sur les oxysulfures de terres rares cériques. *Comptes rendus hebdomadaires des séances de l'Académie des Sciences* 516–518 (1956).
37. Perry, D. L. *Handbook of Inorganic compounds V2* (CRC Press/Taylor and Francis, 2011).
38. Zhukov, S. et al. Structural study of lanthanum oxysulfate LaO_2SO_4 . *Mater. Res. Bull.* **32**, 43–50 (1997). [https://doi.org/10.1016/S0025-5408\(96\)00159-6](https://doi.org/10.1016/S0025-5408(96)00159-6).
39. Kumta, P. N. & Risbud, S. H. Non-aqueous chemical synthesis of tetragonal (β - La_2S_3) lanthanum sulfide powders. *Mater. Sci. Eng. B* **18**, 260–268 (1993). [https://doi.org/10.1016/0921-5107\(93\)90141-9](https://doi.org/10.1016/0921-5107(93)90141-9).
40. Patil, S. J., Kumbhar, V. S., Patil, B. H., Bulakhe, R. N. & Lokhande, C. D. Chemical synthesis of α - La_2S_3 thin film as an advanced electrode material for supercapacitor application. *J. Alloy. Compd.* **611**, 191–196 (2014). <https://doi.org/10.1016/j.jallcom.2014.04.203>.
41. Patil, S. J., Lokhande, A. C. & Lokhande, C. D. Effect of aqueous electrolyte on pseudocapacitive behavior of chemically synthesized La_2S_3 electrode. *Mater. Sci. Semicond. Process.* **41**, 132–136 (2016). <https://doi.org/10.1016/j.mssp.2015.07.094>.
42. Isobe, M., Hayashi, A. & Ueda, Y. Preparation and some physical properties of superconducting $\text{La}_{3-x}\text{S}_4$ and $\text{La}_{3-y}\text{Ba}_y\text{S}_4$. *Physica C* 777–778 (1994).
43. Wood, C. et al. Thermoelectric properties of lanthanum sulfide. *J. Appl. Phys.* **58**, 1542–1547 (1985).
44. Sahu, S. K., Chmielowiec, B. & Allanore, A. Electrolytic extraction of copper, molybdenum and rhenium from molten sulfide electrolyte. *Electrochimica Acta* **243**, 382–389 (2017). <https://doi.org/10.1016/j.electacta.2017.04.071>.
45. Wunderlich, B. Thermal analysis. *Anal. Chem.* **76**, 3299–3312 (2004).
46. Wu Mindy, A. A. & Caldwell, Andrew H. Surface tension of high temperature liquids evaluation with a thermal imaging furnace. *Miner. Metals Mater. Ser.* 33–41. https://doi.org/10.1007/978-3-030-06143-2_4 (2019).
47. Bolgar, A. S., Kriklya, A. I. & Kartuzova, L. N. Enthalpy and heat capacity of lanthanum sulfides. *Poroshkovaya Metallurgiya* **209**, 90–94 (1986).
48. Tesfaye Firdu, F. & Taskinen, P. *Densities of Molten and solid alloys of (Fe, Cu, Ni, Co)-S at elevated temperatures-literature review and analysis* (Multiprint, 2010).

Acknowledgements

The authors wish to acknowledge the DOE-EERE (project DE-EE0008316) for their financial support to this project. The authors also wish to thank Dr. Hachi Yagi, Dr. Andrew Caldwell and Mr. Caspar Stinn for their insights and experimental assistance.

Author contributions

C.B. conducted the research conceived with advising from A.A., and wrote the manuscript. All authors reviewed the manuscript.

Competing interests

The authors declare no competing interests.

Additional information

Correspondence and requests for materials should be addressed to A.A.

Reprints and permissions information is available at www.nature.com/reprints.

Publisher's note Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.

Open Access This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons licence, and indicate if changes were made. The images or other third party material in this article are included in the article's Creative Commons licence, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons licence and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder. To view a copy of this licence, visit <http://creativecommons.org/licenses/by/4.0/>.

© The Author(s) 2021