OPEN

SUBJECT AREAS:
ELECTRONIC DEVICES
APPLIED PHYSICS

Received
24 December 2013

Accepted
6 March 2014

Published
21 March 2014

Correspondence and
requests for materials
should be addressed to
Z.Y.L. (zyli@ustc.edu.
cn) or W.C. (phycw@
nus.edu.sg)

* These authors
contributed equally to
this work.

Elementary Process for CVD Graphene on Cu(110): Size-selective Carbon Clusters

Jialin Zhang^{1*}, Zhunzhun Wang^{2*}, Tianchao Niu³, Shengnan Wang², Zhenyu Li² & Wei Chen^{1,3}

¹Department of Physics, National University of Singapore, 2 Science Drive 3, 117542, Singapore, ²Hefei National Laboratory for Physical Sciences at Microscale, University of Science and Technology of China, Hefei 230026, China, ³Department of Chemistry, National University of Singapore, 3 Science Drive 3, 117543, Singapore.

Revealing the graphene growth mechanism at the atomic-scale is of great importance for achieving high quality graphene. However, the lack of direct experimental observation and density functional theory (DFT) verification hinders a comprehensive understanding of the structure of the carbon clusters and evolution of the graphene growth on surface. Here, we report an in-situ low-temperature scanning tunneling microscopy (LT-STM) study of the elementary process of chemical vapor deposition (CVD) graphene growth via thermal decomposition of methane on Cu(110), including the formation of monodispersed carbon clusters at the initial stage, the graphene nucleation and the ripening of graphene islands to form continuous graphene film. STM measurement, supported by DFT calculations, suggests that the carbon clusters on the surface are C₂H₅. It is found that graphene layers can be joined by different domains, with a relative misorientation of 30°. These graphene layers can be decoupled from Cu(110) through low temperature thermal cycling.

Ever since its mechanical exfoliation from small mesas of highly oriented pyrolytic graphite, graphene has spurred a tremendous of interest because of its exceptional electronic and mechanical properties, such as anomalous quantum Hall Effect (QHE), long-range ballistic transport, high carrier mobility, tunable band gap, high elasticity and intrinsic strength^{1–4}. All these qualify graphene as a promising material for applications in microelectronic and spintronic devices^{1–3}, sensors⁵, supercapacitors⁶, building blocks for multifunctional composites⁷ as well as for structural and mechanical applications⁴. Motivated by these extraordinary properties and numerous potential applications, a number of graphene fabrication methods have been explored, including the micromechanical cleavage of graphite¹, thermal decomposition of SiC⁸, reduction of chemically functionalized graphene^{9–12}, chemical exfoliation of graphite¹³ and transition metal (TM)-catalyzed chemical vapor deposition (CVD)^{14–26}, and so on. Graphene prepared by cleavage and exfoliation of graphite shows superior transport properties, but its size is usually limited to micrometers and the productivity of this method is very low¹. Epitaxial graphene on SiC allows larger area synthesis²⁷, but this method induces noticeable densities of defects and achieving large graphene domains with uniform thickness remains a challenge²⁸. Transition metal assisted growth of graphene, which provides many unique advantages, such as industrial scalability²¹, relatively low temperature processing¹⁸, easy transferring onto other substrates²³, has received the most attention.

The graphene growth on TM surfaces is based on high-temperature pyrolysis of hydrocarbons and different growth mechanisms can be involved according to the carbon solubility limit in the metal. For the growth on TM where carbon is soluble, the graphene forms when the sample is cooled and carbon segregates on the surface (surface segregation)^{29–32}; but for TM with very low carbon solubility, the synthesis is limited to the surface of the catalyst and mainly involves surface diffusion and nucleation of carbon atoms. The growth of graphene can be accomplished by CVD via two approaches: directly cracking the carbon source on TM surface at a high temperature or temperature programmed growth (TPG) via room temperature adsorption of the molecules followed by pyrolysis and graphene growth at a fixed elevated temperature¹⁷.

Graphene growth has been demonstrated on a variety of TMs. For example, Li and colleagues reported a CVD method that used copper-foil to produce single crystal graphene with dimensions of up to 0.5 mm²⁰; Bae and colleagues demonstrated a roll-to-roll production of 30 inch graphene films for transport electrodes²¹; Gao and colleagues showed the repeated growth and bubbling transfer of graphene with millimeter-size single-crystal grains using platinum²⁴. Additionally, intensive theoretical efforts have been devoted to revealing the growth

mechanism^{14,33–43}. Using first-principle calculations, Chen et al. found on flat surfaces of Ir(111) and Ru(0001), two carbon atoms repel each other; while they prefer to form a dimer on Cu(111)³⁷. Zhang et al. also revealed that C_2H_2 can be easily formed on a Cu(111) surface, which represents a more favorable reaction path compared to CH dissociation³⁸. By careful optimization of the supported carbon clusters C_N on Ni(111), Gao et al. indicated a ground state structure transition from a one-dimensional (1D) carbon chain to a two-dimensional (2D) sp^2 carbon network at $N \sim 10$ – 12 ⁴⁰; while Wesep and co-workers proposed an energetic preference for the formation of stable 1D carbon nanoarches consisting of 3–13 atoms on Cu(111) surface⁴³. Explored by ab initio calculations, Yuan et al. showed that the core-shell C_{21} is a very stable magic carbon cluster on Rh(111), Ru(0001), Ni(111) and Cu(111) surfaces⁴². Zangwill et al. predicted that an immobile island composed of six five-atom carbon clusters as the smallest stable precursor to graphene growth on metals⁴¹. Despite these inspiring achievements, most of these theoretical studies only address the number of carbon atoms, and the precise determination of hydrogen atoms within the cluster is rare. Moreover, very little of the growth mechanism in the initial nucleation stages of carbon atoms has been revealed experimentally^{15,16,44}. In this regard, atomic-scale characterization of a complete process of graphene growth in combination with theoretical calculations is of great importance, for both fundamental interest and achieving high quality graphene.

Here, we report an atomic scale characterization of the elementary process of CVD graphene growth via thermal decomposition of methane (CH_4) on Cu(110) using low-temperature scanning tunneling microscopy (LT-STM), including the formation of monodispersed carbon clusters at low temperature, nucleation and ripening of graphene islands at high temperature. Combined with first principles calculations, the monodispersed carbon clusters are identified as C_2H_5 . Different domains stitch together to form a graphene layer,

with a preference angle of 30° at the grain boundaries. These graphene layers can be decoupled from Cu(110) through low temperature thermal cycling.

Results

As shown by the high magnification STM image in Fig. 1a, upon the deposition of CH_4 at room temperature (RT) and subsequent annealing at 480°C in CH_4 at a pressure of 2×10^{-5} mbar for 50 min, the Cu(110) surface was almost decorated with carbon clusters of mono-dispersed size. Each carbon cluster appears as a bright spot with an identical size of 0.4 nm. Careful inspection of the STM image reveals that the surface is decorated by isolated but well-defined superstructures, where the carbon clusters are adsorbed in an epitaxial relationship with the underlying Cu(110). As indicated by the dashed lines in Fig. 1a, the minimum distance between two neighboring rows is $2a_0$ of 0.512 nm; while it is $2b_0$ of 0.723 nm between two columns (a_0 and b_0 are the unit cell dimensions of Cu(110)). It can also be revealed that the carbon cluster arrays are aligned precisely with the crystal orientation of the underlying Cu(110). The carbon cluster at this low coverage was referred to as “cluster 1” with a density around $2.70 \times 10^{14}/\text{cm}^2$. Previous theoretical studies proposed that carbon dimers are energetically favorable on the Cu surface^{37–39}. Therefore, we tentatively assign these carbon clusters as carbon dimers (C_2H_x).

Further increasing the coverage of the carbon clusters can result in the formation of a hexagonally close packed structure, as shown in Fig. 1b. The coverage of the carbon clusters can be increased through low temperature thermal cycling as described in the supporting information. Some gaps can still be observed between the ordered domains. However, the carbon clusters in each ordered domain possess the unit cell with $a = 0.515$ nm, $b = 0.500$ nm and an inclusion angle of 60° , as indicated by arrows A and B. Upon saturation of the carbon clusters on the surface, they formed highly ordered close packed structure over the surface, as shown in Fig. 1c. The unit cell

Figure 1 | Evolution of carbon clusters and formation of graphene on Cu(110). (a) STM image ($V_{\text{tip}} = 0.25$ V, 10×10 nm²) of the low coverage carbon clusters on Cu(110), which were formed upon the deposition of CH_4 at room temperature and subsequent annealing at 480°C in CH_4 at a pressure of 2×10^{-5} mbar for 50 min. (b) STM image ($V_{\text{tip}} = 1$ V, 10×10 nm²) of carbon clusters at higher coverage; A and B indicate the direction of the unit cell vectors. (c) Hexagonally close packed cluster structure formed by further increasing the carbon clusters coverage. ($V_{\text{tip}} = 0.2$ V, 10×10 nm²), C and D indicate the direction of the unit cell vectors. (d) Large scale STM image ($V_{\text{tip}} = 0.5$ V, 50×50 nm²) of carbon clusters and small graphene flakes on Cu(110) by annealing Cu(110) in CH_4 at 550°C at a pressure of 2×10^{-5} mbar for 130 min, where the graphene flakes are indicated by “G”. (e) The corresponding high resolution STM image ($V_{\text{tip}} = 0.1$ V, 15×15 nm²) showing the hexagonally close packed carbon clusters in panel 1 (d), where E and F indicate the direction of the unit cell vectors. (f) The atomically resolved STM image ($V_{\text{tip}} = 0.03$ V, 5×5 nm²) showing the 1×1 graphene lattice.

was further reduced to $c = 0.450$ nm, $d = 0.480$ nm with an unchanged inclusion angle of 60° . At this stage, the carbon cluster density was increased to $10.9 \times 10^{14}/\text{cm}^2$, referred to as “cluster 2”. In this regime, the arrangement is supposed to be cluster-cluster interaction dominated. Some brighter lines can be frequently observed, induced by the stress relaxation at high cluster coverage with increased lateral inter-cluster interaction.

Annealing the Cu(110) surface at high temperature at 550°C in CH_4 at a pressure of 2×10^{-5} mbar for 130 min can promote the nucleation of small graphene flakes. As shown in Fig. 1d, at this stage the carbon clusters co-exist with the small graphene flakes which are indicated as “G”. The high magnification STM image in Fig. 1e reveals that the clusters on Cu(110) are “cluster 2”. The directions of the unit cell are indicated by arrows E and F, with lateral dimensions of $e = 0.450$ nm, $f = 0.480$ nm and an inclusion angle of 60° . The bright stripes inserted between these clusters are clean Cu(110) surface but with a 1×2 superstructure as highlighted by the red dotted line in Fig. 1e. Figure 1f shows the atomically resolved STM image of the 1×1 graphene lattice, and the crystal orientation of the underlying Cu(110) is indicated in the lower right corner.

To obtain the atomic structure of the carbon clusters, the adsorption of various carbon clusters on Cu(110) were simulated using DFT. First, the stability of C_iH_x ($0 \sim 4$) and C_2H_x ($0 \sim 6$) clusters on Cu (110) were studied. We define the formation energy in equation (1)

$$E_F = E_{\text{tot}} - E_{\text{sub}} - \sum_i n_i \mu_i \quad (1)$$

where E_{tot} is the total energy of the adsorbed system, E_{sub} is the energy of clean Cu (110) substrate, μ_i and n_i ($i = \text{C}, \text{H}$) represent chemical potential and the number of atoms in the cluster, respectively. Considering the equilibrium of CH_4 and H_2 , the relationship of μ_{H} and μ_{C} in unit of electron volt can be obtained as equation (2) by the process described in the supporting information:

$$\mu_{\text{C}} = g_{\text{CH}_4} - 4\mu_{\text{H}} = -2\mu_{\text{H}} - 9.695 + 0.0689 \ln \chi \quad (2)$$

Here, χ is the ratio of the partial pressures of CH_4 and H_2 .

For each carbon cluster species, the most stable adsorption configuration was found by checking different adsorption sites on Cu(110) surface, including the hollow site (H-site), bridge-long site (B_{long} site), bridge-short site (B_{short} site) and Top site (T-site)⁴⁵. Figure 2 shows the formation energy of various carbon cluster species

Figure 2 | Relationship of formation energy and chemical potential of H or the pressure of H_2 . Relationship of adsorption energy and chemical potential of H or the pressure of H_2 during CVD growth of carbon-clusters on Cu (110) at $T = 527^\circ\text{C}$. The ratio of partial pressures of CH_4 and H_2 is $\chi = 20$.

as a function of the chemical potential of H (thus the partial pressure of H_2). The χ here was set to be 20 : 1; we also tested $\chi = 1 : 20$, which gave similar results.

From Fig. 2, it is easy to find that clusters C_2H_6 and C_2H_5 are the two most stable species under all physical H_2 partial pressure. Although the formation energy of C_2H_6 is very large, as a close shell molecule, its adsorption energy is expected to be very small, and it's hence easy to desorb from Cu(110) at high temperature. The average lifetime of C_2H_6 and C_2H_5 can be estimated by their adsorption energy E_a via $\tau_a = \frac{1}{\nu_0} e^{E_a/kT}$ ⁴⁶. According to our calculations, adsorption energy of C_2H_6 and C_2H_5 on Cu(110) surface are 0.41 and 2.85 eV, respectively. ν_0 is about 10^{13} s^{-1} . Therefore, their average lifetime on the surface at 480°C is 5.5×10^{-11} and $1.2 \times 10^{-6} \text{ s}$, respectively. Such a short lifetime makes C_2H_6 not be able to be observed by STM. Therefore, C_2H_5 could be the most possible abundant species from the thermodynamic point of view.

STM images of several partially dehydrogenated carbon dimer species were also simulated using the Tersoff and Hamann approximation⁴⁷. Figure 3 shows the optimized structures and simulated STM images of C_2 , C_2H_4 , C_2H_5 and C_2H_6 . The optimized unit cell of the carbon cluster is $2a_0 = 0.504$ nm, $2b_0 = 0.713$ nm. Among these carbon clusters, the simulated STM image of C_2H_5 is in good agreement with the experimental results. All other stable species cannot reproduce the experimental circular shape. Hence, the basic structures of the carbon clusters are elucidated by the STM images in combination with DFT calculations as C_2H_5 .

Large graphene flakes can be achieved through low temperature thermal cycling process as described in the supporting information. Figure 4a shows a large scale STM image of a flake of graphene film on Cu(110) interconnected by two graphene grains, forming a grain boundary in between as indicated by the red ellipse. Close-up (Fig. 4b) and the corresponding atomic-resolution STM images (Fig. 4c) reveal that the two graphene grains are stitched together to form a continuous film with a relative misorientation of 30° . The detailed atomic structure at the grain boundary cannot be identified

Figure 3 | Optimized structures (left panels) and simulated STM images. Optimized structures (left panels) and simulated STM images (right panels) of (a, b) C_2 , (c, d) C_2H_4 , (e, f) C_2H_5 , and (g, h) C_2H_6 . The integrated density of states from 0.25 V below E_F to the Fermi level is used to simulate the STM image, which represents the HOMO of the carbon clusters.

Figure 4 | STM images showing the jointed domains and low temperature thermal cycling induced decoupling of graphene from Cu(110) substrate. (a) Large scale STM image ($V_{\text{tip}} = 1$ V, 100×100 nm²) showing one graphene flake jointed by different domains, which was formed by low temperature thermal cycling and subsequent annealing of the carbon clusters on Cu(110) up to 720°C. (b) The corresponding high resolution STM image ($V_{\text{tip}} = 0.04$ V, 20×20 nm²) showing the domain boundary. (c) The atomically resolved STM image ($V_{\text{tip}} = 0.03$ V, 5×5 nm²) illustrating two distinct graphene orientations, the upper domain is orientated at an angle of 30° relative to the lower domain. (d) Large scale STM image ($V_{\text{tip}} = 1.0$ V, 250×250 nm²) of Cu(110) covered by large flakes of graphene and carbon clusters. (e) A continuous single layer of graphene with different contrast ($V_{\text{tip}} = 0.05$ V, 15×15 nm²). (f) ($V_{\text{tip}} = -0.01$ V, 5×5 nm²) The corresponding high resolution STM images of panel (e), where the orientation of graphene is indicated by the red arrows.

from our STM image, but it has been theoretically proposed and experimentally conformed as a series of pentagons, heptagons and distorted hexagons^{25,48}. The graphene grows in different orientations with respect to the underlying lattice, resulting in two different moiré patterns. As shown in Fig. 4c, the lower right panel shows a moiré superstructure almost aligned with the underlying Cu(110) lattice, referred to as R0 phase. The graphene lattice of the upper left panel shows a different moiré pattern with a larger periodic modulation and is rotated by 30° from the lower R0 phase, referred to as R30 phase. Supplementary Fig. S3 on line shows a graphene film joined by multi-domains taken from a different location on Cu(110), which also shows a 30° misorientation. The preference of around 30° misorientation between two domains has also been reported by other groups^{19,25}. For graphene grown on Ru(0001), only one orientation can be observed, due to the strong interaction between graphene and Ru²⁹. The two dominating orientations observed here and the fact that graphene can grow continuously across Cu step edges could indicate a weaker graphene-Cu interaction when compared with Ru.

As described in the supporting information, during the experiment, we introduced the low temperature thermal cycling method to increase the carbon cluster coverage. Figure 4d shows the STM image of large flakes of graphene coexisting with carbon clusters on Cu(110). After repeating several cycles of low temperature thermal cycling, the graphene flakes on the surface possess two stripe-shaped contrasts. Comparison between Supplementary Fig. S2 on line and Fig. 4d reveals that the appearance of those bright stripes are same with the previous small graphene islands; while the dark stripes are newly produced during the low temperature thermal cycling. Close up STM image in Supplementary Fig. S4 on line and Fig. 4f reveals that the bright and dark stripes alternated between each other with a continuous boundary. As shown in Fig. 4e, the bright stripes (BG) show moiré pattern resembling the underlying Cu(110); while the dark stripes (DG) display perfect hexagonal graphene lattice. These contrasts result from the modulation by different interactions with

the underlying Cu(110). The appearance of the perfect hexagonal graphene lattice in DG suggests that the graphene in this region is physically decoupled from the underlying Cu(110).

The formation of such physically decoupled graphene can arise from the intercalation at the graphene/Cu(110) interface by hydrogen atoms released from CH₄ decomposition, similar to the previously reported hydrogen⁴⁹, lithium⁵⁰, oxygen⁵¹, and fluorine intercalation to form quasi-free-standing graphene⁵²; or from the strain relief during the annealing/cooling cycles due to the different thermal expansion of graphene film and Cu substrate⁵³. More controlled experiment and detailed theoretical calculations will be carried out to unravel the decoupling mechanism.

Discussion

Through the combination of the LT-STM and DFT calculations, we reveal the elementary process of graphene growth on Cu(110) surface via thermal decomposition of CH₄. Low temperature annealing (>480°C) in CH₄ results in the formation of carbon clusters at the initial stage; further high temperature annealing (>550°C) activates the graphene nucleation; prolonged annealing in the absence of CH₄ propels the diffusing and ripening of these graphene island to form continuous graphene films extended over the surface. Low temperature thermal cycling induced decoupling of graphene from Cu(110) has also been demonstrated. Our systematic investigations identify the fundamental carbidic building blocks by STM measurement, and further elucidate their atomic structures through DFT calculations. Our work could lay the foundation for providing rational design rules for synthesis of large area single crystalline graphene films.

Methods

Growth of graphene on Cu(110). Graphene was grown on a single crystal Cu(110) via thermal decomposition of CH₄. Prior to the deposition of CH₄, Cu(110) substrate was cleaned by a few cycles of Ar⁺ ion bombardment and subsequent annealing at 530°C. The CH₄ gas was introduced into the growth chamber through a leak valve, and the pressure was monitored by a cold cathode gauge. A typical growth procedure

is as follows: the Cu(110) substrate was exposed to CH₄ at a pressure of 2×10^{-5} mbar for 20 min; annealing the sample at 480°C in CH₄ at a pressure of 2×10^{-5} mbar resulted in the formation of carbon clusters; further annealing the sample in the absence of CH₄ at 550°C initiated the graphene nucleation; prolonged annealing without CH₄ at higher temperature up to 720°C propelled the ripening of graphene islands.

Characterization of graphene in UHV LT-STM. The LT-STM experiments were carried out in a custom-built multichamber ultra-high-vacuum (UHV) system with base pressure better than 1.0×10^{-10} mbar, housing an omicron LT-STM interfaced to a Nanonis controller. All STM imaging were performed at 77 K using constant current mode with an electrochemically etched tungsten tip. All the bias voltage was applied to the tip⁴⁴.

Structural models of clusters on Cu (110) surface. Stability of C_nH_x ($0 \sim 4$) or C₂H_x ($0 \sim 6$) clusters on Cu (110) surface were studied using DFT calculations. A 5-layer slab with a 20 Å vacuum layer was used as the substrate. The bottom layer was fixed to a Nanonis controller. All STM imaging were performed at 77 K using constant current mode with an electrochemically etched tungsten tip. All the bias voltage was applied to the tip⁴⁴.

Calculation details. All the calculations were performed using DFT implemented in the Vienna Ab Initio Simulation Package (VASP) within the generalized gradient approximation^{55,56} plus DFT-D2 von der Waals (vdW) correction⁵⁷. The exchange-correlation functional of Perdew-Burke-Ernzerhof⁵⁸ and the projector-augmented wave⁵⁹ methods were used. The plane-wave basis cutoff energy was set to 500 eV. The criteria of convergence for energy and force were set to 10^{-5} eV and 0.02 eV/Å. For the (3×4) and (2×2) models, $(7 \times 7 \times 1)$ and $(10 \times 14 \times 1)$ k-point grids were used, respectively. STM images were simulated using the Tersoff and Hamann approximation⁴⁷. The lattice parameter of bulk Cu was optimized to be 3.564 Å⁶⁰.

- Novoselov, K. S. *et al.* Electric field effect in atomically thin carbon films. *Science* **306**, 666–669 (2004).
- Geim, A. K. & Novoselov, K. S. The rise of graphene. *Nat. Mater.* **6**, 183–191 (2007).
- Geim, A. K. Graphene: Status and prospects. *Science* **324**, 1530–1534 (2009).
- Lee, C., Wei, X., Kysar, J. W. & Hone, J. Measurement of the elastic properties and intrinsic strength of monolayer graphene. *Science* **321**, 385–388 (2008).
- Dan, Y., Lu, Y., Kybert, N. J., Luo, Z. & Johnson, A. T. C. Intrinsic response of graphene vapor sensors. *Nano Lett.* **9**, 1472–1475 (2009).
- Stoller, M. D., Park, S., Zhu, Y., An, J. & Ruoff, R. S. Graphene-based ultracapacitors. *Nano Lett.* **8**, 3498–3502 (2008).
- Stankovich, S. *et al.* Graphene-based composite materials. *Nature* **442**, 282–286 (2006).
- Sutter, P. Epitaxial graphene: How silicon leaves the scene. *Nat. Mater.* **8**, 171–172 (2009).
- Park, S. & Ruoff, R. S. Chemical methods for the production of graphenes. *Nat. Nanotechnol.* **4**, 217–224 (2009).
- Stankovich, S. *et al.* Synthesis of graphene-based nanosheets via chemical reduction of exfoliated graphite oxide. *Carbon* **45**, 1558–1565 (2007).
- Li, D., Müller, M. B., Gilje, S., Kaner, R. B. & Wallace, G. G. Processable aqueous dispersions of graphene nanosheets. *Nat. Nanotechnol.* **3**, 101–105 (2008).
- Wang, H. & Hu, Y. H. Effect of oxygen content on structures of graphite oxides. *Ind. Eng. Chem. Res.* **50**, 6132–6137 (2011).
- Hernandez, Y. *et al.* High-yield production of graphene by liquid-phase exfoliation of graphite. *Nat. Nanotechnol.* **3**, 563–568 (2008).
- Loginova, E., Bartelt, N. C., Feibelman, P. J. & McCarty, K. F. Factors influencing graphene growth on metal surfaces. *New J. Phys.* **11**, 063046 (2009).
- Wang, B., Ma, X., Caffio, M., Schaub, R. & Li, W.-X. Size-selective carbon nanoclusters as precursors to the growth of epitaxial graphene. *Nano Lett.* **11**, 424–430 (2011).
- Lu, J., Yeo, P. S. E., Gan, C. K., Wu, P. & Loh, K. P. Transforming C₆₀ molecules into graphene quantum dots. *Nat. Nanotechnol.* **6**, 247–252 (2011).
- Coraux, J. *et al.* Growth of graphene on Ir(111). *New J. Phys.* **11**, 023006 (2009).
- Zhang, B. *et al.* Low-temperature chemical vapor deposition growth of graphene from toluene on electropolished copper foils. *ACS Nano* **6**, 2471–2476 (2012).
- Yu, Q. *et al.* Control and characterization of individual grains and grain boundaries in graphene grown by chemical vapour deposition. *Nat. Mater.* **10**, 443–449 (2011).
- Li, X. *et al.* Large-area graphene single crystals grown by low-pressure chemical vapor deposition of methane on copper. *J. Am. Chem. Soc.* **133**, 2816–2819 (2011).
- Bae, S. *et al.* Roll-to-roll production of 30-inch graphene films for transparent electrodes. *Nat. Nanotechnol.* **5**, 574–578 (2010).
- Bhavaripudi, S., Jia, X., Dresselhaus, M. S. & Kong, J. Role of kinetic factors in chemical vapor deposition synthesis of uniform large area graphene using copper catalyst. *Nano Lett.* **10**, 4128–4133 (2010).
- Kim, K. S. *et al.* Large-scale pattern growth of graphene films for stretchable transparent electrodes. *Nature* **457**, 706–710 (2009).
- Gao, L. *et al.* Repeated growth and bubbling transfer of graphene with millimetre-size single-crystal grains using platinum. *Nat. Commun.* **3**, 699 (2012).
- Huang, P. Y. *et al.* Grains and grain boundaries in single-layer graphene atomic patchwork quilts. *Nature* **469**, 389–392 (2011).
- Wood, J. D., Schmucker, S. W., Lyons, A. S., Pop, E. & Lyding, J. W. Effects of polycrystalline Cu substrate on graphene growth by chemical vapor deposition. *Nano Lett.* **11**, 4547–4554 (2011).
- Lin, Y.-M. *et al.* 100-GHz Transistors from wafer-scale epitaxial graphene. *Science* **327**, 662 (2010).
- Rutter, G. M. *et al.* Scattering and interference in epitaxial graphene. *Science* **317**, 219–222 (2007).
- Marchini, S., Günther, S. & Wintterlin, J. Scanning tunneling microscopy of graphene on Ru(0001). *Phys. Rev. B* **76**, 075429 (2007).
- Sutter, P. W., Flege, J.-I. & Sutter, E. A. Epitaxial graphene on ruthenium. *Nat. Mater.* **7**, 406–411 (2008).
- Li, X., Cai, W., Colombo, L. & Ruoff, R. S. Evolution of graphene growth on Ni and Cu by carbon isotope labeling. *Nano Lett.* **9**, 4268–4272 (2009).
- Vázquez de Parga, A. L. *et al.* Periodically rippled graphene: growth and spatially resolved electronic structure. *Phys. Rev. Lett.* **100**, 056807 (2008).
- Luo, Z., Kim, S., Kawamoto, N., Rappe, A. M. & Johnson, A. T. C. Growth mechanism of hexagonal-shape graphene flakes with zigzag edges. *ACS Nano* **5**, 9154–9160 (2011).
- Shu, H., Chen, X., Tao, X. & Ding, F. Edge structural stability and kinetics of graphene chemical vapor deposition growth. *ACS Nano* **6**, 3243–3250 (2012).
- Gao, J., Yuan, Q., Hu, H., Zhao, J. & Ding, F. Formation of carbon clusters in the initial stage of chemical vapor deposition graphene growth on Ni(111) surface. *J. Phys. Chem. C* **115**, 17695–17703 (2011).
- Mehdipour, H. & Ostrikov, K. Kinetics of low-pressure, low-temperature graphene growth: toward single-layer, single-crystalline structure. *ACS Nano* **6**, 10276–10286 (2012).
- Chen, H., Zhu, W. & Zhang, Z. Contrasting behavior of carbon nucleation in the initial stages of graphene epitaxial growth on stepped metal surfaces. *Phys. Rev. Lett.* **104**, 186101 (2010).
- Zhang, W., Wu, P., Li, Z. & Yang, J. First-principles thermodynamics of graphene growth on Cu surfaces. *J. Phys. Chem. C* **115**, 17782–17787 (2011).
- Riikonen, S., Krasheninnikov, A. V., Halonen, L. & Nieminen, R. M. The Role of Stable and mobile carbon adspecies in copper-promoted graphene Growth. *J. Phys. Chem. C* **116**, 5802–5809 (2012).
- Gao, J., Yip, J., Zhao, J., Yakobson, B. I. & Ding, F. Graphene nucleation on transition metal surface: structure transformation and role of the metal step edge. *J. Am. Chem. Soc.* **133**, 5009–5015 (2011).
- Zangwill, A. & Vvedensky, D. D. Novel growth mechanism of epitaxial graphene on metals. *Nano Lett.* **11**, 2092–2095 (2012).
- Yuan, Q. *et al.* Magic carbon clusters in the chemical vapor deposition growth of graphene. *J. Am. Chem. Soc.* **134**, 2970–2975 (2011).
- Van Wesep, R. G., Chen, H., Zhu, W. & Zhang, Z. Communication: Stable carbon nanoarches in the initial stages of epitaxial growth of graphene on Cu(111). *J. Chem. Phys.* **134**, 171105–171104 (2011).
- Niu, T., Zhou, M., Zhang, J., Feng, Y. & Chen, W. Growth intermediates for CVD graphene on Cu(111): carbon clusters and defective graphene. *J. Am. Chem. Soc.* **135**, 8409–8414 (2013).
- Mi, X., Meunier, V., Koratkar, N. & Shi, Y. Facet-insensitive graphene growth on copper. *Phys. Rev. B* **85**, 155436 (2012).
- Lewis, B. & Anderson, J. C. Nucleation and growth of thin films. Academic Press, London (1978).
- Tersoff, J. & Hamann, D. R. Theory of the scanning tunneling microscope. *Phys. Rev. B* **31**, 805–813 (1985).
- Wei, Y. *et al.* The nature of strength enhancement and weakening by pentagon–heptagon defects in graphene. *Nat. Mater.* **11**, 759–763 (2012).
- Riedl, C., Coletti, C., Iwasaki, T., Zakharov, A. A. & Starke, U. Quasi-free-standing epitaxial graphene on SiC obtained by hydrogen intercalation. *Phys. Rev. Lett.* **103**, 246804 (2009).
- Virojanadara, C., Watcharinyanon, S., Zakharov, A. A. & Johansson, L. I. Epitaxial graphene on 6H-SiC and Li intercalation. *Phys. Rev. B* **82**, 205402 (2010).
- Oida, S. *et al.* Decoupling graphene from SiC(0001) via oxidation. *Phys. Rev. B* **82**, 041411 (2010).
- Wong, S. L. *et al.* Quasi-free-standing epitaxial graphene on SiC(0001) by fluorine intercalation from a molecular source. *ACS Nano* **5**, 7662–7668 (2011).
- Locatelli, A. *et al.* Temperature-driven reversible rippling and bonding of a graphene superlattice. *ACS Nano* **7**, 6955–6963 (2013).
- Chen, W. *et al.* Two-dimensional pentacene:3,4,9,10-perylenetetracarboxylic dianhydride supramolecular chiral networks on Ag(111). *J. Am. Chem. Soc.* **130**, 12285–12289 (2008).
- Kresse, G. & Furthmüller, J. Efficiency of ab-initio total energy calculations for metals and semiconductors using a plane-wave basis set. *Comput. Mater. Sci.* **6**, 15–50 (1996).
- Kresse, G. & Furthmüller, J. Efficient iterative schemes for ab initio total-energy calculations using a plane-wave basis set. *Phys. Rev. B* **54**, 11169–11186 (1996).
- Grimme, S. Semiempirical GGA-type density functional constructed with a long-range dispersion correction. *J. Comput. Chem.* **27**, 1787–1799 (2006).
- Perdew, J. P., Burke, K. & Ernzerhof, M. Generalized gradient approximation made simple. *Phys. Rev. Lett.* **77**, 3865–3868 (1996).
- Kresse, G. & Joubert, D. From ultrasoft pseudopotentials to the projector augmented-wave method. *Phys. Rev. B* **59**, 1758–1775 (1999).

60. Simon, N. J., Drexler, E. S. & Reed, R. P. Properties of copper and copper alloys at cryogenic temperatures. *International Copper Association, Ltd.*, New York and National Institute of Standards and Technology, Gaithersburg (1992).

Acknowledgments

Authors acknowledge the support from Singapore MOE grants R143-000-505-112, R143-000-530-112, R143-000-542-112, R143-000-559-112, NUS YIA grant R143-000-452-101, and NSFC funds 21173202 and 21222304.

Author contributions

W.C. conceived and designed the experiments; J.L.Z. and T.C.N. performed the experiments; Z.Z.W., S.N.W. and Z.Y.L. performed theoretical calculations; W.C. and J.L.Z. wrote the manuscript. All authors contributed to writing and revising the manuscript.

Additional information

Supplementary information accompanies this paper at <http://www.nature.com/scientificreports>

Competing financial interests: The authors declare no competing financial interests.

How to cite this article: Zhang, J.L. *et al.* Elementary Process for CVD Graphene on Cu(110): Size-selective Carbon Clusters. *Sci. Rep.* **4**, 4431; DOI:10.1038/srep04431 (2014).

This work is licensed under a Creative Commons Attribution 3.0 Unported license. To view a copy of this license, visit <http://creativecommons.org/licenses/by/3.0>