OPEN

Rich stoichiometries of stable Ca-Bi system: Structure prediction and superconductivity

Xu Dong & Changzeng Fan

SUBJECT AREAS:

SUPERCONDUCTING
PROPERTIES AND
MATERIALS

ELECTRONIC STRUCTURE

Received
16 October 2014Accepted
19 February 2015Published
20 March 2015Correspondence and
requests for materials
should be addressed to
C.F. (chzfan@ysu.edu.
cn)

State Key Laboratory of Metastable Materials Science and Technology, Yanshan University, Qinhuangdao 066004, China.

Using a variable-composition *ab initio* evolutionary algorithm implemented in the USPEX code, we have performed a systematic search for stable compounds in the Ca-Bi system at different pressures. In addition to the well-known *tI12*-Ca₂Bi and *oS12*-CaBi₂, a few more structures were found by our calculations, among which phase transitions were also predicted in Ca₂Bi (*tI12* → *oI12* → *hP6*), Ca₃Bi₂ (*hP5* → *mC20* → *aP5*) and CaBi (*tI2* → *tI8*), as well as a new phase (Ca₃Bi) with a *cF4* structure. All the newly predicted structures can be both dynamically and thermodynamically stable with increasing pressure. The superconductive properties of *cF4*-CaBi₃, *tI2*-CaBi and *cF4*-Ca₃Bi were studied and the superconducting critical temperature T_c can be as high as 5.16, 2.27 and 5.25 K, respectively. Different superconductivity behaviors with pressure increasing have been observed by further investigations.

Superconductivity has been deeply studied and developed very quickly since its discovery in 1911, but its origin remains enigmatic. The copper oxide family is of enduring interest for initiating energetic activities of high-temperature superconductivity^{1,2} and has been applied in a variety of fields. The discovery of the iron-based superconductors³, which is unconventional, has attracted great attention and aroused extensive research with the intention of finding new superconductors. Iron-based superconductors have been extended to various material groups, such as the so called 1111^{3,4}, 122⁵, 111⁶, 11⁷ compounds, etc. Moreover, it is observed that compounds in which iron is completely substituted by other 3d, 4d, or 5d transition metals^{8,9}, exhibit superconductivity. Since a large variety of phosphide, arsenide and antimonide superconductors have been found, attention is now focusing on bismuthides and related pnictide systems. So bismuth has been a part of various superconducting compounds, such as NiBi₃¹⁰, Bi₄O₄S₃^{11,12}, CsBi₄Te₆¹³ and LaO_{1-x}F_xBiS₂¹⁴. Recently, Sturza *et al.* reported a new complex alkaline earth intermetallic compound superconductor Ca₁₁Bi_{10-x}¹⁵ with $T_c \sim 2.2$ K, which stimulates our interests to find new superconductors in the Ca-Bi system.

A large number of BCS superconductors have been theoretically proposed^{16–18} as the development of computational crystal structure prediction tools^{19,20} and methods. In this paper, we perform a systematic search for thermodynamically stable calcium bismuth at ambient and high pressure by using the variable-composition *ab initio* evolutionary algorithm^{21–23} and density functional theory (DFT). Here we predict several new structures at different pressures that were never reported, and discuss their structures, electronic structures and superconductivity properties of the selected structures.

Results

Crystal structure and structural properties of calcium bismuthides. Some reported experimental crystal structures in the Ca-Bi system are summarized by H. Kim *et al.*²⁴ and other similar Sr-Bi compounds have also been studied by first-principles calculations²⁵. In this paper, we use the variable-composition evolutionary algorithm, which is very effective, to predict stable compositions and their structures. We have performed structure searches with up to 16 atoms in the unit cell at different pressures for the Ca-Bi system of all possible compositions.

Fig. 1 shows the enthalpies of formation of the predicted structures. At ambient pressure, it can be clearly seen that there are three stable structures on the convex hull, i.e., *tI12*-Ca₂Bi (Fig. 2a), *hP5*-Ca₃Bi₂ (Fig. 2b) and *oS12*-CaBi₂ (Fig. 2c). The previously reported *oP32*-Ca₅Bi₃²⁶ and *tI84*-Ca₁₁Bi₁₀²⁷, although not found by our prediction possibly limited by the computational resources, are also on the convex hull, suggesting that they are thermo-

Figure 1 | Enthalpy differences (top) and convex hull for the Ca-Bi system (bottom). Calculated enthalpy differences as a function of pressure relative to *tI12* of Ca_2Bi (top left), *hP5* of Ca_3Bi_2 (top middle) and *tI2* of CaBi (top right) and convex hull (bottom) for the Ca-Bi system at ambient pressure (red) and 30 GPa (black).

dynamically stable. However, these two structures lie above the convex hull curve at 30 GPa, which implies that they will become metastable phases under high-pressure conditions.

The Ca_3Bi_2 phase has been reported in the literature without structural information. Our prediction indicates that it has a hexagonal structure of the La_2O_3 type, and belongs to the space group of $P\bar{3}m$ (164), with Pearson symbol *hP5*. Our calculations reveal that Ca_3Bi_2 undergoes a series phase transitions, *i.e.*, from *hP5* to *mC20* (space group $C2/m$, 12) at 4 GPa and *mC20* to *aP5* (space group $R\bar{3}m$ 166) at about 59 GPa. The calculated phonon dispersion of *hP5*- Ca_3Bi_2 indicates that the phonon mode along the *A-H* direction is imaginary at 0 GPa, and it will be dynamically stable at high pressure, which can be seen in Fig. 3 (further study shows that the imaginary phonon mode along the *A-H* direction will disappear at above 0.5 ~ 0.6 GPa, which can be seen in Figure S1). We also observed a high-pressure phase transition in Ca_2Bi , which is from *tI12*²⁸ (space group $I4/mmm$, 139) to *oI12* (space group $Cmmm$, 65) at 14 GPa and from *oI12* to *hP6* (space group $P6_3/mmc$, 194) at 33 GPa. For CaBi_2 , we predict an *oS12* structure (space group $Cmcm$, 63) with lattice constants $a = 4.782 \text{ \AA}$, $b = 17.160 \text{ \AA}$, $c = 4.598 \text{ \AA}$ at 0 GPa compared with the previously reported $a = 4.701 \text{ \AA}$, $b = 17.053 \text{ \AA}$, $c = 4.613 \text{ \AA}$ ²⁹, which lies on the convex hull at ambient and high pressure, and is both dynamically and thermodynamically stable.

The previously reported Ca-Bi phase diagrams³⁰ mentioned two phases, CaBi_3 and CaBi , without structural information. This work suggests a cubic *cF4* structure for CaBi_3 (space group $Pm\bar{3}m$, 221) and a tetragonal *tI2* structure for CaBi (space group $P4/mmm$, 123), which are thermodynamically unstable at ambient pressure and can be stable at high pressure. The *cF4*- CaBi_3 is very close to the convex hull curve but lies a little above it. In addition, another tetragonal *tI8* structure of CaBi (space group $I4_1/amd$, 141) was also predicted, which is proved to be thermodynamically more stable at above 45 GPa. Besides, our research also predicted a new phase of Ca-Bi system, *i.e.*, *cF4*- Ca_3Bi , the space group of which is the same with *cF4*- CaBi_3 , and can be thermodynamically stable at high pressure. In *cF4*- Ca_3Bi , the Ca and Bi atoms occupy Wyckoff 3c and 1a positions, respectively. However, the situation of the occupancy is just the

opposite in *cF4*- CaBi_3 , which can be seen in Figs. 2d and 2e. The structural parameters for the predicted structures are listed in Table 1.

Electronic structures. We calculated the band structures and density of states of all the predicted structures. All the calcium bismuthides are metallic except for the *hP5*- Ca_3Bi_2 structure, which is semiconductive at 0 GPa, with a narrow band gap of 0.42 eV and becomes metallic at around 20 GPa. Through the calculations we can conclude that the ratio of Ca and Bi will affect their contributions to the DOS at the Fermi level (E_F). For example, if a calcium rich structure of $\text{Ca}_x\text{Bi}_{1-x}$, *i.e.*, $x > 0.5$, the density of states at E_F comes mainly from the calcium atoms, in particular Ca *d* states and bismuth *p* orbital contributes most to bismuth states. On the contrary, the density of states at E_F comes mainly from the bismuth atoms in a bismuth rich structure, in particular Bi *p* states, and calcium *d* orbital contributes most to calcium states at the Fermi level. Fig. 4 shows the band structures and DOS of the *cF4*- Ca_3Bi and *cF4*- CaBi_3 structures. The density of states at E_F of these two structures is 0.32 and 0.20 states/eV, respectively. A careful examination of the band structures show multiple steep bands crossing the Fermi level as well as flat bands, which is considered to be a necessary condition for superconductivity to occur³¹. As bismuth based materials may have strong spin-orbital coupling (SOC) effect^{32,33}, the electronic structures of *cF4*- Ca_3Bi and *cF4*- CaBi_3 have been calculated by including the SOC effect and compared with those without SOC effect, as shown in Figure S2 and S3.

Superconductivity properties. The superconductivity of the selected structures can be conveniently studied by EPC calculation. The calculated Eliashberg spectral function and the electron-phonon coupling strength λ are shown in Fig. 5 for *cF4*- Ca_3Bi and *cF4*- CaBi_3 at 60 and 30 GPa, respectively. The superconducting critical temperature can be estimated from the Allen-Dynes modified McMillan equation³⁴

$$T_C = \frac{\omega_{\log}}{1.2} \exp \left\{ \frac{-1.04(1 + \lambda)}{\lambda - \mu^* (1 + 0.62\lambda)} \right\}, \quad (1)$$

where the electron-phonon coupling constant is calculated as

Figure 2 | Crystal structures for (a): *tI12*-Ca₂Bi, (b): *hP5*-Ca₃Bi₂, (c): *oS12*-CaBi₂, (d): *cF4*-Ca₃Bi and (e): *cF4*-CaBi₃.

Figure 3 | Phonon dispersion curves for the *hP5*-Ca₃Bi₂ at 0 GPa and 5 GPa.

Table 1 | Crystal parameters for the predicted structures

Compound	Space group Pearson symbol	Lattice constants (Å)	Atom position (Wyckoff position)
Ca ₂ Bi	I4 ₁ /mmm #12	a = 4.851 Å, c = 17.005 Å	Ca (4d) [0, 0.5, 0]; (4e) [0, 0, 0.3255]
			Bi (4e) [0, 0, 0.1358]
	Cmmm #12	a = 5.136 Å, b = 16.496 Å, c = 4.572 Å	Ca (4i) [0.5, 0.8224, 0]; (2d) [0, 0, 0] (2d) [0.5, 0, 0.5]
			Bi (3d) [0.5, 0.5, 0]
	P6 ₃ /mmc #16	a = 5.618 Å, c = 6.98 Å	Ca (2d) [0.3333, 0.6667, 0.75]; (2a) [0, 0, 0.5]
Ca ₃ Bi ₂	P3̄m #15	a = 5.304 Å, c = 7.212 Å	Bi (2d) [0.6667, 0.3333, 0.75]
			Ca (2d) [0.3333, 0.6667, 0.6702]; (1a) [0, 0, 0]
			Bi (4e) [0.3333, 0.6667, 0.213]
	C2/m #12	a = 17.239 Å, b = 4.894 Å, c = 8.112 Å, β = 101.329°	Ca (2d) [0.5, 0.5, 0]; (4i) [0.6926, 0.5, 0.8385]; (4i) [0.3506, 0, 0.5584]; (2c) [0.5, 0.5, 0.5]
	R3̄m #15	a = 5.3150 Å, c = 19.8239 Å	Bi (4i) [0.3096, 0.5, 0.7598]; (4i) [0.4428, 0, 0.2374]
CaBi ₂			Ca (3d) [0, 0, 0]; (6d) [0, 0, 0.78103]
			Bi (6d) [0, 0, 0.40366]
	Cmcm #12	a = 4.782 Å, b = 17.160 Å, c = 4.598 Å	Ca (4d) [0, 0.9021, 0.25]
			Bi (4d) [0.5, 0.7578, 0.25]; (4d) [0.5, 0.9339, 0.75]
	Pm3̄m #20	a = 5.108 Å	Ca (3d) [0.5, 0.5, 0]
Ca ₃ Bi			Bi (1d) [0, 0, 0]
	P4 ₁ /mmm #12	a = 3.786 Å, c = 4.355 Å	Ca (1d) [0, 0, 0]
			Bi (1d) [0.5, 0.5, 0.5]
	I4 ₁ /amd #8	a = 4.628 Å, c = 11.656 Å	Ca (4d) [0.5, 0.25, 0.625]
			Bi (4b) [0, 0.25, 0.375]
CaBi ₃	Pm3̄m #20	a = 4.998 Å	Ca (1d) [0, 0, 0] Bi (3d) [0, 0.5, 0.5]

$$\lambda = 2 \int_0^{\infty} \frac{\alpha^2 F(\omega)}{\omega} d\omega, \quad (2)$$

the logarithmic frequency average is

$$\omega_{\log} = \exp\left(\frac{2}{\lambda} \int_0^{\infty} \log \omega \frac{\alpha^2 F(\omega)}{\omega} d\omega\right), \quad (3)$$

and a typical value of the Coulomb pseudopotential $\mu^* = 0.10$ is used.

Our calculations suggest that *cF4*-Ca₃Bi shows no superconductivity behavior below 25 GPa. Its superconducting transition temperature rises as the pressure increases. The dynamic instability of *cF4*-Ca₃Bi is confirmed as the phonon spectrum displays imaginary frequencies above 60 GPa, at which we predict that *cF4*-Ca₃Bi will be superconductor with a T_c of 5.25 K, total λ of 0.96 and $\omega_{\log}$ of 146.1 cm⁻¹. 72% of the total λ results from modes below 140 cm⁻¹, which are mainly displacements of bismuth atoms. The decomposition of the phonon density of states into contributions from the atoms (Fig. 5a) shows that the calcium atoms (below 140 cm⁻¹) has a slight contribution to the electron-phonon coupling in this compound. On the contrary, *cF4*-CaBi₃ can be a superconductor at 0 GPa with a T_c of 5.16 K, total λ of 1.23 and $\omega_{\log}$ of 56.2 cm⁻¹, which will accordingly turn into 0.61 K, 0.41 and 127.8 cm⁻¹ at 30 GPa. 84% of the total λ results from modes below 125 cm⁻¹, which are mainly displacements of bismuth atoms, the same with *cF4*-Ca₃Bi. A further study of the phonon density of states of *cF4*-CaBi₃ indicates that the calcium atoms (below 180 cm⁻¹) has a negligible contribution to the electron-phonon coupling in this compound (Fig. 5b). The calculated λ , $\omega_{\log}$ and T_c at different pressure for *cF4*-Ca₃Bi and *cF4*-CaBi₃ are listed in Table 2 and Table 3,

Figure 4 | Band structure and partial density of states for *cF4*-Ca₃Bi and *cF4*-CaBi₃.

Figure 5 | Total and projected phonon density of states (PHDOS) and Eliashberg function $\alpha^2F(\omega)$ for $cF4\text{-Ca}_3\text{Bi}$ at 60 GPa and $cF4\text{-CaBi}_3$ at 30 GPa and the corresponding integrated electron-phonon coupling constant $\lambda(\omega)$.

respectively. The $tI2\text{-CaBi}$ exhibits different superconductivity behavior through a brief study of our calculation as the T_c will reach a maximum value of 2.27 K at around 10 GPa, as is shown in Fig. 6. A further analysis of the result shows that bismuth phonon mode is thought to play a large role in the superconductivity of $cF4\text{-Ca}_3\text{Bi}$ and $cF4\text{-CaBi}_3$.

Discussion

In summary, by using the variable-composition evolutionary algorithm, we performed a systematic search for all possible compositions in the Ca-Bi system at different pressures. Except the previously reported $oP32\text{-Ca}_5\text{Bi}_3$ and $tI84\text{-Ca}_{11}\text{Bi}_{10}$, we found 10 novel structures either totally unreported or only mentioned but no detail information. In addition, we predicted a series of phase transitions in Ca_2Bi , Ca_3Bi_2 and CaBi , and also one stoichiometry (Ca_3Bi) with a $cF4$ structure. All the newly predicted structures can be both dynamically and thermodynamically stable as the pressure increases. Based on conventional BCS theory, $cF4\text{-CaBi}_3$ is superconductor with a T_c

of 5.16 K at 0 GPa and will drop with pressure increases. While $cF4\text{-Ca}_3\text{Bi}$ shows no superconductive behavior below 25 GPa and the T_c value is enhanced with increasing pressure and reaches 5.25 K at 60 GPa. Compared to the above, $tI2\text{-CaBi}$ is much different as the T_c will reach a maximum value of 2.27 K at around 10 GPa. The newly predicted structures of calcium bismuthides and superconductivity behavior of $cF4\text{-CaBi}_3$, $tI2\text{-CaBi}$ and $cF4\text{-Ca}_3\text{Bi}$ would stimulate further experimental and theoretical studies on alkaline earth metal bismuthides and pnictide.

Methods

We used the evolutionary algorithm USPEX to search for low-enthalpy stable structures as implemented in the USPEX code^{35,36}, which has been widely used to predict stable high-pressure crystal structures without requiring any experimental information.

The underlying structural relaxations and electronic structure calculations of Ca-Bi over a wide range of the pressure presented here were performed within the density functional theory (DFT), using the all electron projector augmented wave (PAW) method³⁷ as implemented in the Vienna *ab initio* simulation package (VASP)³⁸. The $3s^23p^64s^2$ and $5d^{10}6s^26p^3$ electrons are treated as valence electrons for Ca and Bi atoms,

Table 2 | Calculated logarithmic average phonon frequency ($\omega_{\log}$), EPC (λ) and critical temperature T_c for $cF4\text{-Ca}_3\text{Bi}$ at selected pressures

Pressure(GPa)	λ	$\omega_{\log}(\text{cm}^{-1})$	$T_c(\text{K})$
30	0.24	236.4	0.01
40	0.33	228.3	0.24
50	0.47	197.9	1.08
60	0.96	146.1	5.25

Table 3 | Calculated logarithmic average phonon frequency ($\omega_{\log}$), EPC (λ) and critical temperature T_c for $cF4\text{-CaBi}_3$ at selected pressures

Pressure(GPa)	λ	$\omega_{\log}(\text{cm}^{-1})$	$T_c(\text{K})$
0	1.23	56.2	5.16
10	0.65	88.0	2.55
20	0.49	110.9	1.24
30	0.41	127.8	0.61

Figure 6 | The calculated logarithmic average phonon frequency ($\omega_{\log}$), EPC (λ) and critical temperature T_c for *tI2*-CaBi as a function of pressure.

respectively. The exchange-correlation energy was treated within the generalized gradient approximation (GGA), using the functional of Perdew-Burke-Ernzerhof⁶⁹ for both Ca and Bi. A plane-wave cutoff energy of 500 eV and dense Monkhorst-Pack *k*-point meshes⁴⁰ with the reciprocal space resolution of $2\pi \times 0.03 \text{ \AA}^{-1}$ were used for all structures to ensure that the enthalpy calculations are converged to better than 1 meV/atom.

The calculation of electron-phonon coupling (EPC) parameter λ are performed using the pseudopotential plane-wave method within the density functional perturbation theory (DFPT) as implemented in the Quantum Espresso package⁴¹ using Martins Troullier-type norm-conserving pseudopotential with cutoff energies of 80 and 360 Ry for the wave functions and the charge density, respectively. In order to interpolate the interatomic force constant matrix for the phonon dispersions, $4 \times 4 \times 4$, $4 \times 4 \times 4$ and $4 \times 4 \times 3$ *q*-meshes in the first Brillouin zone (BZ) were used for interpolation for *cF4*-CaBi₃, *cF4*-Ca₃Bi and *tI2*-CaBi, respectively. The denser $24 \times 24 \times 24$, $24 \times 24 \times 24$ and $24 \times 24 \times 18$ grids were sufficient to ensure the convergence needed for the EPC calculations for the three calcium bismuthides, respectively.

To ensure the dynamical stability of the newly predicted structures, the phonon dispersion curves were calculated throughout the Brillouin zone using the finite-displacement approach as implemented in the PHONOPY code⁴².

- Orenstein, J. Advances in the Physics of High-Temperature Superconductivity. *Science* **288**, 468–474 (2000).
- Schilling, A., Cantoni, M., Guo, J. D. & Ott, H. R. Superconductivity above 130 K in the Hg–Ba–Ca–Cu–O system. *Nature* **363**, 56–58 (1993).
- Kamihara, Y., Watanabe, T., Hirano, M. & Hosono, H. Iron-based layered superconductor La[O_{1-x}F_x]FeAs (*x* = 0.05–0.12) with $T_c = 26$ K. *J. Am. Chem. Soc.* **130**, 3296–3297 (2008).
- Han, F. *et al.* SrFeAsF as a parent compound for iron pnictide superconductors. *Phys. Rev. B* **78**, 180503 (2008).
- Christianson, A. D. *et al.* Unconventional superconductivity in Ba_{0.6}K_{0.4}Fe₂As₂ from inelastic neutron scattering. *Nature* **456**, 930–932 (2008).
- Tapp, J. H. *et al.* LiFeAs: An intrinsic FeAs-based superconductor with $T_c = 18$ K. *Phys. Rev. B* **78**, 060505 (2008).
- Hsu, F. C. *et al.* Superconductivity in the PbO-type structure α -FeSe. *Proc. Natl. Acad. Sci.* **105**, 14262–14264 (2008).
- Bauer, E. D., Ronning, F., Scott, B. L. & Thompson, J. D. Superconductivity in SrNi₂As₂ single crystals. *Phys. Rev. B* **78**, 172504 (2008).
- Imai, M. *et al.* Superconductivity in 122 antimonide SrPtSb₂. *Supercond. Sci. Technol.* **26**, 075001 (2013).
- Kumar, J. *et al.* Physical property and electronic structure characterization of bulk superconducting Bi₃Ni. *Supercond. Sci. Technol.* **24**, 085002 (2011).
- Mizuguchi, Y. *et al.* BiS₂-based layered superconductor Bi₄O₄S₃. *Phys. Rev. B* **86**, 220510 (2012).
- Singh, S. K. *et al.* Bulk superconductivity in bismuth oxysulfide Bi₄O₄S₃. *J. Am. Chem. Soc.* **134**, 16504–16507 (2012).
- Malliakas, C. D., Chung, D. Y., Claus, H. & Kanatzidis, M. G. Superconductivity in the narrow-gap semiconductor CsBi₄Te₆. *J. Am. Chem. Soc.* **135**, 14540–14543 (2013).
- Lee, J. *et al.* Crystal structure, lattice vibrations, and superconductivity of LaO_{1-x}F_xBiS₂. *Phys. Rev. B* **87**, 205134 (2013).
- Sturza, M. *et al.* Superconductivity in the intermetallic pnictide compound Ca₁₁Bi_{10-x}. *Phys. Rev. B* **89**, 054512 (2014).
- Zhou, X.-F. *et al.* Superconducting high-pressure phase of platinum hydride from first principles. *Phys. Rev. B* **84**, 054543 (2011).

- Li, Y. L. *et al.* Formation of Nanofoam carbon and re-emergence of Superconductivity in compressed CaC₆. *Sci. Rep.* **3**, 3331 (2013).
- Raza, Z., Errea, I., Oganov, A. R. & Saitta, A. M. Novel superconducting skutterudite-type phosphorus nitride at high pressure from first-principles calculations. *Sci. Rep.* **4**, 5889 (2014).
- Hautier, G., Jain, A. & Ong, S. P. From the computer to the laboratory: materials discovery and design using first-principles calculations. *J. Mater. Sci.* **47**, 7317–7340 (2012).
- Curtarolo, S. *et al.* The high-throughput highway to computational materials design. *Nat. Mater.* **12**, 191–201 (2013).
- Lyakhov, A. O., Oganov, A. R. & Valle, M. How to predict very large and complex crystal structures. *Comput. Phys. Commun.* **181**, 1623–1632 (2010).
- Oganov, A. R. *et al.* Evolutionary Crystal Structure Prediction as a Method for the Discovery of Minerals and Materials. *Rev. Mineral. Geochem.* **71**, 271–298 (2010).
- Oganov, A. R., Lyakhov, A. O. & Valle, M. How evolutionary crystal structure prediction works-and why. *Acc. Chem. Res.* **44**, 227–237 (2011).
- Kim, H. *et al.* Thermodynamic properties of calcium–bismuth alloys determined by emf measurements. *Electrochim. Acta* **60**, 154–162 (2012).
- Wang, Y. *et al.* Thermodynamic assessment of the Sr–In and Sr–Bi systems supported by first-principles calculations. *Calphad* **45**, 49–54 (2014).
- Martinez-Ripoll, M., Haase, A. & Brauer, G. The crystal structure of Ca₅Bi₃. *Acta Crystallogr. B* **30**, 2004–2006 (1974).
- Deller, K. & Eisenmann, B. On the Intermetallic Compounds Ca₁₁Sb₁₀ and Ca₁₁Bi₁₀. *Z. Naturforsch* **31b**, 29–34 (1976).
- Eisenmann, B. & Schafer, H. The Crystal Structures of Ca₂Sb and Ca₂Bi. *Z. Naturforsch* **29**, 13–15 (1974).
- Merlo, F. & Fornasini, M. L. Crystal structure of some phases and alloying behaviour in alkaline earths, europium and ytterbium pnictides. *Mater. Res. Bull.* **29**, 149–154 (1994).
- Notin, M. *et al.* The thermodynamic properties of calcium intermetallic compounds. *J. Alloys Compd.* **220**, 62–75 (1995).
- Deng, S., Köhler, J. & Simon, A. A Chemist Approach to Superconductivity. *J. Supercond.* **15**, 635–638 (2002).
- Wang, Z. *et al.* Dirac semimetal and topological phase transitions in A₃Bi (A = Na, K, Rb). *Phys. Rev. B* **85**, 195320 (2012).
- Liu, Z. K. *et al.* Discovery of a Three-Dimensional Topological Dirac Semimetal, Na₃Bi. *Science* **343**, 864–867 (2014).
- Allen, P. B. Transition temperature of strong-coupled superconductors reanalyzed. *Phys. Rev. B* **12**, 905–922 (1975).
- Oganov, A. R. & Glass, C. W. Crystal structure prediction using ab initio evolutionary techniques: principles and applications. *J. Chem. Phys.* **124**, 244704 (2006).
- Lyakhov, A. O., Oganov, A. R., Stokes, H. T. & Zhu, Q. New developments in evolutionary structure prediction algorithm USPEX. *Comput. Phys. Commun.* **184**, 1172–1182 (2013).
- Blöchl, P. E. Projector augmented-wave method. *Phys. Rev. B* **50**, 17953–17979 (1994).
- Kresse, G. Efficient iterative schemes for ab initio total-energy calculations using a plane-wave basis set. *Phys. Rev. B* **54**, 11169–11186 (1996).
- Perdew, J. P., Burke, K. & Ernzerhof, M. Generalized Gradient Approximation Made Simple. *Phys. Rev. Lett.* **77**, 3865–3868 (1996).
- Monkhorst, H. J. & Pack, J. D. Special points for Brillouin-zone integrations. *Phys. Rev. B* **13**, 5188–5192 (1976).
- Giannozzi, P. *et al.* QUANTUM ESPRESSO: a modular and open-source software project for quantum simulations of materials. *J. Phys.: Condens. Matter* **21**, 395502 (2009).
- Togo, A., Oba, F. & Tanaka, I. First-principles calculations of the ferroelastic transition between rutile-type and CaCl₂-type SiO₂ at high pressures. *Phys. Rev. B* **78**, 134106 (2008).

Acknowledgments

This work was supported by the Research Foundation of Education Bureau of Hebei Province (ZD20131039), the Natural Science Foundation of Hebei Province (E2014203243) and the NSFC (Grant No. 51121061), which is gratefully acknowledged.

Author contributions

C.Z.F. conceived the idea. X.D. performed the *ab initio* evolutionary simulations and the superconductivity properties calculations. C.Z.F. and X.D. wrote the manuscript.

Additional information

Supplementary information accompanies this paper at <http://www.nature.com/scientificreports>

Competing financial interests: The authors declare no competing financial interests.

How to cite this article: Dong, X. & Fan, C. Rich stoichiometries of stable Ca–Bi system: Structure prediction and superconductivity. *Sci. Rep.* **5**, 9326; DOI:10.1038/srep09326 (2015).

This work is licensed under a Creative Commons Attribution 4.0 International License. The images or other third party material in this article are included in the article's Creative Commons license, unless indicated otherwise in the credit line; if

the material is not included under the Creative Commons license, users will need to obtain permission from the license holder in order to reproduce the material. To view a copy of this license, visit <http://creativecommons.org/licenses/by/4.0/>