SCIENTIFIC REPORTS

OPEN

Signatures of new *d*-wave vortex physics in overdoped $\text{Ti}_2\text{Ba}_2\text{CuO}_{6+x}$ revealed by TF- $\mu^+\text{SR}$

Jess H. Brewer¹, Scott L. Stubbs¹, Ruixing Liang^{1,2}, D. A. Bonn^{1,2}, W. N. Hardy^{1,2}, J. E. Sonier^{2,3}, W. Andrew MacFarlane⁴ & Darren C. Peets^{1,5}

Received: 11 December 2014

Accepted: 19 August 2015

Published: 16 September 2015

The spontaneous expulsion of applied magnetic field, the Meissner effect, is a defining feature of superconductors; in Type-II superconductors above the lower critical field, this screening takes the form of a lattice of magnetic flux vortices. Using implanted spin-1/2 positive muons, one can measure the vortex lattice field distribution through the spin precession and deduce key parameters of the superconducting ground state, and thereby fundamental properties of the superconducting pairing. Muon spin rotation/relaxation (μSR) experiments have indeed revealed much interesting physics in the underdoped cuprates, where superconductivity is closely related to, or coexistent with, disordered or fluctuating magnetic and charge excitations. Such complications should be absent in overdoped cuprates, which are believed to exhibit conventional Fermi liquid behaviour. These first transverse field (TF)- $\mu^+\text{SR}$ experiments on heavily-overdoped single crystals reveal a superfluid density exhibiting a clear inflection point near $0.5T_c$, with a striking doping-independent scaling. This reflects hitherto unrecognized physics intrinsic to *d*-wave vortices, evidently generic to the cuprates, and may offer fundamentally new insights into their still-mysterious superconductivity.

Charge doping of the CuO_2 planes tunes the occurrence of superconductivity in the high-temperature hole-doped cuprate superconductors between the limits of an undoped insulating antiferromagnet and a possible conventional Fermi liquid at high dopings. It is appealing to try to understand how the unconventional superconductivity evolves out of these more conventional electronic ground states. However, hole doping is typically effected chemically, in the best case *via* the composition of a distinct, well-separated subunit of the layered crystal structure, to leave the planes themselves little altered structurally and the dopant site well-shielded when a hole is promoted to the planes. One such example is oxygen doping in the CuO chain layer of $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ (YBCO). Unfortunately, compositional tuning is limited by (thermodynamic) phase stability and can seldom be used to traverse the entire superconducting phase diagram in a single system. In this context overdoped cuprates, those nearer the apparent Fermi liquid regime, are rare and, moreover, relatively few have highly-ordered CuO_2 planes. For example, doping by cation substitution in $\text{La}_x\text{Sr}_{2-x}\text{CuO}_4$ (LSCO) introduces substantial disorder directly adjacent to the CuO_2 planes¹. In contrast, $\text{Ti}_2\text{Ba}_2\text{CuO}_{6+x}$ (Ti-2201) offers tunability throughout the overdoped regime with highly-ordered, isolated, and flat CuO_2 planes, doped *via* dilute interstitial oxygen in the distant TlO layers², although Cu/Ti substitution in this layer^{3,4} may contribute an offset in doping. The overdoping also appears to eliminate a predicted electron Fermi surface (FS) pocket at the Γ point, leaving only a single, large, FS sheet⁵.

¹Department of Physics and Astronomy, The University of British Columbia, Vancouver, BC, Canada V6T 1Z1.

²Canadian Institute for Advanced Research, Toronto, Ontario, Canada M5G 1Z8. ³Department of Physics, Simon Fraser University, Burnaby, BC, Canada V5A 1S6. ⁴Department of Chemistry, The University of British Columbia, Vancouver, BC, Canada V6T 1Z1. ⁵Center for Correlated Electron Systems, Institute for Basic Science, Seoul National University, Seoul 151-747, Korea. Correspondence and requests for materials should be addressed to J.H.B. (email: jess@triumf.ca) or D.C.P. (email: dpeets@snu.ac.kr)

Figure 1. Example of μ^+ SR data. (a) Complex TF- μ^+ SR time spectrum (red circles: real part; blue triangles: imaginary part) in a rotating reference frame (RRF) at 0.1 T and 10 K on the $T_c \approx 56$ K Tl-2201 mosaic, including time-domain best fit, the residual errors of which are shown in (b) for the first 4 μ s where the statistics are highest. (c) Fourier transforms at several temperatures. The relatively sharp peak at 13.55 MHz arises from muons stopping outside the sample.

Pure $d_{x^2-y^2}$ -wave symmetry of the superconducting order in Tl-2201 has been conclusively established by observation of half-integer flux quanta at crystal boundaries in films⁶; line nodes are evident in microwave^{7–9} and thermal transport¹⁰ measurements; and the admixture of another pairing symmetry is unlikely because it would require spontaneous breaking of the crystal symmetry. However, some μ SR measurements have suggested an additional transition at low temperatures within the vortex state^{11–13}, which has been interpreted in terms of a multiple-component order parameter. Here, we extend μ SR studies of the vortex state of the cuprates deep into the overdoped regime with the first transverse-field muon spin rotation (TF- μ^+ SR) results on single-crystalline Tl-2201, in the form of high-quality single crystal mosaics at a range of dopings. Our measurements were performed at low magnetic fields, in a doping regime free from competing charge density wave order^{14,15} and are thus sensitive to the intrinsic structure of d -wave vortices. We show that the unusual temperature dependence is real, and generic to the cuprates, but also demonstrate that it is a signature of d -wave vortex physics rather than a multicomponent order parameter.

Results

Figure 1 shows an example of the data and time domain fit at 10 K on a $T_c = 56$ K mosaic. Fits on all mosaics at all fields and temperatures converged very well, and fully reproduce the data. Fourier transforms corresponding to the field distribution are also shown for a selection of temperatures; the additional peak just above the cusp is attributed to muons stopping outside the sample and precessing about the applied field, and is accounted for in the fits. The high-field (high-frequency) cutoff in the lineshape is indistinct, precluding a quantitative analysis of the in-plane coherence length ξ_{ab} , but the in-plane magnetic penetration depth λ_{ab} , which controls the linewidth, may be reliably extracted. Varying the fit parameters indicated that the absolute $1/\lambda_{ab}^2$ is accurate to within $\sim 10\%$, while its temperature dependence is robust; after a few global fits with different choices of $\kappa_{ab} \equiv \lambda_{ab}/\xi_{ab}$ we chose a fixed value, $\kappa_{ab} = 100$, for all remaining fits.

One strength of TF- μ^+ SR in a Type-II superconductor is its ability to determine the *absolute* λ and its inverse square, which is proportional to the density of superconducting carriers¹⁶. Circumstances are not yet as good for Tl₂Ba₂CuO_{6+x} as for high-quality YBCO; in particular, only small improvements of global χ^2 minimization distinguish the broadening due to vortex lattice disorder, σ_b , which should scale with $\lambda^{-2}(T)$, from T -independent broadening due to nuclear magnetic dipoles and crystal defects, σ_0 . The amplitude A_b of the background signal due to muons stopping outside the sample is also known only from the best fit; like σ_0 , it can be subtly coupled to λ^{-2} . These uncertainties do not alter the temperature dependence, and have been incorporated into the quoted $\sim 10\%$ uncertainty in $1/\lambda_{ab}^2$.

Figure 2. (a) Temperature dependence of fitted λ_{ab}^{-2} at $H = 0.1$ T for all Tl-2201 mosaics; A and B denote two different mosaics with the same T_c . Absolute microwave data (curve) at zero field on a $T_c = 25$ K crystal at 2.497 GHz⁹, included for comparison, follow a qualitatively different form. Curves are provided for two mosaics as a guide to the eye. (b) Normalized values $\lambda_{ab}^{-2}(T)/\lambda_{ab}^{-2}(0)$ vs. reduced temperature T/T_c for all Tl-2201 mosaics. All dopings exhibit essentially the same temperature dependence, and differ from the microwave results (solid curve).

T_c (K)	46(1), A	46(1), B	56(1)	60(1)	72(1)	75(1)
$\lambda_{ab}(0)$ (nm)	187(2)	165(2)	166(1)	175(1)	182(2)	153(2)

Table 1. Zero-temperature in-plane magnetic penetration depths in 0.1 T for overdoped Tl-2201 mosaics having various T_c s, from a linear extrapolation of $\lambda_{ab}^{-2}(T)$ at low temperatures, with estimated uncertainties in parentheses. The variations in $\lambda_{ab}(0)$ are most likely dominated by the degree of order in the samples, rather than any systematic doping dependence, as discussed in the text. Uncertainties in T_c represent primarily the variation in T_c among the crystals comprising the mosaic.

Figure 2 shows the vortex-state $1/\lambda_{ab}^2(T)$, which is proportional to the superconducting carrier density, for the six mosaics measured, and Table 1 reports the zero-temperature penetration depth $\lambda_{ab}(0)$ from linear extrapolations of $\lambda_{ab}^{-2}(T)$. A highly unusual T -dependence, common to all dopings, is immediately apparent. The extent of this similarity is more striking when $\lambda_{ab}^{-2}(T)$ is normalized to its extrapolated $T = 0$ value and plotted against reduced temperature T/T_c —the *relative* temperature dependence is *identical*. The most intriguing feature, exhibited in all six mosaics, is upward curvature between $\frac{1}{3}T_c$ and an inflection point around $0.5T_c$. This unusual temperature dependence is robust and evident in any measure of the linewidth, but is absent in zero-field (Meissner state) microwave surface resistance at higher and lower dopings^{8,9}, the former included for comparison. The intrinsic T -dependence of the

superconducting carrier density (or $1/\lambda_{ab}^2$) in a single-gap *s*- or *d*-wave superconductor exhibits downward curvature over the entire temperature range 0 – T_c .

Discussion

μ SR reports of the cuprates' temperature-dependent in-plane penetration depth typically exhibit the shape associated with a pure *d*-wave order parameter^{17,18}. However, this has not been the case in all data. Upward curvature in the μ SR penetration depth can be recognized in relatively disordered overdoped LSCO¹¹; at high dopings in cleaner YBa₂Cu₃O_{7- δ} ¹⁹, in lightly underdoped YBa₂Cu₄O₈¹²; and in optimally and overdoped Bi₂Sr₂CaCu₂O_{8+ δ} ¹³. This unusual temperature dependence has appeared most clearly near and above optimal doping^{18,19}, with some limited evidence that it strengthens on overdoping¹³. It is most evident at relatively low applied fields^{20,21}.

With no phase transition expected at the fields and temperatures in question, no such feature unambiguously visible in most published data or any microwave penetration depth studies, and based on a small number of data points in many of these cases, it has not been widely accepted as a real effect. Its now-confirmed appearance in a variety of systems, and its particularly conspicuous appearance in Tl-2201, implies that it is real and generic, at least to high doping ranges. The contrast with zero-field microwave data argues against the few interpretations floated thus far, instead pointing toward an origin in an unexpected property of the cuprates' vortex state. We first briefly dispense with some alternative explanations before returning to vortex physics.

First, multiband superconductors, those with more than one band crossing the Fermi level, can exhibit unconventional temperature dependence in the vortex state²²; a two-component order parameter, *e.g.* *d* + *s*, with separate order parameters on distinct Fermi surface sheets, has been advanced to explain the LSCO¹¹ and YBa₂Cu₄O₈¹² results. However, Tl-2201 has only one FS sheet, and the pure *d*-wave symmetry and dissimilar microwave penetration depth at both lower and higher dopings^{7,9} exclude such an origin. Second, the remarkable scaling seen in Fig. 2 argues against an electronic phase transition within the superconducting dome, such as an extension of the pseudogap crossover temperature T^* . Third, dilute paramagnetic impurities would yield an additional broadening scaling with H/T , contrary to the observed T dependence. Some type of magnetically frozen state might account for the observed temperature dependence (since μ^+ SR is a local probe, macroscopic phase separation would not affect the superconducting component's lineshape). However, one would not expect the onset of a competing magnetic phase to track T_c with doping²³. Furthermore, higher fields should enhance any competing magnetic order²⁴, particularly in the vortex cores²⁵, but in YBCO they instead suppress the exotic upward curvature in the temperature dependence of the linewidth^{11,20}. Proximity-induced chain superconductivity has been advanced as an explanation for the inflection point in YBCO¹⁹, but this cannot explain its appearance in chain-free Tl-2201.

Having excluded several alternative explanations, we return to physics of the vortex phase, which would be absent in the Meissner-phase microwave experiments and previous work on Tl-2201 powder²⁶, and may thus offer a natural explanation. First, the resistive upper critical field of Tl-2201 (actually the irreversibility field^{27,28}) exhibits unusual upward curvature²⁹ and stays very close to $H_{c2}(T)$, far from the required temperature regime at the low fields relevant here. A dimensionality crossover within the frozen vortex state, as in the much more anisotropic Bi₂Sr₂CaCu₂O₈^{13,30}, would produce a symmetric lineshape, and the reduced field inhomogeneity would narrow the linewidth at high temperatures, in contrast to our results. Trapping of vortices by preferred pinning sites at low temperature has been advanced to explain the inflection in YBCO²⁰, but the linewidth changes in Tl-2201 would require *very* significant disorder and change the lineshape significantly. This is not seen in the FFT spectra; moreover, allowing the temperature-independent σ_0 broadening to vary produced no systematic trend with temperature. To further exclude vortex disorder, it will be essential to quantify it independently using, for instance, small-angle neutron scattering or scanning probe techniques.

Another relevant feature of the vortex state is the symmetry of the vortex lattice itself. An unusual square vortex lattice, as found in optimally and overdoped LSCO^{31,32} and in YBCO³³, produces a broader but qualitatively similar field distribution with a more pronounced low-field tail. However, the vortex lattice in fully-oxygenated YBCO gradually transforms from triangular to square as the field increases from 4 to 11 T, while strong upward curvature in the second moment of the TF- μ^+ SR lineshape is strongest at much lower fields ~ 0.1 T³⁴ and is completely suppressed by 4 T¹⁸, excluding this interpretation, at least for YBCO. The μ SR data for the $T_c = 56$ K Tl-2201 mosaic were fit to a simple square vortex lattice model as a trial, but no crossover, in the form of a systematic improvement in the quality of fit, was evident.

We are thus drawn to the conclusion that the upward curvature must arise from some fundamental property intrinsic to the *d*-wave vortices themselves. In this scenario, the difference between the zero-field microwave measurements and these vortex-state μ SR results arises because the measurements probe different phases. In microwave measurements, only the surface contributes, while the bulk is shielded. In μ SR, however, vortices also contribute, and these can overlap and interact in certain field and temperature regimes.

The scaling with T_c and absence in underdoped samples point to an explanation in terms of the electronic structure expected for a vortex in a *d*-wave superconductor. Theoretical calculations^{35,36} show that such vortex cores shrink with increasing magnetic field due to an enhanced transfer of quasiparticles

Figure 3. Fitted values of λ_{ab}^{-2} vs. T for the earlier (A) and later (B) $T_c = 46$ K mosaics. Inset: same data in normalized form.

between neighbouring vortices. This effect has been observed in YBCO by μSR ^{18,19,37}, with the core size rapidly shrinking and saturating at fields above $H \sim 4$ T. At low fields where the vortices are well separated, the quasiparticle transfer is minimal and the vortices are expected to behave essentially as if they were isolated. A vortex in a d -wave superconductor is fourfold symmetric at low temperatures, with extended low-energy quasiparticle states along the 45° (nodal) directions in the CuO_2 plane. With increasing thermal population of the higher energy states, the vortex core size grows, and calculations show that above $\sim 0.5T_c$ the fourfold-symmetric magnetic field profile about the vortex core becomes nearly cylindrical³⁸.

As previously stressed²⁵, λ_{ab} as measured by μSR may be regarded as the in-plane magnetic penetration depth only in the $T \rightarrow 0$ and $H \rightarrow 0$ limit, but is otherwise an effective length scale partially influenced by changes to the field profile outside the vortex core by extended quasiparticle states. Consequently, below $\sim 0.5T_c$ and at low fields the temperature dependence of λ_{ab} is expected to be influenced by the evolving quasiparticle states that extend far beyond the vortex core. At higher temperatures, where the fourfold symmetry of the vortex is essentially gone, the behavior of λ_{ab} should closely resemble that of the magnetic penetration depth, unless the vortex lattice melts. Since the vortex core radius is directly proportional to the gap magnitude³⁹, which in turn is proportional to T_c in overdoped cuprates, the scaling with T_c is naturally explained.

The inflection point near $0.5T_c$ being less prominent or absent in underdoped cuprates is likely due to the stabilization of competing charge-density-wave (CDW) order localized in the vicinity of the vortex cores. STM measurements on optimally- and slightly overdoped $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$ ^{40,41} and nuclear magnetic resonance (NMR) measurements on underdoped YBCO^{24,42} show static CDW order in the vortex core region, where superconductivity is suppressed. While this induced static CDW order is observed only at low temperatures in optimally and slightly overdoped samples, in underdoped YBCO with $p \sim 0.12$, NMR shows that static CDW order occurs over much of the temperature range below T_c . The occurrence of static CDW order in the vortex core region constitutes a significant modification of the electronic structure of the d -wave vortex⁴³, and consequently the loss of the inflection point in the temperature dependence of λ_{ab} is not surprising. The CDW competes with superconductivity^{14,15}, so it will preferentially inhabit—and likely gap out—the regions of momentum space in the nodal direction at the Fermi surface to maximally avoid competition between the two orders. As a result, the extended quasiparticle core states along the nodal directions will become bound. This should lead to isotropic s -wave-like vortex behaviour throughout much of the underdoped side of the phase diagram, while the behaviour seen in the overdoped regime reflects the intrinsic physics of d -wave vortices without such complications. Supplementary Fig. S2 online shows that the fit parameters, based on an s -wave model, fail at the lowest temperatures (beginning well below the inflection point). The s -wave model's inability to reproduce the observed field distribution provides evidence of its failure to adequately describe the vortex phase, particularly at low temperatures.

Finally, our use of mosaics with similar T_c s has important implications for techniques relying on μSR for values of the zero-temperature penetration depth. Mosaics grown and annealed under very similar conditions, having the same or similar T_c , exhibit quite different absolute penetration depths, as shown in Fig. 3 for $T_c = 46$ K. The *normalized* linewidths $\lambda_{ab}^{-2}(T) / \lambda_{ab}^{-2}(0)$, however, are almost identical. Mosaics with T_c s of 46 K (“A”) and 72 K were prepared several years before the 46 K (“B”) and 75 K mosaics. The crystal growth was still being optimized when the early mosaics were assembled, demonstrating that suppression of T_c by disorder is *not equivalent* to its suppression by carrier overdoping. That the

zero-temperature λ_{ab}^{-2} can apparently increase by $\sim 30\%$ due to increasing crystalline perfection means that the $\lambda_{ab}(0)$ values in Table 1 should *not* be regarded as intrinsic. A variety of other techniques rely upon μ SR to obtain absolute penetration depth values, but our work indicates that in the overdoped regime, the values are only valid for $T, H \rightarrow 0$, and even then are highly susceptible to disorder and must be treated with caution.

The nature of superconductivity in the cuprates remains one of the most important open questions in condensed matter physics, and the overdoped regime proffers the promising prospect of understanding the normal state from which high-temperature superconductivity emerges. However, our μ^+ SR data indicate exotic physics survives to high dopings. A striking universal temperature dependence unambiguously confirms an unusual upturn in the in-plane penetration depth, now seen in at least four distinct material families, establishing that it is new physics generic to the cuprates. Fundamental differences from zero-field microwave measurements of nominally the same quantity⁹ imply it is intrinsic to the *d*-wave vortices themselves. Aside from the substantial impacts of this result on vortex physics and what light this may shed on cuprate superconductivity, there are important ramifications for other techniques. μ SR is uniquely suited to extracting the absolute penetration depth from the vortex phase, and the values thus obtained underpin results of other techniques which can't measure λ in absolute terms or at all. While the μ SR temperature evolution should be robust¹⁶, the absolute values are model-dependent. Our data indicate that a more complex model is required when *d*-wave vortices are present, which will necessitate revisiting some previous results. First, however, the details and origin of the exotic temperature dependence must be conclusively confirmed. Sensitive scanning probe microscopies may provide insights into the current and quasiparticle distribution in the vortex cores, while confirmation that this is a vortex state phenomenon awaits Meissner-state field distribution measurements, such as low-energy μ SR⁴⁴ or β -NMR⁴⁵. The regimes in which these *d*-wave vortices manifest their unique *d*-wave physics may provide crucial new insight on the cuprates' order parameter and still-mysterious pairing.

Methods

Single crystals of Tl-2201 were grown in gold-sealed alumina crucibles by an encapsulated copper-rich self-flux method as described elsewhere⁴⁶. The oxygen content (which determines hole content and T_c) was set by annealing under controlled oxygen partial pressures and temperatures⁴⁷; two different annealing schemes were employed depending on the desired oxygen content⁴⁶. Crystals were assembled in mosaics on substrates of aluminized mylar or GaAs to minimize the background signal, with the crystallographic *c*-axis perpendicular to the substrate (parallel to the applied field). In this geometry, the applied field is shielded by supercurrents running within the *ab*-plane, thus the in-plane penetration depth λ_{ab} governs the field distribution. The large number of small crystals to be mutually aligned precluded measuring the superconducting transition of every individual crystal, but care was taken to construct each mosaic from a small number of annealing batches, each drawing crystals from only one growth run, and T_c was measured on a selection of crystals sampled from each annealing run. Examples of magnetization data on three mosaics are included in Supplementary Fig. S1 online. Quoted uncertainties in T_c reflect transition widths of individual crystals, as determined by DC magnetization in applied fields of 0.1–0.2 mT, and the expected variation within the mosaic based on the crystals sampled. These fields were used because the lower critical field H_{c1} in this material is quite low.

Spin-polarized positive muons from the M15 muon channel at TRIUMF were injected into the mosaics at an energy of 3–4 MeV in one of several different μ^+ SR spectrometers. While a range of magnetic fields were used, the lowest field for which the rotating reference frame transformation worked reliably was 0.1 T, and this field was used for all data presented here. In muon spin rotation/resonance/relaxation (μ SR)^{16,48}, implanted muons settle into specific preferred crystallographic sites, where their spins precess around the local magnetic field $\vec{B}_{loc}$ with frequency $\omega = \gamma B_{loc}$, where the muon gyromagnetic ratio $\gamma \approx 2\pi \times 135.54$ MHz/T. The precession is detected *via* a decay positron (in the case of μ^+) emitted preferentially along the muon's spin direction. The experimental β^+ decay asymmetry reflects the precession of the ensemble of $\sim 10^7$ randomly implanted muons and thereby the distribution of the local magnetic field. A Fourier transform of the time spectrum, which can be useful for visualizing the field distribution characteristic of the vortex state, shows a low-field cutoff corresponding to the midpoint of a triad of near neighbor vortices, a van Hove cusp from saddle points in the vortex lattice, and a high-field tail and cutoff corresponding to the maximum B_{loc} in the vortex cores. However, fitting is best performed on the original time spectra: statistics decay with the muon lifetime (2.197 μ s), and mixing high- with low-statistics data (as in an FFT) is undesirable, but later times determine the frequency resolution and thereby the reliability of fit parameters. All λ_{ab} values were therefore extracted from fits in the time domain to the lineshape described in Ref. 49 as calculated numerically for a triangular vortex lattice with λ_{ab} and ξ_{ab} as fitted parameters. A test with a square vortex lattice used the same approach.

References

1. H. Eisaki *et al.* Effect of chemical inhomogeneity in bismuth-based copper oxide superconductors. *Phys. Rev. B* **69**, 064512, doi: 10.1103/PhysRevB.69.064512 (2004), arXiv:cond-mat/0312570.
2. J. L. Wagner *et al.* Multiple defects in overdoped $\text{Ti}_2\text{Ba}_2\text{CuO}_{6+x}$: effects on structure and superconductivity. *Physica C* **277**, 170, doi: 10.1016/S0921-4534(97)00062-2 (1997).

3. Y. Shimakawa. Chemical and structural study of tetragonal and orthorhombic $\text{Ti}_2\text{Ba}_2\text{CuO}_6$. *Physica C* **204**, 247 doi: 10.1016/0921-4534(93)91006-H (1993).
4. D. C. Peets *et al.* $\text{Ti}_2\text{Ba}_2\text{CuO}_{6+\delta}$ brings spectroscopic probes deep into the overdoped regime of the high- T_c cuprates. *New J. Phys.* **9**, 28, doi: 10.1088/1367-2630/9/2/028 (2007), arXiv:cond-mat/0609250.
5. M. Pláté *et al.* Fermi surface and quasiparticle excitations of overdoped $\text{Ti}_2\text{Ba}_2\text{CuO}_{6+\delta}$. *Phys. Rev. Lett.* **95**, 077001, doi: 10.1103/PhysRevLett.95.077001 (2005), arXiv:cond-mat/0503117.
6. C. C. Tsuei *et al.* Pure $d_{x^2-y^2}$ order-parameter symmetry in the tetragonal superconductor $\text{Ti}_2\text{Ba}_2\text{CuO}_{6+\delta}$. *Nature* **387**, 481, doi: 10.1038/387481a0 (1997).
7. D. M. Broun *et al.* In-plane microwave conductivity of the single-layer cuprate $\text{Ti}_2\text{Ba}_2\text{CuO}_{6+\delta}$. *Phys. Rev. B* **56**, R11443, doi: 10.1103/PhysRevB.56.R11443 (1997).
8. S. Özcan *et al.* Electrical transport measurements in the superconducting state of $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+x}$ and $\text{Ti}_2\text{Ba}_2\text{CuO}_{6+\delta}$. *Phys. Rev. B* **73**, 064506, doi: 10.1103/PhysRevB.73.064506 (2006), arXiv:cond-mat/0508621.
9. D. Deepwell *et al.* Microwave conductivity and superfluid density in strongly overdoped $\text{Ti}_2\text{Ba}_2\text{CuO}_{6+\delta}$. *Phys. Rev. B* **88**, 214509, doi: 10.1103/PhysRevB.88.214509 (2013), arXiv:1312.6459 [cond-mat.supr-con].
10. D. G. Hawthorn *et al.* Doping dependence of the superconducting gap in $\text{Ti}_2\text{Ba}_2\text{CuO}_{6+\delta}$ from heat transport. *Phys. Rev. B* **75**, 104518, doi: 10.1103/PhysRevB.75.104518 (2007), arXiv:cond-mat/0502273.
11. R. Khasanov *et al.* Experimental evidence for two gaps in the high-temperature $\text{La}_{1.83}\text{Sr}_{0.17}\text{CuO}_4$ superconductor. *Phys. Rev. Lett.* **98**, 057007, doi: 10.1103/PhysRevLett.98.057007 (2007), arXiv:cond-mat/0606175.
12. R. Khasanov *et al.* s -Wave symmetry along the c -axis and $s + d$ in-plane superconductivity in bulk $\text{YBa}_2\text{Cu}_3\text{O}_8$. *J. Supercond. Nov. Magn.* **21**, 81, doi: 10.1007/s10948-007-0302-z (2008), arXiv:0705.0577 [cond-mat.supr-con].
13. T. Blasius *et al.* Evidence for a two-stage melting transition of the vortex matter in $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$ single crystals obtained by muon spin rotation. *Phys. Rev. Lett.* **82**, 4926, doi: 10.1103/PhysRevLett.82.4926 (1999), arXiv:cond-mat/9903232.
14. G. Ghiringhelli *et al.* Long-range incommensurate charge fluctuations in $(\text{Y,Nd})\text{Ba}_2\text{Cu}_3\text{O}_{6+x}$. *Science* **337**, 821, doi: 10.1126/science.1223532 (2012), arXiv:1207.0915 [cond-mat.str-el].
15. J. Chang *et al.* Direct observation of competition between superconductivity and charge density wave order in $\text{YBa}_2\text{Cu}_3\text{O}_{6.67}$. *Nat. Phys.* **8**, 871, doi: 10.1038/NPHYS2456 (2012), arXiv:1206.4333 [cond-mat.supr-con].
16. J. E. Sonier, J. H. Brewer & R. F. Kiefl, μSR studies of the vortex state in type-II superconductors. *Rev. Mod. Phys.* **72**, 769, doi: 10.1103/RevModPhys.72.769 (2000).
17. J. Sonier *et al.* New muon-spin-rotation measurement of the temperature dependence of the magnetic penetration depth in $\text{YBa}_2\text{Cu}_3\text{O}_{6.95}$. *Phys. Rev. Lett.* **72**, 744, doi: 10.1103/PhysRevLett.72.744 (1994).
18. J. E. Sonier *et al.* Field induced reduction of the low-temperature superfluid density in $\text{YBa}_2\text{Cu}_3\text{O}_{6.95}$. *Phys. Rev. Lett.* **83**, 4156, doi: 10.1103/PhysRevLett.83.4156 (1999), arXiv:cond-mat/9906452.
19. J. E. Sonier *et al.* Hole-doping dependence of the magnetic penetration depth and vortex core size in $\text{YBa}_2\text{Cu}_3\text{O}_y$: Evidence for stripe correlations near 1/8 hole doping. *Phys. Rev. B* **76**, 134518, doi: 10.1103/PhysRevB.76.134518 (2007).
20. D. R. Harshman *et al.* Nodeless pairing state in single-crystal $\text{YBa}_2\text{Cu}_3\text{O}_7$. *Phys. Rev. B* **69**, 174505, doi: 10.1103/PhysRevB.69.174505 (2004).
21. M. Amin, M. Franz & I. Affleck. Effective “penetration depth” in the vortex state of a d -wave superconductor. *Phys. Rev. Lett.* **84**, 5864, doi: 10.1103/PhysRevLett.84.5864 (2000), arXiv:cond-mat/9912196.
22. M. Zehetmayer. A review of two-band superconductivity: materials and effects on the thermodynamic and reversible mixed-state properties. *Supercond. Sci. Technol.* **26**, 043001, doi: 10.1088/0953-2048/26/4/043001 (2013), arXiv:1402.3956 [cond-mat.supr-con].
23. C. Niedermayer *et al.* Common phase diagram for antiferromagnetism in $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ and $\text{Y}_{1-x}\text{Ca}_x\text{Ba}_2\text{Cu}_3\text{O}_6$ as seen by muon spin rotation. *Phys. Rev. Lett.* **80**, 3843, doi: 10.1103/PhysRevLett.80.3843 (1998).
24. T. Wu *et al.* Magnetic-field-induced charge-stripe order in the high-temperature superconductor $\text{YBa}_2\text{Cu}_3\text{O}_y$. *Nature* **477**, 191, doi: 10.1038/nature10345 (2011), arXiv:1109.2011 [cond-mat.supr-con].
25. J. E. Sonier. Muon spin rotation studies of electronic excitations and magnetism in the vortex cores of superconductors. *Rep. Prog. Phys.* **70**, 1717, doi: 10.1088/0034-4885/70/11/R01 (2007), arXiv:0802.2942 [cond-mat.supr-con].
26. Y. J. Uemura *et al.* Magnetic-field penetration depth in $\text{Ti}_2\text{Ba}_2\text{CuO}_{6+\delta}$ in the overdoped regime. *Nature* **364**, 605, doi: 10.1038/364605a0 (1993).
27. B. Lundqvist *et al.* Vortex dynamics in a thin film of $\text{Ti}_2\text{Ba}_2\text{CuO}_6$. *J. Low Temp. Phys.* **117**, 1441, doi: 10.1023/A:1022554019336 (1999).
28. D. N. Zheng *et al.* Upper critical field and irreversibility field of over-doped $\text{Ti}_2\text{Ba}_2\text{CuO}_{6+\delta}$ superconductors. *Physica C* **341-348**, 1373, doi: 10.1016/S0921-4534(00)00892-3 (2000).
29. A. P. Mackenzie *et al.* Resistive upper critical field of $\text{Ti}_2\text{Ba}_2\text{CuO}_6$ at low temperatures and high magnetic fields. *Phys. Rev. Lett.* **71**, 1238, doi: 10.1103/PhysRevLett.71.1238 (1993).
30. C. Bernhard *et al.* Anisotropy and dimensional crossover of the vortex state in $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$ crystals. *Phys. Rev. B* **52**, R7050, doi: 10.1103/PhysRevB.52.R7050 (1995).
31. R. Gilardi *et al.* Direct evidence for an intrinsic square vortex lattice in the overdoped high- T_c superconductor $\text{La}_{1.83}\text{Sr}_{0.17}\text{CuO}_{4+\delta}$. *Phys. Rev. Lett.* **88**, 217003, doi: 10.1103/PhysRevLett.88.217003 (2002), arXiv:cond-mat/0204278.
32. J. Chang *et al.* Spin density wave induced disordering of the vortex lattice in superconducting $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$. *Phys. Rev. B* **85**, 134520, doi: 10.1103/PhysRevB.85.134520 (2012), arXiv:1204.2152 [cond-mat.supr-con].
33. J. S. White *et al.* Magnetic-field-induced nonlocal effects on the vortex interactions in twin-free $\text{YBa}_2\text{Cu}_3\text{O}_7$. *Phys. Rev. B* **84**, 104519, doi: 10.1103/PhysRevB.84.104519 (2011), arXiv:1108.2176 [cond-mat.supr-con].
34. R. Khasanov *et al.* Multiple gap symmetries for the order parameter of cuprate superconductors from penetration depth measurements. *Phys. Rev. Lett.* **99**, 237601, doi: 10.1103/PhysRevLett.99.237601 (2007), arXiv:0708.2374 [cond-mat.supr-con].
35. M. Ichioka, A. Hasegawa & K. Machida. Vortex lattice effects on low-energy excitations in d -wave and s -wave superconductors. *Phys. Rev. B* **59**, 184, doi: 10.1103/PhysRevB.59.184 (1999).
36. M. Ichioka, A. Hasegawa, and K. Machida. Field dependence of the vortex structure in d -wave and s -wave superconductors. *Phys. Rev. B* **59**, 8902, doi: 10.1103/PhysRevB.59.8902 (1999), arXiv:cond-mat/9901339.
37. J. E. Sonier *et al.* Expansion of the vortex cores in $\text{YBa}_2\text{Cu}_3\text{O}_{6.95}$ at low magnetic fields. *Phys. Rev. B* **56**, R729, doi: 10.1103/PhysRevB.56.R729 (1999), arXiv:cond-mat/9806064.
38. M. Ichioka, N. Hayashi, N. Enomoto & K. Machida. Vortex structure in d -wave superconductors. *Phys. Rev. B* **53**, 15316, doi: 10.1103/PhysRevB.53.15316 (1996), arXiv:cond-mat/9512001.
39. J. E. Sonier. Investigations of the core structure of magnetic vortices in type-II superconductors using muon spin rotation. *J. Phys.: Condens. Matter* **16**, S4499, doi: 10.1088/0953-8984/16/40/006 (2004), arXiv:cond-mat/0404115.
40. J. E. Hoffman *et al.* A four unit cell periodic pattern of quasi-particle states surrounding vortex cores in $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$. *Science* **295**, 466, doi: 10.1126/science.1066974 (2002), arXiv:cond-mat/0201348.
41. G. Levy *et al.* Fourfold structure of vortex-core states in $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$. *Phys. Rev. Lett.* **95**, 257005, doi: 10.1103/PhysRevLett.95.257005 (2005), arXiv:cond-mat/0503219.

42. T. Wu *et al.* Emergence of charge order from the vortex state of a high-temperature superconductor. *Nat. Commun.* **4**, 2113, doi: 10.1038/ncomms3113 (2013), arXiv:1307.2049 [cond-mat.supr-con].
43. D. F. Agterberg & J. Garaud. Checkerboard order in vortex cores from pair density wave superconductivity. *Phys. Rev. B* **91**, 104512, doi: 10.1103/PhysRevB.91.104512 (2015), arXiv:1412.5101 [cond-mat.supr-con].
44. O. Ofer *et al.* Absolute value and temperature dependence of the magnetic penetration depth in $\text{Ba}(\text{Co}_{0.074}\text{Fe}_{0.926})_2\text{As}_2$. *Phys. Rev. B* **85**, 060506(R), doi: 10.1103/PhysRevB.85.060506 (2012).
45. M. D. Hossain *et al.* Low-field cross spin relaxation of ^7Li in superconducting NbSe_2 . *Phys. Rev. B* **79**, 144518, doi: 10.1103/PhysRevB.79.144518 (2009).
46. D. C. Peets, R. Liang, M. Raudsepp, W. N. Hardy & D. A. Bonn. Encapsulated single crystal growth and annealing of the high-temperature superconductor Tl-2201. *J. Cryst. Growth* **312**, 344, doi: 10.1016/j.jcrysgro.2009.10.042 (2010), arXiv:0910.3457 [cond-mat.supr-con].
47. C. Opagiste *et al.*, Phase diagram of the $\text{Tl}_2\text{Ba}_2\text{CuO}_6$ compounds in the $T, p(\text{O}_2)$ plane. *Physica C* **213**, 17, doi: 10.1016/0921-4534(93)90753-D (1993).
48. J. H. Brewer. Muon spin rotation/relaxation/resonance. in *Encyclopedia of Applied Physics*. Vol. 11 (ed G. L. Trigg) 23–53, doi: 10.1002/3527600434.eap258 (VCH Publishers, 1994).
49. J. E. Sonier *et al.* Shrinking magnetic vortices in V_3Si due to delocalized quasiparticle core states: Confirmation of the microscopic theory for interacting vortices. *Phys. Rev. Lett.* **93**, 017002 doi: 10.1103/PhysRevLett.93.017002 (2004).

Acknowledgements

This work was supported by the Canadian Institute for Advanced Research and the Natural Sciences and Engineering Research Council of Canada. The authors are indebted to Ch. Bernhard, D.M. Broun, M. Franz, and K. Machida for stimulating discussions, D. Deepwell and D.M. Broun for microwave data, M.D. Le and A.C. Shockley for critical reading of the manuscript, and the TRIUMF CMMS staff for their assistance. A portion of this work was supported by IBS-R009-G1.

Author Contributions

This study was conceived, planned and supervised by J.H.B., D.A.B., W.N.H. and R.L. Crystals were grown, annealed and characterized by D.C.P. and R.L., then aligned into mosaics by S.L.S., J.H.B. and R.L. $\mu^+\text{SR}$ experiments were performed by S.L.S. and J.H.B., and J.H.B. was pestered by D.C.P. and W.A.M. into analysing the data. The data were interpreted and the manuscript written by W.A.M., D.C.P., J.H.B. and J.E.S.

Additional Information

Supplementary information accompanies this paper at <http://www.nature.com/srep>

Competing financial interests: The authors declare no competing financial interests.

How to cite this article: Brewer, J. H. *et al.* Signatures of new d -wave vortex physics in overdoped $\text{Tl}_2\text{Ba}_2\text{CuO}_{6+x}$ revealed by TF- $\mu^+\text{SR}$. *Sci. Rep.* **5**, 14156; doi: 10.1038/srep14156 (2015).

This work is licensed under a Creative Commons Attribution 4.0 International License. The images or other third party material in this article are included in the article's Creative Commons license, unless indicated otherwise in the credit line; if the material is not included under the Creative Commons license, users will need to obtain permission from the license holder to reproduce the material. To view a copy of this license, visit <http://creativecommons.org/licenses/by/4.0/>