# SCIENTIFIC REPORTS

Received: 14 June 2015 Accepted: 19 October 2015 Published: 11 February 2016

## **OPEN** Self-induced synthesis of phasejunction TiO<sub>2</sub> with a tailored rutile to anatase ratio below phase transition temperature

Wei-Kang Wang, Jie-Jie Chen, Xing Zhang, Yu-Xi Huang, Wen-Wei Li & Han-Qing Yu

The surface phase junction of nanocrystalline TiO<sub>2</sub> plays an essential role in governing its photocatalytic activity. Thus, facile and simple methods for preparing phase-junction TiO<sub>2</sub> photocatalysts are highly desired. In this work, we show that phase-junction TiO<sub>2</sub> is directly synthesized from Ti foil by using a simple calcination method with hydrothermal solution as the precursor below the phase transition temperature. Moreover, the ratio of rutile to anatase in the TiO<sub>2</sub> samples could be readily tuned by changing the ratio of weight of Ti foil to HCl, which is used as the hydrothermal precursor, as confirmed by the X-ray diffraction analysis. In the photocatalytic reaction by the TiO<sub>2</sub> nanocomposite, a synergistic effect between the two phases within a certain range of the ratio is clearly observed. The results suggest that an appropriate ratio of anatase to rutile in the TiO<sub>2</sub> nanocomposite can create more efficient solidsolid interfaces upon calcination, thereby facilitating interparticle charge transfer in the photocatalysis.

Titania is an intriguing material with wide applications in the fields of water splitting<sup>1</sup>, solar cell<sup>2</sup>, pollutant degradation<sup>3,4</sup>, and lithium-ion batteries<sup>5</sup>. It has been recognized as one of the most promising and suitable photocatalytic materials for energy conversion and environmental remediation due to its abundant availability, nontoxicity, and high chemical stability. In principle, TiO<sub>2</sub> is recognized as an ideal catalyst, but its capability to efficiently separate photoinduced electrons and holes needs substantial improvement<sup>6,7</sup>. Since photoinduced electrons and holes of anatase or rutile phase in TiO<sub>2</sub> are easy to combine, resulting in their poor availability on the surface and corresponding limited photocatalytic activity. It is reported that crystal form might be the most significant factor governing the photocatalytic performance of TiO<sub>2</sub><sup>8</sup>.

Today, it is widely recognized that the mixed phase of TiO<sub>2</sub> is beneficial to reducing the recombination of photogenerated electrons and holes, which results in an enhanced photocatalytic activity. In particular, Degussa P25, a successful commercialized  $TiO_2^9$ , as a typical phase-mixed  $TiO_2$ , has been extensively used in many fields<sup>10,11</sup>. Recently, the phase junctions of mixed-phase TiO<sub>2</sub> have attracted considerable attention because they exhibit better photocatalytic performance than the pure single phase. Due to the difference in their conduction bands, the charge transfer from one phase to another makes it possible to prolong charge lifetime for photocatalytic reactions. Also, the robust separation of photoexcited charge carriers between the two phases and an efficient route to improve photocatalysts have been extensively reported and recognized<sup>12-15</sup>

To date, several methods to synthesize such a phase-junction TiO<sub>2</sub> have been reported. For instance, dose of organic reagents and anions (e.g.,  $NO_3^-$  and  $SO_4^{(2-)}$ ) into the preparation precursor has been used to synthesize mixed-phase TiO<sub>2</sub> nanoparticles<sup>13,16-18</sup>. TiO<sub>2</sub> films containing the phases of anatase and rutile were prepared by advanced plasma electrolytic oxidation of pure titanium foils<sup>14</sup>. Surface anatase/rutile junction was prepared by calcinating the tianium isopropoxide hydrolyzed on commercial rutile particles<sup>15,19</sup>. Also, template methods have been used to achieve the phase transition by adjusting the calcination temperature. Although substantial progress has been made in preparing  $TiO_2$ -based materials with a better photocatalytic activity<sup>20-26</sup>, development of more facile and simple methods for the synthesis of tunable phase-junction TiO<sub>2</sub> is still highly desired.

In this work, a simple but effective calcination method was developed to synthesize phase-junction TiO<sub>2</sub> nanocomposites below the phase transition temperature with a tunable anatase to rutile ratio using the hydrothermal

CAS Key Laboratory of Urban Pollutant Conversion, Department of Chemistry, University of Science & Technology of China, Hefei, 230026, China. Correspondence and requests for materials should be addressed to H.-O.Y. (email: hqyu@ustc.edu.cn)



**Figure 1.** XRD patterns of the phase-junction  $TiO_2$  nanoparticles: (a) the crystallization process with the increasing annealing temperature; (b) obtained with 0.6 g of Ti (W1), 0.4 g of Ti (W2), 0.2 g of Ti (W3), and 0.1 g of Ti (W4).

solution containing Ti foil and hydrochloric acid without any adjustors as the precursor. Photocatalytic activities of the phase-junction  $TiO_2$  nanocomposites were evaluated in the degradation of Rhodamine B (RhB) and the hydrogen production tests. In this way, a novel strategy for self-controllable phase junction engineering of  $TiO_2$  was successfully developed.

#### Results

**Structural and chemical characteristics of the phase-junction TiO<sub>2</sub> nanocomposites.** Figure 1a shows the X-ray diffraction (XRD) patterns of the phase-junction TiO<sub>2</sub> nancomposites prepared by annealing the precursor at different temperatures. The crystallinity of the samples increased with the increasing annealing temperature. Since the photocatalytic activity of TiO<sub>2</sub> is dependent greatly on its crystallinity<sup>27</sup>, the crystallinity of the samples W1-W4 could be ensured by annealing at 500 °C (Fig. 1a). It should be noticed that this temperature did not change the phase of the obtained samples until 600 °C (Supplementary Figure S1a).

The XRD patterns of the samples (Fig. 1b) exhibited similar diffraction peaks, indicating that the obtained samples were the  $TiO_2$  nanocomposites consisting of anatase and rutile nanoparticles. Figure 1 clearly shows the coexistence of two titania polymorphs, i.e., tetragonal rutile (JCPDS No. 21-1276) and tetragonal anatase (JCPDS No. 21-1272). The existence of rutile in the nanocomposites was readily discernible from its (110) diffraction peak located at 2 theta of 27.4° in the XRD pattern, because no overlapping of this peak with any other peaks from anatase occurred. Anatase phase can be also easily identified from its (101) peak located at 2 theta of 25.3°, as this peak doesn't overlap with any other peaks of rutile. This result clearly demonstrates that rutile and anatase coexisted in the samples W1-4. However, the XRD pattern clearly shows that W5 exhibited anatase phase only (Supplementary Figure S1b).

The weight percentage of rutile phase can be calculated from the individual diffraction peaks using a previously reported method<sup>18</sup>. The phase contents of the samples can be estimated from the respective XRD peak intensities with the following equation:

$$f_A = \frac{1}{1 + \frac{1}{K} \frac{I_R}{I_A}} \tag{1}$$

$$K = 0.79, f_{\rm A} > 0.2;$$
  
 $K = 0.68, f_{\rm A} \le 0.2.$ 

where  $f_A$  is the fraction of anatase phase in the powder, and  $I_A$  and  $I_R$  are the X-ray intensities of the anatase (101) and rutile (110) diffraction peak, respectively.

From the XRD patterns of W1-W4 (Fig. 1b), it is estimated that the weight percentages of rutile in the four mixed-phase nanocomposites were 51.8, 46.9, 34.4, and 11.6%, respectively. This result indicates that the rutile to anatase ratio of the nanocomposites could be tuned over a wide range with our synthesis approach. In addition, this ratio was not substantially affected by the hydrothermal time or the Ti precursor preparation temperature (Supplementary Figure S2a,b). Since HCl would react with Ti foil, the lesser dose of Ti foil would result in a higher HCl/Ti ratio<sup>28</sup>. Thus, the HCl/Ti ratio of the Ti solutions increased from W1 to W4, and consequently led to a decrease in rutile content for the obtained samples. Such a result is also consistent with previous reports that rutile formation was suppressed at high HCl/Ti ratios<sup>28</sup>.

The formation mechanism of the phase-junction  $TiO_2$  could be explained from both experimental result and first-principle calculations. The enhanced photocatalytic performance of the anatase/rutile nanocomposites over

 $2\text{Ti}(\text{foil}) + 6\text{HCl} + 6\text{H}_2\text{O} \longrightarrow 2\text{Ti}\text{Cl}_3 \cdot 6\text{H}_2\text{O} + 3\text{H}_2$ (1)



Figure 2. Proposed formation reactions of the phase-junction TiO<sub>2</sub>.



**Figure 3.** (a) Visible Raman spectra and (b) UV Raman spectra of the obtained  $TiO_2$  samples with the excitation lines at 514.5 nm and 325 nm respectively.

pure anatase or rutile nanocrystals might be contributed by the synergistic effects<sup>29</sup> and the built-in electric field at the interface<sup>30-32</sup>. The possible mixed-phase junctions between rutile and anatase included: rutile (101)/anatase (001) with the closest bonding arrangements and parameters<sup>30</sup>; rutile (100)/anatase (100) with a nice fit rearrangement of the top anatase layer to form a rutile-like layer<sup>33</sup>, and rutile (111)/anatase (101) with well-matched lattice fringes<sup>31</sup>. The high-resolution transmission electron microscopy (HRTEM) analysis shows that our TiO<sub>2</sub> samples with a tunable phase ratio might contain all the above possible phase junctions, and also include some junctions from crystal surface with relatively high energies, resulting in a stronger tendency to form interfaces<sup>34,35</sup>.

The formation reactions of the two-phase  $TiO_2$  are proposed as shown in Fig  $2^{36-38}$ . The Raman spectra of the samples in Fig. 3 also reveal similar information about the bulk  $TiO_2$  with XRD patterns<sup>15</sup>. From visible Raman spectra (Fig. 3a), two important phenomena were observed: 1) no obvious broadening of anatase  $E_g$  mode at 143 cm<sup>-1</sup>, suggesting that the crystal sizes of the samples were of similar levels; and 2) two rutile modes at 445 cm<sup>-1</sup> and 612 cm<sup>-1</sup> for W1, W2, and W3, except for W4, indicating that the rutile phase was almost absence in the bulk phase of W4<sup>21</sup>. Additionally, due to its high sensitivity for surface phase detection, UV Raman spectra could offer useful information about the surface phase structure of the samples. As shown in Fig. 3b, both anatase and rutile modes were observed for the samples W1-4, confirming that both anatase and rutile phases were present in the surface region. The above XRD patterns and visible and UV Raman spectra results show that the rutile phase of W4 was mainly located on the surface<sup>39</sup>.

The low-magnification TEM images of the phase-junction  $TiO_2$  samples synthesized from  $Ti^{3+}$  with different concentrations are shown in Fig. 4. All these samples showed similar morphologies, i.e., aggregates of  $TiO_2$  nanoparticles with a size of about 40 nm. This result is consistent with the visible Raman observation that all the samples had a similar crystal size. The TEM images of the particles after Pt deposition are shown in Supplementary Figure S3, indicating that Pt nanoparticles were uniform and had a diameter of approximately 2 nm in all the phase-junction samples. Furthermore, the ICP results show that the Pt content of the samples W1–4 were 0.54, 0.59, 0.53, and 0.55 µg/mL, respectively. Thus, the ICP results and TEM images demonstrate that the amounts of Pt were almost of the same level for all the samples.



Figure 4. Typical TEM images of the phase-junction TiO<sub>2</sub> sample W1 (a), W2 (b), W3 (c), and W4 (d).



Figure 5. HRTEM image of the phase-junction TiO<sub>2</sub> sample (W4).

In order to further demonstrate the existence of phase junction, the synthesized  $TiO_2$  samples were subjected to HRTEM imaging on one single particle. Figure 5 shows the HRTEM image of the sample W4, which shows one particle (Fig. 4). The lattice spacing of 0.32 nm, which corresponds to the (110) plane of the rutile lattice, could be clearly observed. In addition, the lattice spacing of neighbor nanoparticle was 0.35 nm, which corresponds to the (101) plane of the anatase lattice. Thus, the HRTEM observation confirms the existence of anatase-rutile phase junction.

**Photophysical properties of the TiO<sub>2</sub> nanocomposites.** The optical absorption property of semiconductor materials, an important factor to evaluate their photocatalytic activity, is strongly related with their electronic band structures. The UV-vis absorbance spectra of the prepared TiO<sub>2</sub> samples exhibit an absorption edge at about 420 nm (Fig. 6). Compared with W1-W3, W4 exhibited a slight blue shift. This result is reasonable as the less rutile phase decreases the contribution to the photon absorption range<sup>40</sup>. The order is consistent with the decreasing rutile content in the phase-junction TiO<sub>2</sub>. Furthermore, a successive increase in the absorption at  $\lambda < 400$  nm as a function of decreasing rutile content could be observed. The UV light absorbance of the sample



**Figure 6.** (a) UV-vis absorbance spectra of the phase-junction  $TiO_2$  samples and (b) PL spectra of anatase (W5) and phase-junction  $TiO_2$  (W4).



Figure 7. Photocatalytic degradation of RhB in aqueous solution under UV-vis irradiation in the presence of the phase-junction TiO<sub>2</sub> photocatalys, anatase, and rutile, respectively. Here,  $C_0$  and C refer to the RhB concentrations at t = 0 and t = t, respectively.

W4 with a rutile content (11.6%) exhibited the highest UV absorbance. The increased UV absorbance might play an important role in  $h^+/e^-$  separation<sup>41</sup>. Thus, these results can be attributed to a charge separation, in which electrons transfer from rutile to anatase and holes move in the opposite direction<sup>18,40</sup>.

On the other hand, the phase-junction  $TiO_2$  exhibited a much lower photoluminescence (PL) intensity than the anatase  $TiO_2$  in the wavelength range of 300~700 nm (Supplementary Figure S4). Since PL is the emission of fluorescence originating from the recombination of photogenerated electron-hole pairs, the decreased PL intensity of the phase-junction  $TiO_2$  indicates a lower density of recombination centers and consequently higher availability of effective photogenerated carriers for catalytic reactions<sup>42</sup>. It is the reason why the photogenerated electrons and holes of rutile phase  $TiO_2$  are much less than those of the other samples. Such a decreased electron-hole recombination might be ascribed to an accelerated transfer of the photogenerated electrons from rutile phase to anatase phase of the phase-junction  $TiO_2^{43}$ .

**Photocatalytic activity of the TiO**<sub>2</sub> **nanocomposites.** Photocatalytic experiments were conducted to evaluate the photocatalytic activities of the prepared catalysts at various rutile to anatase ratios. Figure 7a shows the photocatalytic degradation of RhB by the TiO<sub>2</sub> nanocomposites. The blank control (without photocatalyst) showed a stable concentration of RhB under UV-vis irradiation. By contrast, the presence of the TiO<sub>2</sub> resulted in a rapid decrease in the RhB concentration. As shown in Fig. 6a, the photocatalytic capabilities of the phase-junction TiO<sub>2</sub> nanocomposites were better than those of the anatase (W5) and rutile (W6). The highest photodegradation efficiency (92.4%) of RhB was achieved on the sample (W4) containing 11.6 wt% rutile after 90-min irradiation. The samples prepared with 51.8, 46.9, and 34.4 wt% rutile showed the total RhB photodegradation efficiency significantly increased with the decreasing amount of rutile to 11.6 wt%. This result indicates that both rutile to anatase ratio

Catalyst	Rutile content (wt %)	k (min <sup>-1</sup> )	$R^2$
W1	51.8	-0.016	0.998
W2	46.9	-0.018	0.996
W3	34.4	-0.022	0.987
W4	11.6	-0.028	0.973
W5	0	-0.012	0.994
W6	100	-0.004	0.998

Table 1. Rate Constants (k) and Linear Correlation Coefficient ( $R^2$ ) of RhB Degradation with Different Rrutile Contents.



Figure 8. Time course of evolved  $H_2$  under UV-vis irradiation in the presence of the phase-junction  $TiO_2$  (W1-4), anatase (W5), and rutile (W6) catalysts, respectively.

and surface phase junction play important roles in governing the recombination of photogenerated  $h^+/e^-$  pairs for the phase-mixed TiO<sub>2</sub><sup>44</sup>, and accordingly influencing its photocatalytic activity. From UV and visible Raman spectra, W4 with more anatase in bulk region and less rutile on surface, exposed more phase-junction on TiO<sub>2</sub> surface, which is beneficial as the photogenerated electrons and holes could be trapped by oxygen and absorbed H<sub>2</sub>O to form active species<sup>15</sup>.

The RhB photodegradation process over time is illustrated in Fig. 7b, which follows the first-order kinetics. Thus, the apparent RhB degradation rate constant (*k*) could be calculated from the slope of the  $\ln(C/C_0)$ versus time fitting line, where *C* represents the RhB concentration. A comparison of the RhB degradation rate constants with different photocatalysts in Table 1 reveals that the fastest RhB degradation was achieved by the phase-junction TiO<sub>2</sub>. In addition,  $k_{W4}$  was larger than  $k_{W1-3}$  and  $k_{W5,6}$  in absolute value, implying that, to some extent, a lower proportion of rutile in the phase-junction TiO<sub>2</sub> is favorable for strengthening its photocatalytic capability.

The photocatalytic  $H_2$  evolution from water/methanol by the phase-junction  $TiO_2$  with different rutile to anatase ratios (deposited with Pt as cocatalyst) was investigated. The  $TiO_2$  samples were calcinated at the same temperature with different concentrations of precursor. Figure 8 shows that the  $H_2$  evolution rate changed with the rutile to anatase ratio and the  $H_2$  evolution rate of the phase-junction  $TiO_2$  was greater than those of the anatase (W5) and rutile (W6). Especially, the overall photocatalytic activity was more directly related to the surface region and the rutile content of the catalyst. The  $H_2$  evolution rate increased with the decreasing rutile content from W1 to W4. Meanwhile, the photocatalytic  $H_2$  evolution from water/methanol by the phase-junction  $TiO_2$  without Pt nanoparticles was investigated. As shown in Supplementary Figure S5, a small amount of  $H_2$  evolution at the beginning was attributed to the photogenerated-electrons that were utilized for forming the oxygen vacancies. After 1 h, the subsequent  $H_2$  evolution rate tended to be stable, exhibiting the similar tendency in the efficiency for the four phase-junction  $TiO_2$  nanoparticles (without Pt). Notably, the change of rutile to anatase ratio did not alter the surface phase and bulk region according to UV and visible Raman spectra. Thus, this result suggests that the surface-phase junction containing main anatase in bulk region and a little rutile on surface is more favorable for  $H_2$  production. For phase-junction  $TiO_2$  with more anatase in bulk region and less rutile, more  $H_2$  would be produced.

### Discussion

The above results demonstrate that the phase-junction  $TiO_2$  is responsible for the high photocatalytic activity. The formation of the surface phase junctions between the anatase and rutile nanoparticles enables effective interparticle electron transfer, which results in more efficient charge separation<sup>15,45,46</sup>. In addition, the two-phase mixed  $TiO_2$  with a small amount of rutile exhibited a higher photocatalytic activity. The photocatalytic activity of the





samples decreased at a higher rutile content because the surface of the anatase  $TiO_2$  might be fully covered by the rutile nanoparticles, which reduced the amount of exposed anatase/rutile phase junction on the  $TiO_2$  surface.

On the basis of the above analysis, the mechanism for the photocatalysis of the phase-junction  $TiO_2$  under UV-vis irradiation is proposed (Fig. 9). The phase- junction samples allow electrons to flow from rutile to anatase, while the holes move in the opposite direction. Thus, the separation of photoexcited  $h^+/e^-$  pairs is promoted<sup>40,47</sup>. The greater photoactivity of the  $TiO_2$  is mainly attributed to a synergistic effect between the two phases.

In the photocatalytic degradation of RhB,  $\cdot$ OH radicals play a predominant role<sup>48</sup>. The excited electrons and transferred electrons on the surface of TiO<sub>2</sub> can be trapped by oxygen to form  $\cdot$ O<sub>2</sub><sup>-</sup>,  $\cdot$ HO<sub>2</sub> and H<sub>2</sub>O<sub>2</sub>, then the  $\cdot$ O<sub>2</sub><sup>-</sup> or electrons can further react with H<sub>2</sub>O<sub>2</sub> to generate  $\cdot$ OH. The photogenerated holes on the surface of TiO<sub>2</sub> react with OH<sup>-</sup> and H<sub>2</sub>O to produce  $\cdot$ OH<sup>48</sup>. The  $\cdot$ OH radical, as the main reactive species, can attack pollutant for degradation<sup>49</sup>. Consequently, not only an efficient consumption of the photo-induced h<sup>+</sup>/e<sup>-</sup> pairs can be achieved, but also the h<sup>+</sup>/e<sup>-</sup> recombination (fluorescence process) can be suppressed (Supplementary Figure S6a). The transfer of the photogenerated carriers (h<sup>+</sup>and e<sup>-</sup>) in the semiconductor photoexcitation pathways for the generation of reactive species is shown in Supplementary Figure S6b.

Likewise, in the photocatalytic  $H_2$  evolution, the excited electrons can be transferred to Pt nanoparticles of the Pt-loaded TiO<sub>2</sub> catalysts. This would strengthen the interaction between Pt and TiO<sub>2</sub> matrix as well as the interfacial electron transfer and  $h^+/e^-$  separation, resulting in more efficient photocatalytic water splitting for  $H_2$  evolution<sup>50</sup>. Therefore, the phase-junction TiO<sub>2</sub> has a higher UV-visible photocatalytic activity for both photocatalor (i.e., dye decomposition) and photoreduction (i.e., water splitting for  $H_2$  evolution). In such a TiO<sub>2</sub> nanocomposite, the rutile to anatase ratio governs the efficiency of interfacial electron transfer and thus its photocatalytic activity.

#### Conclusions

A simple but effective approach is developed to synthesize phase-junction TiO<sub>2</sub> nanocomposites with a tunable ratio of rutile to anatase. In this approach, neither adjustors for tuning the ratio nor temperature adjustment is need to make phase transition. The experimental results indicate that the precusor concentration governs the synthesis of the phase-junction TiO<sub>2</sub> nanocomposites through affecting the rutile content. The rutile content reduces with the decreasing Ti precusor concentration, while the hydrothermal time and temperature have no distinct effect on the rutile to anatase ratio. The photocatalytic activity of the TiO<sub>2</sub> nanocomposites is significantly affected by the rutile to anatase ratio. A synergy between the two phases within a certain ratio range is observed. Compared with the other catalysts, W4 prepared by annealing the hydrothermal solution containing 0.1 g Ti and 40 ml HCl (6 mol/L), which has 11 wt% rutile content, exhibits the most excellent photocatalytic performance, because it reduces the rutile content in bulk region and makes rutile generate surface-phase junction, which promotes the charge separation. An appropriate ratio of rutile to anatase enables the formation of the surface-phase junctions in direct contact to facilitate the electron transfer between the two phases. This work not only offers a strategy to prepare unique nanocrystalline phase-junction TiO<sub>2</sub>, but also deepens our understanding about the properties of the phase-mixed TiO<sub>2</sub> in photocatalysis, photoelectrochemical and photoelectric applications. Furthermore, such a phase-junction semiconductor may stand out as a promising candidate in environment remediation and the photoinduced splitting of water into hydrogen.

#### Methods

**Rutile/anatase composite synthesis.** All chemicals used in this work were of analytical-grade and used without further purification. The hydrothermal solution was prepared using a modified method from Guo *et al*<sup>51</sup>. Briefly, a 0.30 mm thick Ti foil was cleaned with acetone, alcohol and deionized water sequentially. The obtained Ti foils of different weights (0.6, 0.4, 0.2, 0.1, and 0.05 g) were then added into Teflon-lined stainless autoclaves with 50 mL of effective volume, and a mixture of water (20 mL) and concentrated hydrochloric acid (20 mL) was slowly added into each autoclave. Thereafter, the samples were autoclaved at 160 °C for 2 h and then naturally cooled under room temperature to obtain purple solutions without any precipitation. The ionic species in this purple solution is Ti<sup>3+</sup> ion derived from Ti foil, as evidenced by the low temperature electron paramagnetic resonance (EPR) spectra (Supplementary Figure S7). The detailed measurement results of the Ti<sup>3+</sup> concentration (Supplementary Figure S8) are described in Supplementary Information. Corresponding to four different weights of Ti foil, the obtained purple solutions with four different concentrations of Ti<sup>3+</sup> were used in the subsequent synthesis.

Rutile/anatase-mixed  $\text{TiO}_2$  nanocomposites were prepared as follows: the as-prepared purple solution was annealed at different temperatures (300, 350, 400, 450, 500, 600, 700, and 800 °C (denoted as W6)) with a heating rate of 5 °C/min in air. The samples are cooled rapidly after reaching the above temperature.

The as-prepared solutions with different ratios of Ti foil to HCl were annealed at 500 °C for 2 h with a heating rate of 5 °C/min in air, and cooled to room temperature naturally. Thus, the samples with different weights of Ti foils were obtained, which were denoted as W1, W2, W3, W4, and W5 according to their ratios of Ti foil to HCl.

To prepare Pt/phase-junction TiO<sub>2</sub> composites, the cocatalyst Pt (0.1 mg) was photodeposited on the rutile/ anatase TiO<sub>2</sub> catalyst (100 mg) *in situ* with H<sub>2</sub>PtCl<sub>6</sub>·6H<sub>2</sub>O as the precursor. Then, the Pt-loaded TiO<sub>2</sub> samples were cleaned with water, and annealed at 450 °C for 0.5 h with a heating rate of 5 °C/min in air.

Characterization. The low-temperature electron paramagnetic resonance (EPR) spectra of the obtained purple solution were recorded at 150 K to confirm the presence of  $Ti^{3+}$  ions (JES-FA200, JEOL Inc., Japan).  $Ti^{3+}$ concentration was determined with the method of redox titration by TIM865 titration manager (Radiometer Analytical, Villeurbanne, France). The crystal phase of the obtained samples were determined by X-ray diffraction (XRD) analysis using a Rigaku diffractometer (TTR-III, Rigaku Co., Japan), with a Cu K $\alpha$  radiation source  $(\lambda = 1.541841 \text{ Å})$ . The XRD scan speed was 8°/min, and the accelerating voltage and current were 40 kV and 200 mA, respectively. Visible and UV Raman spectra were recorded at ambient temperature using a Raman spectrometer (LabRamHR, HORIBA Scientific Inc., Japan) with an excitation wavelength of 514.5 nm generated by an Ar<sup>+</sup> laser or 325 nm generated by a He-Cd laser. The Pt element in the phase-junction TiO<sub>2</sub> samples after loading the Pt nanoparticles was analyzed by using inductively coupled plasma atomic emission spectrometry (ICP-AES) (Optima 7300 DV, PerkinElmer Co., USA). Morphology and structure of the samples were characterized by a transmission electron microscopy (TEM) (JEM2100, JEOL Inc., Japan). The high-resolution transmission electron microscopy (HRTEM) images were taken on an HRTEM (JEM-2010, JEOL Inc., Japan) at an acceleration voltage of 200 kV. The optical absorbance spectra of the samples were obtained using a UV-vis spectrophotometer (SOLID3700, Shimadzu Co., Japan). The PL measurement of the samples was carried out with a photoluminescence spectrophotometer (5301, Shimadzu Co., Japan).

**Photocatalytic activity evaluation.** Photoactivities of the phase-junction  $TiO_2$  samples for RhB degradation and  $H_2$  evolution under UV-vis illumination were measured. Photocatalytic degradation of RhB was tested in a 50-mL beaker with a cold bath. In each beaker, 20 mg of the  $TiO_2$  catalyst was dispersed in a 30-mL RhB solution. Absorption spectrum of RhB was recorded using a UV-vis spectrophotometer (UV-2401PC, Shimadzu Co., Japan). Photocatalytic  $H_2$  evolution from methanol/water solution with the Pt-loaded  $TiO_2$  was investigated using a quartz reaction cell connected to a closed gas circulation and evacuation system. The light source was a 350 W (15 A) Xenon lamp (CHF-XM-350W, Beijing Trusttech. Co., China). The 0.1 wt % Pt-loaded catalyst (50 mg) was dispersed in an aqueous methanol solution (10 mL of CH<sub>3</sub>OH and 90 mL of  $H_2O$ ) with magnetic stirring. The  $H_2$  yield was quantified by a gas chromatograph (GC) (SP-6890, Lunan Co., China) equipped with a thermal conductivity detector and Ar gas as the carrier.

#### References

- 1. Fujishima, A. & Honda, K. Photolysis-decomposition of water at the surface of an irradiated semiconductor. *Nature* 238, 37–38 (1972).
- 2. Ito, S. *et al.* High-efficiency organic-dye-sensitized solar cells controlled by nanocrystalline-TiO<sub>2</sub> electrode thickness. *Adv. Mater.* **18**, 1202–1205 (2006).
- Li, G. Z., Park, S., Kang, D. W., Krajmalnik-Brown, R. & Rittmann, B. E. 2,4,5-trichlorophenol degradation using a novel TiO<sub>2</sub>coated biofilm carrier: roles of adsorption, photocatalysis, and biodegradation. *Environ. Sci. Technol.* 45, 8359–8367 (2011).
- Chen, C. C., Ma, W. H. & Zhao, J. C. Semiconductor-mediated photodegradation of pollutants under visible-light irradiation. *Chem. Soc. Rev.* 39, 4206–4219 (2010).
- Yang, Z. X. et al. Synthesis of uniform TiO<sub>2</sub>@carbon composite nanofibers as anode for lithium ion batteries with enhanced electrochemical performance. J. Mater. Chem. 22, 5848–5854 (2012).
- 6. Ma, Y. et al. Titanium dioxide-based nanomaterials for photocatalytic fuel generations. Chem. Rev. 114, 9987-10043 (2014).
- 7. Bai, Y., Mora-Sero, I., De Angelis, F., Bisquert, J. & Wang, P. Titanium dioxide nanomaterials for photovoltaic applications. *Chem. Rev.* **114**, 10095–10130 (2014).
- 8. Liu, G. et al. Titanium dioxide crystals with tailored facets. Chem. Rev. 114, 9559-9612 (2014).
- Ohno, T., Sarukawa, K., Tokieda, K. & Matsumura, M. Morphology of a TiO<sub>2</sub> photocatalyst (Degussa, P25) consisting of anatase and rutile crystalline phases. *J. Catal.* 203, 82–86 (2001).
- Hurum, D. C., Agrios, A. G., Gray, K. A., Rajh, T. & Thurnauer, M. C. Explaining the enhanced photocatalytic activity of Degussa P25 mixed-phase TiO<sub>2</sub> using EPR. J. Phys. Chem. B 107, 4545–4549 (2003).

- Bickley, R. I., Gonzalezcarreno, T., Lees, J. S., Palmisano, L. & Tilley, R. J. D. A structural investigation of titanium-dioxide photocatalysts. J. Solid. State. Chem. 92, 178–190 (1991).
- 12. De Angelis, F., Di Valentin, C., Fantacci, S., Vittadini, A. & Selloni, A. Theoretical studies on anatase and less common TiO<sub>2</sub> phases: bulk, surfaces, and nanomaterials. *Chem. Rev.* **114**, 9708–9753 (2014).
- 13. Liao, Y. L. *et al.* Controllable synthesis of brookite/anatase/rutile TiO<sub>2</sub> nanocomposites and single-crystalline rutile nanorods array. *J. Mater. Chem.* **22**, 7937–7944 (2012).
- 14. Su, R. et al. How the anatase-to-rutile ratio influences the photoreactivity of TiO<sub>2</sub>. J. Phys. Chem. C 115, 24287-24292 (2011).
- Zhang, J., Xu, Q., Feng, Z., Li, M. & Li, C. Importance of the relationship between surface phases and photocatalytic activity of TiO<sub>2</sub>. Angew. Chem. Int. Ed. 47, 1766–1769 (2008).
- 16. Zhao, B., Lin, L. & He, D. N. Phase and morphological transitions of titania/titanate nanostructures from an acid to an alkali hydrothermal environment. *J. Mater. Chem. A* **1**, 1659–1668 (2013).
- 17. Li, G. H. *et al.* Synthesizing mixed-phase TiO<sub>2</sub> nanocomposites using a hydrothermal method for photo-oxidation and photoreduction applications. *J. Catal.* **253**, 105–110 (2008).
- Yan, M. C., Chen, F., Zhang, J. L. & Anpo, M. Preparation of controllable crystalline titania and study on the photocatalytic properties. J. Phys. Chem. B 109, 8673–8678 (2005).
- Kawahara, T., Ozawa, T., Iwasaki, M., Tada, H. & Ito, S. Photocatalytic activity of rutile-anatase coupled TiO<sub>2</sub> particles prepared by a dissolution-reprecipitation method. J. Colloid. Interf. Sci. 267, 377–381 (2003).
- 20. Xiong, G. *et al.* Photoemission electron microscopy of TiO<sub>2</sub> anatase films embedded with rutile nanocrystals. *Adv. Funct. Mater.* **17**, 2133–2138 (2007).
- 21. Liu, G. et al. Synthesis of rutile-anatase core-shell structured TiO2 for photocatalysis. J. Mater. Chem. 19, 6590-6596 (2009).
- 22. Huang, W. P., Tang, X. H., Wang, Y. Q., Koltypin, Y. & Gedanken, A. Selective synthesis of anatase and rutile via ultrasound irradiation. *Chem. Commun.* 1415–1416 (2000).
- Li, S. X., Chen, J., Zheng, F. Y., Li, Y. C. & Huang, F. Y. Synthesis of the double-shell anatase-rutile TiO<sub>2</sub> hollow spheres with enhanced photocatalytic activity. *Nanoscale* 5, 12150–12155 (2013).
- 24. Pan, L. *et al.* TiO<sub>2</sub> rutile-anatase core-shell nanorod and nanotube arrays for photocatalytic applications. *RSC Adv.* **3**, 3566–3571 (2013).
- Liu, B., Khare, A. & Aydil, E. S. TiO<sub>2</sub>-B/anatase core-shell heterojunction nanowires for photocatalysis. ACS Appl. Mater. Interfaces 3, 4444–4450 (2011).
- Wu, M. M. *et al.* Sol-hydrothermal synthesis and hydrothermally structural evolution of nanocrystal titanium dioxide. *Chem. Mater.* 14, 1974–1980 (2002).
- 27. Cong, S. & Xu, Y. M. Explaining the high photocatalytic activity of a mixed phase TiO<sub>2</sub>: a combined effect of O<sub>2</sub> and crystallinity. *J. Phys. Chem. C* **115**, 21161–21168 (2011).
- 28. Li, G. H. & Gray, K. A. Preparation of mixed-phase titanium dioxide nanocomposites via solvothermal processing. *Chem. Mater.* **19**, 1143–1146 (2007).
- Kho, Y. K. *et al.* Photocatalytic H<sub>2</sub> evolution over TiO<sub>2</sub> nanoparticles. the synergistic effect of anatase and rutile. *J. Phys. Chem. C* 114, 2821–2829 (2010).
- 30. Xia, T. *et al.* Directional heat dissipation across the interface in anatase-rutile nanocomposites. ACS Appl. Mater. Interfaces 5, 9883–9890 (2013).
- 31. Ju, M. G., Sun, G. X., Wang, J. J., Meng, Q. Q. & Liang, W. Z. Origin of high photocatalytic properties in the mixed-phase TiO<sub>2</sub>: a first-principles theoretical study. ACS Appl. Mater. Interfaces 6, 12885–12892 (2014).
- Zhang, X. et al. Interface junction at anatase/rutile in mixed-phase TiO<sub>2</sub>: formation and photo-generated charge carriers properties. Chem. Phys. Lett. 504, 71–75 (2011).
- Deskins, N. A., Kerisit, S., Rosso, K. M. & Dupuis, M. Molecular dynamics characterization of rutile-anatase interfaces. J. Phys. Chem. C 111, 9290–9298 (2007).
- 34. Gong, X. Q., Selloni, A., Batzill, M. & Diebold, U. Steps on anatase TiO<sub>2</sub> (101). *Nat. Mater.* **5**, 665–670 (2006).
- 35. Yang, H. G. et al. Anatase TiO<sub>2</sub> single crystals with a large percentage of reactive facets. Nature 453, 638-642 (2008).
- Zheng, W. J., Liu, X. D., Yan, Z. Y. & Zhu, L. J. Ionic liquid-assisted synthesis of large-scale TiO<sub>2</sub> nanoparticles with controllable phase by hydrolysis of TiCl<sub>4</sub>. ACS Nano. 3, 115–122 (2009).
- Zheng, Y. Q., Shi, E. W., Chen, Z. Z., Li, W. J. & Hu, X. F. Influence of solution concentration on the hydrothermal preparation of titania crystallites. J. Mater. Chem. 11, 1547–1551 (2001).
- Pottier, A., Chaneac, C., Tronce, E., Mazerolles, L. & Jolivet, J. P. Synthesis of brookite TiO<sub>2</sub> nanoparticles by thermolysis of TiCl<sub>4</sub> in strongly acidic aqueous media, J. Mater. Chem. 11, 1116–1121 (2001)
- Zhang, J., Li, M. J., Feng, Z. C., Chen, J. & Li, C. UV Raman spectroscopic study on TiO<sub>2</sub>. I. phase transformation at the surface and in the bulk. J. Phys. Chem. B 110, 927–935 (2006).
- 40. Scanlon, D. O. et al. Band alignment of rutile and anatase TiO2. Nat. Mater. 12, 798-801 (2013).
- Hung, W. C., Chen, Y. C., Chu, H. & Tseng, T. K. Synthesis and characterization of TiO<sub>2</sub> and Fe/TiO<sub>2</sub> nanoparticles and their performance for photocatalytic degradation of 1,2-dichloroethane, *Appl. Surf. Sci.* 255, 2205–2213 (2008).
- 42. Bian, Z. F., Tachikawa, T., Kim, W., Choi, W. & Majima, T. Superior electron transport and photocatalytic abilities of metalnanoparticle-loaded TiO<sub>2</sub> superstructures. J. Phys. Chem. C 116, 25444–25453 (2012).
- Yang, L. X. et al. High efficient photocatalytic degradation of p-nitrophenol on a unique Cu<sub>2</sub>O/TiO<sub>2</sub> p-n heterojunction network catalyst. Environ. Sci. Technol. 44, 7641–7646 (2010).
- 44. Yun, T. K. *et al.* Effect of the rutile content on the photovoltaic performance of the dye-sensitized solar cells composed of mixed-phase TiO<sub>2</sub> photoelectrodes. *Dalton Trans.* **41**, 1284–1288 (2012).
- Etacheri, V., Seery, M. K., Hinder, S. J. & Pillai, S. C. Highly visible light active TiO<sub>2-x</sub>N<sub>x</sub> heterojunction photocatalysts. *Chem. Mater.* 22, 3843–3853 (2010).
- Kim, W., Tachikawa, T., Moon, G. H., Majima, T. & Choi, W. Molecular-level understanding of the photocatalytic activity difference between anatase and rutile nanoparticles. Angew. Chem. Int. Ed. 53, 14036–14041 (2014).
- 47. Deak, P., Aradi, B. & Frauenheim, T. Band lineup and charge carrier separation in mixed rutile-anatase systems. *J. Phys. Chem.* C 115, 3443–3446 (2011).
- Yang, L. X. et al. High efficient photocatalytic degradation of p-Nitrophenol on a unique Cu<sub>2</sub>O/TiO<sub>2</sub> p-n heterojunction network catalyst. Environ. Sci. Technol. 44, 7641–7646 (2010).
- 49. Zhu, Q. et al. Stable blue TiO<sub>2-x</sub> nanoparticles for efficient visible light photocatalysts. J. Mater. Chem. A 2, 4429–4437 (2014).
- Kamegawa, T., Matsuura, S., Seto, H. & Yamashita, H. A visible-light- harvesting assembly with a sulfocalixarene linker between dyes and a Pt-TiO<sub>2</sub> photocatalyst. Angew. Chem., Int. Ed. 52, 916–919 (2013).
- Guo, W. X. *et al.* Rectangular bunched rutile TiO<sub>2</sub> nanorod arrays grown on carbon fiber for dye-sensitized solar cells. J. Am. Chem. Soc. 134, 4437–4441 (2012).

#### Acknowledgements

This work is partially supported by the National Basic Research Program of China (2011CB933702), the Natural Science Foundation of China (51538011), and the Program for Changjiang Scholars and Innovative Research

Team in University and the Collaborative Innovation Center of Suzhou Nano Science and Technology of the Ministry of Education of China.

#### **Author Contributions**

W.K.W., J.J.C., X.Z. and H.Q.Y. designed the experiments; W.K.W. carried out the experiments and characterization. W.K.W., J.J.C., X.Z. and Y.X.H. guided the work and analysis; H.Q.Y. contributed to the planning and coordination of the project; W.K.W, J.J.C., W.W.L. and H.Q.Y. wrote and edited the manuscript. All authors contributed to discussion about the results and the manuscript.

#### Additional Information

Supplementary information accompanies this paper at http://www.nature.com/srep

Competing financial interests: The authors declare no competing financial interests.

How to cite this article: Wang, W.-K. *et al.* Self-induced synthesis of phase-junction  $TiO_2$  with a tailored rutile to anatase ratio below phase transition temperature. *Sci. Rep.* **6**, 20491; doi: 10.1038/srep20491 (2016).

This work is licensed under a Creative Commons Attribution 4.0 International License. The images or other third party material in this article are included in the article's Creative Commons license, unless indicated otherwise in the credit line; if the material is not included under the Creative Commons license, users will need to obtain permission from the license holder to reproduce the material. To view a copy of this license, visit http://creativecommons.org/licenses/by/4.0/